Journal of Mines, Metals and Fuels, *71(12C) : 193-196; 2023. DOI: 10.18311/jmmf/2023/47310*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.com/index.php/jmmf*

Review and Study on 3D Printed Technology Using Biomaterials for Hip Prosthesis Applications

Syed Zameer and S. K. Moinuddin*

Department of Mechanical Engineering, Ghousia college of Engineering, Ramanagaram - 562159, Karnataka, India; moinuddinsk88@gmail.com

Abstract

There is a developing interest in imaginative ways to deal with address the substitution and recuperating of bones and organs in patients experiencing sicknesses like cracks or hip-related illnesses. Hip replacement procedures heavily rely on the choice of implant material, which may not in every case meet necessities due to mechanical and biocompatibility issues, potentially exacerbating inflammation. To conquer these limits, specialists are investigating the utilization of different biomaterials as an option for inserts. Three-dimensional (3D) printing emerges as a promising and efficient manufacturing method for hip replacement applications due to its biocompatibility with the human body. This survey delves into the factors determining hip replacement, examining various production techniques, including direct 3D printing, Melded Affidavit Displaying (FDM), specific Stereolithography (SLA), and Selective Laser Sintering. The concentrate additionally includes surface adjustments of 3D-printed embeds and gives an outline of 3D tissue recovery. This review discusses challenges, issues, also, patterns in 3D printing for inserts, drawing conclusions and presenting limitations and challenges. The gathered information underscores the significant potential of 3D printing in facilitating affordable hip replacement solutions. The research spans key domains, including mining, minerals, metallurgy, and the bio-polymer composite industry, addressing scientific and technical challenges pertinent to the metallurgy of polymer matrix composites.

Keywords: Biomaterials, 3D Printing Technology, Hip Joint, Processing Techniques

1.0 Introduction

Fused Deposition Modelling (FDM) has proven effective in manufacturing parts of short fiber-supported polymer composites that as it may, on the ground that the naturally confined mechanical properties of structure polymers, there is a fundamental neediest further develop fiber-upheld predominant execution of composites for 3D printing to broaden planning purposes. Hence the investigation study focuses on technology and innovation in the mining field and newly developed biomaterials.

The review investigates the capability of 3D printing for the smallest Carbon Fiber (CF) upheld superior execution composite materials. Composite strands with fiber items in 5wt%, 10wt%, and 15wt% were arranged utilizing the expulsion cycle and portrayed through micro morphology perception. Combined Testimony Demonstrating (FDM) has turned into a norm in 3D printing, utilizing thermoplastic filaments as feedstock and layering them methodically by storing material from a warmed spout as per the modified way created by cutting programming. The expansion of short or constant strands into a thermoplastic grid improves mechanical properties fundamentally and is more practical and doable than ceaseless fiber application. Baroli *et al.*, examined the essential kinds of biomaterials utilized in tissue designing, extensively sorted as engineered polymers *e.g.*, poly(lactic-co-glycolic) corrosive, poly

*Author for correspondence

anhydrides, and others[1]. Normally happening polymers like complex sugars (chitosan) and inorganics are additionally referenced alongside functional solutions like hydro circumstances[4,5].

Regarding biocompatibility, Kohane *et al*., emphasized its significance but noted that it depends on the biological environment[6]. Anderson *et al*., highlighted the potential harmful effects of local tissue response to biomaterials, even without an immune-mediated response[7]. Bostman *et al*., examined issues connected with the breakdown of biomaterials, which can prompt entanglements[8], while Yeo *et al*., emphasized the importance of considering the possible poisonousness of materials breakdown items and unreacted cross-linking agents[9].

Fukuda *et al*., cautioned that a materials clear absence of cytotoxicity doesn't ensure biocompatibility, citing an illustration of cross-linked chitosan causing adhesions *in vivo* despite minimal toxicity *in vitro*[11]. Karp *et al*., examined the idea of biodegradability in tissue designing, underscoring that materials frequently disappear once their planned capability is satisfied[12].

In conclusion, the research underscores the potential of FDM-3D printing for advanced composite materials and the diverse considerations in biomaterials for tissue engineering, ranging from mechanical properties to biocompatibility and biodegradability.

2.0 Experimental Work

This review chose High-thickness Polyethylene (HDPE), an arising thermoplastic polymer for FDM-3D printing, as the framework material. HDPE has a thickness of 1.3g/cm^3. Before mixing, carbon fiber went through medicines of anodic oxidation and silane coupling specialists independently. These methods are regularly used to work on the holding between the fiber and lattice. Anodic oxidation treatment expanded the surface unpleasantness of the support, additionally increasing the quantity of oxygen useful gatherings on the external layer of carbon fiber.

The composite definitions, with fiber items in 5wt%, 10wt%, and 15wt% (fiber or HDPE), were resolved involving the standard of blend for composites. HDPE and strands were effectively mixed in a high-temperature extruder to make composite fibers. At the same time expulsion cycle, the temperature of the extruder, fiber yielded speed, and rope broadness were set at 155 °C, 1.35 m/min, and 2.5 mm, separately. Thus, the fibers were continuously reduced temperature, formed by strands, and cut into small pieces. These pellets were then dried for ensuing expulsion utilizing a solitary screw extruder. Through two expulsion processes, composite filaments loaded up with uniformly conveyed strands were acquired. The fiber breadth was exactly controlled at 1.75 mm utilizing a modified pass on and a programmed pressure control framework. The course of readiness of fiber is as displayed in Figure 1.

The pre-arranged composite filaments went through drying in a stove as a planning step for 3D printing. A FDM-3D printer, situated at Indian Tech Keys in Bangalore, was utilized to manufacture test tests of fiber or HDPE composite examples.

The created tests were printed by the printing boundaries framed in Table 1 to evaluate mechanical characters, including flexural strength and unyielding nature. These examples were additionally used to dissect thickness and micromorphology.

The solidness and flexural strength were estimated utilizing an auto-controlled testing machine at the colleges material trying exploration lab, furnished with a 10 KN force transducer and a stacking pace of 2 mm/min. To assess the level of porosity, Archimedes standard was utilized, measuring the compactness of raw fibers, what's more, parts printed by machine. This method




Figure 1. Interaction of composite fibers readiness.

Table 1. FDM 3D printing parameters for composites

3D Printing Criterion	Value
Nozzle diameter	0.4
Nozzle temperature	265^0 C
Thickness of layers	0.25 mm
Printing velocity (mm/s)	14
Infill density	100

allows for assessing the material's porosity by comparing the densities of the actual printed parts with the densities of the solid fibers.

3.0 Morphological Observation

The microstructures of fiber cross-segments and cracked surfaces were investigated utilizing a Filtering Electron Magnifying lens (SEM) to notice inside deserts and look at their tendency. Also, the fiber morphology was examined using SEM. Figure 2 delineates the pliable crack surface of 3D printed CF or HDPE with differing fiber weight portions.

4.0 Results and Discussions

The characteristics of the threads, including type, appeased, and length, generally influence the show of composite rolls as well as printed parts. Figure 3 portrays the thorough mechanical properties of 3D printed short threads composites. The impact of thread type and thread weight part on the immovability, flexural durability, and impact durability of composite models is depicted. It is fundamental that the versatility what's more, flexural durability of 3D printed composite specimens in this order of assessments are by and large worked on appear differently in relation to those without fiber support. Besides, consideration regarding prolongation at break shows that the decrease in malleability brings about diminished adaptability. This is credited to the short strands upsetting the coordinated course of action of polymer chains, causing the polymer chains to break all the more without any problem. The sort and content of filaments essentially affect the augmentation at the break point of the sample. All malleable cracks of fiber-upheld composites show weakness contrasted with adaptability with necking qualities.




Figure 2. SEM of malleable crack surface for CF or HDPE.




Figure 3. Stretching out at the break point of 3D printed threads-maintained composites.




Figure 4. Porosity of fibers and printed leaves behind changed fiber contents.

5.0 Microstructural and Porosity

To additionally evaluate the disappointment component, the broken exterior of printed threads specimens examples was analyzed utilizing SEM, as outlined in Figure 4. It will, in general, be seen that with an expansion in fiber content, the quantity of strands on the cracked segment increments, and porosity creates, as shown in the Figure. Enormous air pores are obvious among stacked ways furthermore, layers in the FDM cycle. Past evaluations have shown that porosity plays a crucial part in the mechanical prospects of 3D-printed fiber-maintained polymer composites. The impact of fiber type and fiber contended on the porosity of fibers and printed composite specimens was solely explored utilizing Archimedes standard. Further assessment uncovers that the expansion in porosity brought about by the fiber planning process is roughly 5%, while a 10% increment is credited to the FDM cycle for fiber-upheld composites.

6.0 Conclusions

The conclusions drawn from the research work carried out: In this understanding, 3D printing extrusion was employed to fabricate fiber-reinforced HDPE composites

with varying percentages of carbon fiber, going from 5wt% to 15wt%. Far-reaching assessments were directed at the cross-sectional morphology and crystallinity of the composite filaments. The accompanying ends can be drawn in light of the exploration results.

Improved fiber-matrix interface: The CF or HDPE composites exhibit enhanced fibre-matrix interfacial bonding, attributed to additional active functional groups on Carbon Fibers (CF). This contributes to better overall performance. The mechanical parameters of the composite materials decrease as the level of fiber weight increases. Despite this decline, the stiffness and flexural strength of the fabricated printed samples remain superior to those of pure HDPE.

These findings highlight the trade-offs between increased fiber content and certain mechanical properties, emphasizing the importance of optimizing the composition to achieve the desired balance of strength and flexibility in the printed composite materials. The exploration study was connected with innovative work in science, innovation and designing polymeric and polymer-based materials.

7.0 References

1. Baroli B. Hydrogels for tissue engineering and delivery of tissue-inducing substances. J Pharm Sci. 2007; 96(9):2197–2223. https://doi.org/10.1002/jps.20873
2. Kretlow JD, Klouda L, Mikos AG. Injectable matrices and scaffolds for drug delivery in tissue engineering. Adv Drug Deliv Rev. 2007; 59(4-5):263–73. https://doi.org/10.1016/j.addr.2007.03.013
3. Chung HJ, Park TG. Surface engineered and drug-releasing pre-fabricated scaffolds for tissue engineering. Adv Drug Deliv Rev. 2007; 59(4-5):249–62. https://doi.org/10.1016/j.addr.2007.03.015
4. Ma Z, Mao Z, Gao C. Surface modification and property analysis of biomedical polymers used for tissue engineering. Colloids Surf B Biointerfaces. 2007; 60(2):137–57. https://doi.org/10.1016/j.colsurfb.2007.06.019
5. Domb A, Mikos AG. Matrices and scaffolds for drug delivery in tissue engineering. Adv Drug Deliv Rev. 2007; 59(4-5):185–6. https://doi.org/10.1016/j.addr.2007.05.001
6. Kohane DS, Tse JY, Yeo Y, Padera R, Shubina M, Langer R. Biodegradable polymeric microspheres and nanospheres for drug delivery in the peritoneum. J Biomed Mater Res A. 2006; 77A(2):351–61. https://doi.org/10.1002/jbm.a.30654
7. Anderson JM. *In vivo* biocompatibility of implantable delivery systems and biomaterials. Eur J Pharm Biopharm. 1994; 40:1–8.
8. Bostman O, Pihlajamaki H. Clinical biocompatibility of biodegradable orthopaedic implants for internal fixation: A review. Biomater. 2000; 21(24):2615–21. https://doi.org/10.1016/s0142-9612(00)00129-0
9. Ito T, Yeo Y, Highley CB, Bellas E, Benitez CA, Kohane DS. The prevention of peritoneal adhesions by *in-situ* cross-linking hydrogels of hyaluronic acid and cellulose derivatives. Biomater. 2007; 28(6):975–83. https://doi.org/10.1016/j.biomaterials.2006.10.021
10. Yeo Y, Burdick JA, Highley CB, Marini R, Langer R, Kohane DS. Peritoneal application of chitosan and UV-cross-linkable chitosan. J Biomed Mater Res A. 2006; 78A(4):668–75. https://doi.org/10.1002/jbm.a.30740
11. Fukuda J, Khademhosseini A, Yeo Y, Yang X, Yeh J, Eng G, Blumlimg J, Wang CF, Kohane DS, Langer R. Micromolding of photocrosslinkable chitosan hydrogel for spheroid microarray and co-cultures. Biomater. 2006; 27(30):5259–67. https://doi.org/10.1016/j.biomaterials.2006.05.044
12. Karp JM, Yeo Y, Geng W, Cannizarro C, Yan K, Kohane DS, Vunjak-Novakovic G, Langer R, Radisic M. A photolitographic method to create cellular micropatterns. Biomater. 2006; 27(27):4755–64. https://doi.org/10.1016/j.biomaterials.2006.04.028
13. D790 ASTM standard test method for flexural properties of unreinforced and reinforced plastics and electrical insulating materials. Annu B ASTM Stand. 2010; 10:1–11.
14. D6110-18 ASTM standard test method for determining the charpy impact resistance of notched specimens of plastics. Annu B ASTM Stand. 2018.
15. Zar G, Haberer M, Park CB, Benhabib B. Mechanical properties of short-fibre layered composites: prediction and experiment. Rapid Prototyp J. 2000; 6(2):107-18. https://doi.org/10.1108/13552540010323583
16. D638 ASTM standard test method for tensile properties of plastics. Annu B ASTM Stand. 2010; 10:1–16.