Journal of Mines, Metals and Fuels, *72(11): 1215-1223; 2024. DOI: 10.18311/jmmf/2024/45579*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.co.in/index.php/jmmf*

An Analysis of Nanoparticles in Composite Materials

Chaitalee Mali[1], Kamalkishor Maniyar[1]*, Shobha Rupanar[2], Aarti Jathar[1], Beena Nawghare[1], Nirmala Kakade[3], Girish Modak[4], Vijay Bhambere[5], Swapnil Deshmukh[1], Jagannath Gawande[6] and Ramdas Biradar[7]

[1]Dr. D. Y. Patil Institute of Technology, Pimpri, Pune - 411018, Maharashtra, India; kkmaniyar2020@gmail.com
[2]Ajeenkya D. Y. Patil School of Engineering, Lohegaon - 412105, Maharashtra, India
[3]Dadapatil Rajale Arts and Science College, Ahmednagar - 414001, Maharashtra, India
[4]PES Modern College of Engineering, Pune - 411005, Maharashtra, India
[5]Jagadambha College of Engineering and Technology, Yavatmal - 445001, Maharashtra, India
[6]Savitribai Phule Pune University (SPPU), Pune - 411007, Maharashtra, India
[7]Pimpri Chinchwad University, Pune - 412106, Maharashtra, India

Abstract

A blend of various materials with nano-scale dimensions is called a nanocomposite. Combining the qualities of various materials to create a unique nanomaterial with improved and increased chemical and physical capabilities is the goal of creating nanocomposites. The characteristics of nanocomposites and raw materials are very different. On comparing nanocomposites to standard composite materials, a big surface area and a remarkable surface-to-volume ratio are seen. Environmental professionals have taken an interest in these composite materials, particularly in relation to their ability to remove pesticides from various samples. This is mostly due to the many special qualities that the nanomaterials which help with pesticide remediation offer. The necessity of composite materials above conventional materials is demonstrated by this study. Composite parts are produced in several industries using various moulding techniques. The main benefits of composites are their relative stiffness, strength and lightweight. The physical characteristics, material qualities, design, tooling, inspection and repair of composites are its fundamental ideas. Strong, lightweight materials are crucial for military vehicles like rockets, helicopters and aeroplanes. In terms of mechanical qualities, the metallic components that had been utilised until that point undoubtedly performed the job, but their large weight was prohibitive. The polymer industry was expanding rapidly and aimed to broaden the market for plastics to include a wider range of applications. A potential remedy was provided by the introduction of novel, lightweight polymers from research and development facilities.

Keywords: *Characteristics, Composite Materials, Conventional Materials, Properties and Applications*

1.0 Overview of Nanoparticles in Composites

A composite is a material mixture consisting of two or more distinct components combined to produce qualities that outperform those of their components. A multiphase solid material with one, two, or three dimensions less than 100nm is called a nanocomposite, as is a structure with recurring nanoscale intervals between the various phases that comprise the material. The basic constituents of nanocomposites are several nanomaterials or nanomaterials integrated into a different bulk material. Organic-organic, inorganic-inorganic and inorganic-inorganic phases can occur in nanocomposites.

**Author for correspondence*

Nanoparticles can be used to create nanocomposite materials, such as nanofilled or nanohybrid composites. In comparison to conventional composites, nanocomposites exhibit superior finishing, polishing ability, shade matching, flexural strength and hardness.

Human needs inspire inventions. Humans first simply used the materials that were found in their immediate environment. Animal pelts were used as clothes and wood and stones served as tools. After that, they learnt how to weave textiles using natural fibres like cotton and silk. With time they learnt how to create various hunting tools out of iron and copper. Over the past 200 years, there has been a significant advancement in technology and a corresponding rise in human understanding of science. The process of creating unique synthetic materials like plastics has been mastered by scientists. Plastic can be natural or manmade, inorganic or organic. But increasingly, the term is used to describe synthetic organic plastics, which are essentially polymers. The main components of each monomer are hydrogen and carbon. They occasionally could include other elements including silicon, nitrogen, oxygen and chlorine. The majority of the polymers are incredibly lengthy chains that are occasionally branching and occasionally linear. This occurs because carbon atoms mix readily with a wide variety of other atom types as well as with one another. In lengthy chains, they can establish robust connections. "Two inherently different materials that when combined produce a material with properties that exceed the constituent materials" is the definition of a composite. Put another way, a composite material is made up of a reinforcement and a matrix that, when combined, provides qualities that are better than those of each component alone. The qualities of the resultant composite can be altered by varying the cutting, aligning and placement of the reinforcement fibres. The reinforcement is kept in the intended orientation by the matrix, which is often a type of resin. It ties the reinforcement together to provide for the efficient transfer of applied loads while shielding it from chemical and environmental damage.

2.0 Literature Survey

Polymer composites have found extensive application in the industry in recent times owing to their exceptional mechanical qualities, resistance to lightening, and light weight[1]. They are now more useful than metals due to these characteristics[2]. Owing to its low weight, low production cost, high thermal deflection temperature and renewability, Polypropylene (PP) is a significant and extensively used thermoplastic[3,4]. PP demonstrates excellent mechanical, thermal and physical characteristics when utilised at room temperature. Improved polymeric materials, which are challenging to obtain by direct polymerisation procedures, can frequently be obtained by the convenient method of blending polymers[5,6]. Today, nanomaterials play a major role in several sectors. To reinforce nanocomposites, nanomaterials are utilised. These nanomaterials include nanographene, nano silica, carbon nanotubes and clay nanotubes[7-9].

Mechanical characteristics of carbon nanotubes were examined[10-12]. Graphene sheets have the appearance of honeycombs because graphene is a single layer of closely bonded carbon atoms. The application of graphene has expanded due to its special qualities, which include excellent bonding between the filler particles and the polymer matrix, a strong filler-matrix interface, high specific surface area and high Young's modulus[13]. The structural properties and manufacturing of graphene/PP nanocomposites were investigated[14]. Evidently, PP's modulus of elasticity is enhanced when 0.5-weight percent graphene is added to it. Digital light processing[15] produced high-strength nanocomposites reinforced with graphene that were net-shaped and intended for use in intricate 3D constructions.

It was discovered that the modulus of elasticity of PP greatly increased with the addition of 5-weight percent graphene. The mechanical and thermal properties of graphene oxide-loaded PP composites were evaluated[16]. They came to the conclusion that PP's tensile strength and Young's modulus dramatically improved by 42% and 71%, respectively, when graphene oxide was added[17]. Also looked at the usage of graphene to improve the mechanical behavior of composites. Tensile, morphological and thermal properties were examined in the samples and it was discovered that the tensile qualities of the PP were enhanced by the addition of a small amount of graphene.

PP nanocomposites reinforced with carbon fiber and calcium carbonate nanoparticles were created and their mechanical properties were compared[18]. They discovered that, in comparison to nanocomposites without

nanoparticles, the impact strength of those containing calcium carbonate nanoparticles was increased. They ascribed this rise to the calcium carbonate and two-phase PP adhesion being strong and homogenous in structure. Better tensile qualities were obtained when 1 weight per cent of graphene oxide was added to PP, according to[19], which supports the results of our work. Additionally[20], investigated the thermal and mechanical properties of graphene oxide-reinforced PP nanocomposites. The addition of 0.1%, 0.3% and 0.5% AGO increased the Young's polymer modulus by 20%, 30% and 34%, respectively.

Additionally, pure PP caused a 2, 8 or 12°C rise in the 10% mass reduction temperature for AGO nanocomposites at 0.1%, 0.3% and 0.5%, respectively. Layered silicates are prevalent nanofillers used in polymers. Silicate nanocomposites are less heavy than conventional composites due to their reduced mineral phase, making them suitable as alternatives for these composites in a variety of applications[21,22]. The impact of adding nano clay to steel-polyurea bi-layer plates on their ability to absorb energy was investigated[23]. It was determined that adding 1 weight per cent of nano clay to polyuria increased the modulus of elasticity by almost sixty per cent. Researchers[24] looked into the mechanical properties of hybrid polyethene-based nanocomposites that were nano perlite and nano clay reinforced.

They claimed that adding 7-weight percent more nanoparticles to the polyethylene matrix produced a uniform distribution of the particles and increased tensile strength. Additionally, the composites containing 5-weight percent nano clay and 2-weight percent nano perlite had a modulus of elasticity that was almost twice that of pure polyethylene. These days, fibres are employed in a wide range of composite materials to strengthen them against different loads. These fibre-reinforced composites find employment in numerous applications across numerous industries[25-28]. Basalt is one of the eco-friendly fibres. Basalt fibres provide excellent heat tolerance, sufficient corrosion resistance and good flexibility and resilience. There are several uses for them[29]. For example, exterior bonding sheets made of basalt-reinforced composites are employed in post-earthquake cleanup and strengthening[30,31].

Lopresto *et al*. explored the mechanical characteristics of polyethylene reinforced with basalt[32]. They prepared their samples using vacuum technology, and they performed tensile testing using a universal machine. They discovered that basalt reinforcement produced superior mechanical qualities compared to reinforcement using other types of fibres. A study[33] that looked at the fatigue behaviour and resistance of composite materials reinforced with basalt, glass and carbon fibres concluded that the potential for fatigue tolerance was boosted by carbon/basalt composites.

Studies[34] focused on the characterisation of contemporary basalt-reinforced composite materials and contended that the mechanical qualities of composites reinforced with epoxy resin were superior to those reinforced with vinyl ester.

Basalt was employed[35] as a concrete reinforcement material. The basalt-reinforced concrete's flexural structure seemed to have contributed to the material's good serviceability and high compressive strength. The behaviour of polymer composites reinforced with basalt was studied[36]. They compared them with carbon fibre-reinforced polymer plates, concentrating on the primary low-velocity impact metrics of energy absorption, initial maximum force and deformation. Their findings demonstrated that basalt fibres' exceptional toughness explained why the plates reinforced with these fibres performed significantly better than those reinforced with carbon fibres. Manufacturing basalt fibres requires fewer resources and is more affordable than producing glass or carbon fibres, which is another important advantage[37,38]. The mechanical behaviour of basalt-reinforced PP/ clay nanocomposites was observed and it was[39] concluded that the final strength and modulus of elasticity rose considerably because of the strong resilience of basalt. Author in[40] investigated the mechanical characteristics of polymers reinforced with basalt. The results showed that the samples had a modulus of elasticity, fracture strain and tensile stress of 77.9 GPa, 0.021 and 1642.2 MPa, respectively.

2.1 Literature Summary

It was discovered that the properties of the nanocomposites are very different from those of the basic ingredients after conducting an exploratory analysis of the literature survey. When nanocomposites are compared to traditional composite materials, the huge surface area and remarkable surface-to-volume ratio are noted.

These composite materials have attracted interest from environmental professionals due to their ability to remove pesticides from a range of samples. The main reason for this is the abundance of special and advantageous qualities of the nanomaterials used to help with pesticide cleanup. The superiority of composite materials over traditional materials is demonstrated by this work. Many businesses use various moulding techniques to create composite goods. One of the main benefits of composite materials is their relative rigidity. They are also lightweight.

3.0 Benefits of Nanoparticles in Composites

Composite materials provide several advantages over conventional materials utilised today, such as wood and metal. Lightweight, somewhat stiff and strong qualities are the main benefits of composites. Less weight during transportation means better acceleration and more fuel savings. Longer golf drives, quicker tennis swings and straighter archery shots are all made possible by lightweight composite sports equipment. The more electricity a wind turbine can generate, the lighter each blade must be. Rubber bands have taken the place of wooden wheels, clothing made of bright nylon or polyester is starting to replace cotton and lighter tennis rackets are preferred over the old, bulky wooden ones. Carbon-fiber reinforced composite, for instance, can weigh only 5% of the weight of 1020-grade steel while having a strength of five times greater. Carbon-fiber composites can have up to seven times the strength and twice the modulus of aluminium (6061 grade), despite aluminium being significantly lighter overall. Metals, polymers, ceramics, inorganic glasses and composites are some of the categories into which materials are divided. Iron and steel become weaker at high temperatures. Lower temperatures are often not a problem for high-polymeric materials. Because of their brittleness, ceramics and polymers are not as structural materials as other materials despite having strong strength, thermal expansion characteristics, and temperature tolerance. In general, composites fall into



Figure 1. Illustrates the benefits of nanoparticles in composites.

the following categories: Fiber Composites: The length of the fibres is reinforced. Composite Particles: Particles that provide support to a matrix. Particles that are randomly distributed throughout a matrix have an equal tendency to reinforce in all directions such as plastics and former cement. Composites made of flakes: Flakes are often reinforced in two dimensions due to their form. Mica and glass are common materials for flake. Laminar Composites (layered): these composites consist of two or more layers made of the same material or a different one. To provide strength, the layers can be placed in various ways. Composites that have been combined: Multiple materials can be incorporated into a single composite. It is also feasible to create a single product by combining multiple distinct composites.

With respect to traditional composites, nanocomposites have the following advantages:

Enhanced rigidity, increased toughness enhanced flexural strength, excellent polish retention, greater transparency, special qualities for handling and reduced shrinkage during polymerisation (in polymer-based nanocomposites application).

4.0 Methods of Fabrication of Nanoparticles in Composites

The process of creating nanoparticles and creating metal, ceramic, and polymeric nanocomposites. A variety of nanoparticle synthesis techniques, including sol-gel, microwave, pulse laser ablation, coprecipitation, hydrothermal synthesis, inert gas condensation, ion sputtering scattering, microemulsion, spark discharge, template synthesis, biological synthesis, spray pyrolysis, liquid infiltration, rapid solidification, high-energy ball milling, chemical vapour deposition, physical vapour deposition, and colloidal and sol-gel chemical processes are some of the methods used in the synthesis of metal nanocomposites. The powder, polymer precursor and sol-gel processes are used in the production of ceramic nanocomposites. Lastly, intercalation, melt intercalation, *in situ* intercalative polymerisation, template synthesis, mixing, *in situ* polymerisation and the sol-gel method are all involved in the creation of polymer nanocomposites. Considering their little history, composite materials have achieved remarkable success. Ceramics need to overcome specific challenges, particularly in structural applications. In the composite sector, there are several modifications related to cost. Operations for Molding: Many composite products are produced by using moulding operations. Press moulding, transfer moulding, winding, casting, centrifugal casting, continuous casting, and slip forming are examples of other fabrication techniques and filament pultrusion moulding. Additionally, forming capabilities include wet lay-up, vacuum infusion, CNC thermoplastic filament winding, and compression moulding[10].

5.0 Usage of Nanoparticles in Composites

Due to their special blend of qualities, composite materials have a high strength-to-weight ratio or are lightweight. Enhanced resilience, weariness, rigidity and functional superiority, such as improved anti-friction, electrical insulation and resistance to weathering, fire, and corrosion The variety or ease of fabrication methods increased robustness and reduced upkeep costs Composites are regarded as extremely important raw materials for many different industries. Composite materials are of great interest to the automotive and transportation industries due to their potential to increase fuel economy through vehicle weight reduction. Thus, for automotive parts involving friction, industrialised nations like Japan are heavily utilising graphite-dispersed aluminium composites. Worldwide, composite materials have a long history of use in road and railroad transportation. When it comes to manufacturing three-wheeled vehicles for the disabled, commercial vehicles (trucks and cabs), automobile bodies, sports cars, buses, ambulances, caravans, mobile stores, etc. abroad, glass fiber-polyester epoxy composites are typical materials of choice. Due to weight savings and the requirement for affordable, weather-resistant streamlined fairings, Glass Reinforced Plastic (GRP) is also utilised in the motorbike and scooter industries. In aircrafts, composite materials are mostly utilised for dielectric panels and radomes, with secondary applications including doors, ring tips, ducting and fairing structures. Due to their superior mechanical and electrical qualities, epoxy resin and e-glass rovings are the materials used to make walls. The method used is called polar winding. Lightweight resistance to corrosion resistance, fatigue ability to mould intricate and massive objects, ability to preserve alignment and dimensional

stability, the potential for minor dielectric loss and a high degree of optimisation capability are some of the benefits. Some of the drawbacks are de-lamination (occurs when the laminate separates at the interface between two layers due to shock, impact, or recurrent cyclic pressures and fibres can come apart from the matrix individually), absorption of moisture, weak laminated structure and high likelihood of production flaws. Composites have comparatively low bearing strengths when compared to metals. The majority of the aerospace industry employs composites as raw materials while using autoclave manufacturing. Glass fibre composites are utilised for aeroplanes flying at low speeds. Conversely, metallic conventional tooling is preferred for large numbers of components. Resign injection moulding is utilised for unique items like radomes. A radome is a shield that reduces distortion and loss in electromagnetic signal transmission. A radome's uniform electrical thickness and wavelength must match the radar equipment it will be used with, as these are the most crucial specifications.

6.0 Findings

The applications being investigated by the following survey of nanocomposite applications include: Generating batteries with higher energy output. A technique involving the formation of a composite of silicon nanospheres and carbon nanoparticles has been devised by researchers to create anodes for lithium-ion batteries. Faster charging and discharging of power is possible because of the tighter contact between the silicon-carbon nanocomposite anodes and the lithium electrolyte; Accelerating the healing of fractured bones: Studies have demonstrated that the implantation of a nanotube-polymer nanocomposite as a sort of scaffold to direct the formation of replacement bone accelerates the process of bone regrowth. The goal of the research is to learn more about how this nanocomposite promotes bone formation. Manufacturing structural elements with a high ratio of strength to weight. For instance, carbon nanotube-containing epoxy can be utilised to create composite windmill blades made of nanotubes and polymers. This produces a lightweight but robust blade, making longer windmill blades useful. Each windmill can produce more electricity thanks to these longer blades utilising graphene to create composites with even greater ratios of strength to weight. Compared to epoxy composites employing a similar weight of carbon nanotubes, components made with graphene may be stronger or stickier, according to research. It seems that graphene adheres more firmly to the epoxy's polymers, facilitating a more successful integration of graphene into the composite's structure. This characteristic may lead to the production of parts with greater strength-to-weight ratios for applications like aircraft or windmill blades. Using nanocomposites to create lightweight sensors. The electrical conductivity of a polymer-nanotube nanocomposite is dependent on the nanotube spacing. Because of this characteristic, polymer-nanotube nanocomposite patches on windmill blades can function as stress sensors. Strong gusts of wind will cause the material to bend along with the blades. The electrical conductivity of the nanocomposite sensor is altered by bending, which sets off an alarm. The windmill could be turned off thanks to this alarm before significant damage was done. Making flexible batteries with nanocomposites. A conductive paper might be created by combining nanotubes and cellular materials in a nanocomposite.

7.0 Conclusion

This comprehensive study of nanoparticles in composites helps to choose the right matrix and fibre and also obtain the optimum performance of nanocomposites which is essential for a successful design since such materials provide countless design possibilities. Today, nanocomposite materials are used in many aspects of daily life. A quality nanocomposite material can be created by carefully choosing the raw materials and using the proper production processes. To satisfy the needs of the end user, nanocomposite material structures can be created with certain features. Utilising nanocomposites suggests the ideal combination of the lowest structural weight and production cost. The development of novel nanocomposite materials to replace traditional composite materials has been the subject of several studies both past and present.

8.0 References

1. Moskaleva A, Safonov A, Hernández-Montes E. Fiber-Reinforced polymers in freeform structures: A review.

Adv Build. 2021; 11:481. https://doi.org/10.3390/buildings11100481
2. Zabihi O, Ahmadi M, Nikafshar S, Preyeswary KC, Naebe MA. A technical review on epoxy-clay nanocomposites: Structure, properties and their applications in fiber reinforced composites. Compos. Part B Eng. 2018; 135:1-24. https://doi.org/10.1016/j.compositesb.2017.09.066
3. Selvakumar V, Palanikumar K, Palanivelu K. Studies on mechanical characterization of polypropylene/Na+-MMT nanocomposites. J Miner Mater Charact Eng. 2010; 9:671-81. https://doi.org/10.4236/jmmce.2010.98048
4. Gabr M, Okumura W, Ueda H, Kuriyama W, Uzawa K, Kimpara I. Mechanical and thermal properties of carbon fiber/polypropylene composite filled with nano clay. Compos Part B Eng. 2015; 69:94-100. https://doi.org/10.1016/j.compositesb.2014.09.033
5. Paul DR, Bucknall CB, Polymer blends. Wiley, New York, NY, USA. 2000.
6. Karger-Kocsis J. Thermoplastic rubbers via dynamic vulcanization. In Polymer blends and alloys. Shonaike GO, Simon GP, Editors. New York, NY, USA: Marcel Dekker; 1999.
7. Seifan M, Mendoza S, Berenjian A. A comparative study on the influence of nano and microparticles on the workability and mechanical properties of mortar supplemented with fly ash. Adv Build. 2021; 11:60. https://doi.org/10.3390/buildings11020060
8. Zarabimanesh Y, Saffari PR, Refahati N. Hygro-thermo mechanical vibration of two vertically aligned single-walled boron nitride nanotubes conveying fluid. J Vib Control. 2021. https://doi.org/10.1177/10775463211006512
9. Roodgar Saffari P, Fakhraie M, Roudbari MA. Size-dependent vibration problem of two vertically-aligned single-walled boron nitride nanotubes conveying fluid in thermal environment via nonlocal strain gradient shell model. J Solid Mech. 2021; 13:164-85.
10. Saffari PR, Fakhraie M, Roudbari MA. Free vibration problem of fluid conveying double-walled boron nitride nanotubes via nonlocal strain gradient theory in thermal environment. J Mech Based Des Struct Mach. 2020; 234:1-18.
11. Saffari PR, Fakhraie M, Roudbari MA. Free vibration and transient response of heterogeneous piezoelectric sandwich annular plate using third-order shear deformation assumption. J Solid Mech. 2020; 2:315-33.
12. Saffari PR, Fakhraie M, Roudbari MA. Nonlinear vibration of fluid conveying cantilever nanotube resting on visco Pasternak foundation using non-local strain gradient theory. Micro Nano Lett. 2020; 15:181-6. https://doi.org/10.1049/mnl.2019.0420
13. Nadiv R, Shtein M, Buzaglo M, Peretz-Damari S, Kovalchuk A, Wang T, Tour JM, Regev O. Graphene nanoribbon-polymer composites: The critical role of edge functionalization. Carbon. 2016; 99:444-50. https://doi.org/10.1016/j.carbon.2015.12.039
14. Shokrieh MM, Joneidi VA. Manufacturing and experimental characterization of graphene/polypropylene nanocomposites. Modares Mech Eng. 2014; 13:55-63.
15. Feng Z, Li Y, Xin C, Tang D, Xiong W, Zhang H. Fabrication of graphene-reinforced nanocomposites with improved fracture toughness in net shape for complex 3D structures via digital light processing. Carbon Res. 2019; 5:25. [Green Version] https://doi.org/10.3390/c5020025
16. Yetkİn SH, Karadenİz B, Güleşen M. Investigation of the mechanical and thermal properties of graphene oxide filled polypropylene composites. Araştırma Makalesi 2017; 4:34-40.
17. Wang J, Song F, Ding Y, Shao M. The incorporation of graphene to enhance mechanical properties of polypropylene self-reinforced polymer composites. Mater Des. 2020; 195:109073. https://doi.org/10.1016/j.matdes.2020.109073
18. Ansari MJ, Bbaripour B. Manufacture and comparison of mechanical properties of reinforced polypropylene nanocomposite with carbon fibers and calcium carbonate nanoparticles. Iran J Manuf Eng. 2019; 6:1-12.
19. Yuan B, Bao C, Song L, Hong N, Liew KM, Hu Y. Preparation of functionalized graphene oxide/polypropylene nanocomposite with significantly improved thermal stability and studies on the crystallization behavior and mechanical properties. Chem Eng J. 2014; 237:411-20. https://doi.org/10.1016/j.cej.2013.10.030
20. Gharebeiglou M, Zadkhah MS, Erfan-Niya H, Entezami AA. Improving the mechanical and thermal properties of chemically modified graphene oxide/polypropylene nanocomposite. Modares Mech Eng. 2016; 16:196-206.

21. Hadadi Asl V, Karimkhani V. Introduction to nanotechnology applications in polymers. Tehran, Iran: Petroleum Industry Research Center; 2010. p. 165-78.
22. Rahmani R, Ghorbanpoor Arani A, Shokravi M. Introduction to nanotechnology. Tehran, Iran: Academic Book Publishing; 2009. p. 300-4.
23. Bidi A, Liaghat G, Rahimi G. Effect of nano clay addition to energy absorption capacity of steel-polyurea bi-layer. J Sci Technol Compos. 2016; 3:157-64.
24. Esmizadeh E, Sahraeian R, Naderi G, Esfandeh M. Mechanical behavior of nano perlite/nano clay hybrid nanocomposites based on polyethylene. J Sci Technol Compos. 2019; 6:283-93.
25. Maniyar KG, Ingole DS. Multi response optimization of EDM process parameters for aluminium hybrid composites by GRA, Mater Today: Proceedings. 2018; 5:19836-43. https://doi.org/10.1016/j.matpr.2018.06.347
26. Maniyar KG, Ingole DS. Investigation of EDM process parameters for hybrid metal matrix composites. IOP Conference Series. Mater Sci Eng. 2018; 377:012204. https://doi.org/10.1088/1757-899X/377/1/012204
27. Maniyar KG, Ingole DS. Mathematical modelling and optimization of EDM process parameters for aluminium hybrid composites. Mater Today: Proceedings. 2018; 5:27700-9 https://doi.org/10.1016/j.matpr.2018.10.004
28. Maniyar KG, Ingole DS. Influence of EDM control factors for aluminium hybrid composites, advanced manufacturing and materials science; 2018. p. 275-84. https://doi.org/10.1007/978-3-319-76276-0_27
29. Maniyar KG. An experimental analysis of aluminium hybrid metal matrix composites. Mater Today: Proceedings. 2024. https://doi.org/10.1016/j.matpr.2024.01.021
30. Maniyar KG, Roshan V, Marode SB, Chikalthankar. Optimization of EDM process parameters on MRR and TWR of tungsten carbide by Taguchi method. Int J Eng Adv Technol. 2016; 5:112-16.
31. Maniyar KG. Analysis of EDM process parameters on material removal rate of WC. Int J Recent Innov Trends Comput Commun. 2017; 5:9.
32. Maniyar KG, Agarwal SK, Ingole DS. Optimization of multiple performance characteristics in EDM: A critical literature review. Int J Innov Technol Explor Eng. 2016; 5:10.
33. Maniyar KG, Deore HV. Design and testing of carbon fiber composite material with comparative analysis. Int Res J Eng Tech. 2020; 7(8).
34. Maniyar KG, Ingole DS. Current research development in the machining of hybrid metal matrix composites: A review. Int J Recent Innov Trends Comput Commun. 2016; 4(7).
35. Maniyar K, Jadhav P, Biradar R, Gawande J. An experimental study of process parameters for nanocomposites. NanoWorld J. 2024; 10(S1):S209-S211.
36. Maniyar K, Jadhav P, Biradar R, Gawande J. Effect of nano-lubricants on journal bearing for performance enhancement. NanoWorld J. 2024; 10(S1):S206-8.
37. Maniyar K, Suhane S. Parametric analysis of electric discharge machining for nanocomposites. NanoWorld J. 2024; 10(S1):S63-S65.
38. Maniyar K *et al*. The comprehensive study for machining of metal matrix composite. AIP Conf Proc. 2024; 3196:040005. https://doi.org/10.1063/5.0227955
39. Maniyar K *et al*. An extensive study of mechanical properties and tribological characteristics for hybrid composites. AIP Conf Proc. 2024; 3149:030038. https://doi.org/10.1063/5.0224994
40. Maniyar K *et al*. The comprehensive study of synthesis and characterization of hybrid nanofluids. AIP Conf Proc. 2024; 3149:030048. https://doi.org/10.1063/5.0224988
41. Pallavi Abhinandan Jadhav, Kamalkishor Maniyar, Evaluation and characterization of aluminum silicon carbide Metal Matrix Composites. AIP Conf Proc. 2024. https://doi.org/10.1063/5.0227945
42. Priti R. Ghutepatil; Sarika Khapare; Rujuta Barve Joshi; Kamalkishor G. Maniyar. A critical review of nanotechnology in various fields of engineering. AIP Conf Proc. 2024 3149: 030002. https://doi.org/10.1063/5.0224984
43. Vaishnavi Thamke; Namrata Saravade; Snehal Banarase; Kamalkishor Maniyar. Seismic performance and cost analysis of AAC blocks vs. fly ash bricks: A comparative study utilizing STAAD pro. AIP Conf Proc. 2024 3196: 060006. https://doi.org/10.1063/5.0227895
44. Banarase S, Banarase M, Saravade N, Thamke V, Maniyar K. Evaluation of concrete building

strengthening through non-destructive testing methods - A case study. AIP Conf Proc. 2024 3196: 040001.https://doi.org/10.1063/5.0227927
45. Stepien A, Kostrzewa P. The impact of basalt components on the structure of bricks formed as a result of hydrothermal treatment. Buildings. 2019; 9:192. https://doi.org/10.3390/buildings9090192
46. Bagheri S, Amini MM, Behbahani M, Rabiee G. Lowcost thiol-functionalized mesoporous silica, KIT-6-SH, as a useful adsorbent for cadmium ions removal: A study on the adsorption isotherms and kinetics of KIT-6-SH. Microchem J. 2019; 145:460-69. https://doi.org/10.1016/j.microc.2018.11.006
47. Szczęśniak B, Borysiuk S, Choma J, Jaroniec M. Mechanochemical synthesis of highly porous materials. Mater Horiz. 2020; 7:1457-73. https://doi.org/10.1039/D0MH00081G
48. Chen D, Wei L, Li J, Wu Q. Nanoporous materials derived from metal-organic framework for supercapacitor application. J Energy Storage. 2020; 30:101525. https://doi.org/10.1016/j.est.2020.101525
49. Zhang L, Jaroniec M. Strategies for development of nanoporous materials with 2D building units. Chem Soc Rev. 2020; 49:6039-55. https://doi.org/10.1039/D0CS00185F
50. Li Y, Cao H, Yu J. Toward a new era of designed synthesis of nanoporous zeolitic materials. ACS Nano. 2018; 12:4096-104. https://doi.org/10.1021/acsnano.8b02625