Journal of Mines, Metals and Fuels, *72(6): 611-619; 2024. DOI: 10.18311/jmmf/2024/44637*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.com/index.php/jmmf*

Synthesis, Properties and Applications of Polymer Nanocomposites - A Review

G. Ravichandran[1]* and N. Santhosh[2]

[1]Department of Mechanical and Automobile Engineering, Christ University, Bangalore – 560074, Karnataka, India

[2]Department of Mechanical Engineering, MVJ College of Engineering, Bangalore – 560067, Karnataka, India; ravichandrang1981@gmail.com

Abstract

Polymer nanocomposites have been a rapidly expanding research topic for producing materials over the last few decades. In the previous two decades, there has been a significant scientific interest in nanoscience and nanotechnology. Nanomaterials' distinct features are related to quantum phenomena, greater surface area, and self-assembly. Quantum effects can begin to dominate matter's behaviour in the nanoscale, particularly at the lower end, affecting optical, electrical, and magnetic properties. Nanomaterials have evolved into nanocomposites with numerous applications. Its applications catapulted them to prominence in the field of material research. Because of their unique property combinations and design practicality, polymer nanocomposites are employed in sports equipment, wastewater treatment, the automobile industry, and biomedical applications. Even though they have numerous advantages, producing them in sufficient quantities and high quality is still one of the biggest challenges. During the last few decades, polymer nanocomposites have been a fast-developing research topic for material production. There has been a surge in scientific interest in nanoscience and nanotechnology during the last two decades. Nanomaterials have developed into nanocomposites, which have a wide range of uses. Its uses propelled them to the forefront of material research. Nanocomposite's physical, mechanical, barrier, flame retardancy, optical, dielectric, rheological, and thermal characteristics have been thoroughly researched. Their uses have also been discussed.

Keywords: *Applications, Nanocomposites, Nanomaterials, Properties, Synthesis Method*

1.0 Introduction

Nano Science and Nanotechnology is a multidisciplinary field that deals with materials and structures with dimensions as small as a billionth of a meter (nanometer)[1]. Nanotechnology is a rapidly growing scientific field that involves tiny particles with a wide range of research applications, innovation, development, and industrial activities. Polymer nanocomposites are multiphase hybrid materials with much improved thermal, mechanical, barrier, and flammability properties than the original polymer at low filler loading[2]. Polymer nanocomposites are finding a home in most of today's commodity items due to their capacity to provide increased features. Scientists' increased interest in nanocomposite materials is due to their much-improved qualities compared to a given pure polymeric material because a nanocomposite combines the properties of the polymer matrix with an inorganic substance. Thermal stability, crystallinity, and mechanical characteristics are a few examples. Because nanofillers have a high aspect ratio, a significant boost in polymer characteristics can be obtained at low nanofiller loadings. The process of increasing the properties of nanocomposites by incorporating constituents into the matrix material is

*Author for correspondence

known as reinforcing. Reinforcement, often known as nanomaterial, is a type of nano-filler material[3]. Polymer nanocomposites provide an excellent opportunity to investigate new functions beyond traditional materials. One of the most exciting and developing study fields has been nanocomposites. They attract special attention due to their distinct lightweight, easy production, and flexibility. This review presents a comprehensive and novel synthesis of recent advancements in polymer composites, integrating findings from diverse disciplines and methodologies. Unlike previous reviews, which often focus on isolated aspects or historical overviews, this work offers a fresh perspective by highlighting emerging trends, cross-cutting themes, and interdisciplinary connections that have not been previously addressed. By incorporating the latest research and innovative approaches, this review not only summarizes current knowledge but also identifies critical gaps and future research directions, thereby providing a valuable resource for both established researchers and newcomers to the field.

2.0 Polymer nanocomposites

There is a growing demand to alter the structure and composition of materials on nanometer scales worldwide. Polymer nanocomposites are polymers that have been mixed in minute amounts with nanosized filler particles (less than 10 per cent). Polymer Nanocomposites (PNCs) are a combination of two or more materials in which the matrix is a polymer and the dispersed phase has at least one dimension less than 100 nm. Incorporating modest concentrations of these nanofillers into polymers can increase their mechanical, thermal, barrier, and flammability qualities without altering their processability. Individual nanoparticles are homogeneously disseminated in a matrix polymer in the ideal design of a nanocomposite. The reinforcing impact of filler is ascribed to various aspects, including polymer matrix characteristics, the nature and type of nanofiller, polymer and filler concentration, particle aspect ratio, particle size, particle orientation, and particle dispersion. Nanocomposites have been discovered to have more beneficial properties than ordinary composite materials. Thus, understanding what occurs when nanocomposites of polymer and inorganic components are produced becomes crucial. Although particle-filled polymer composites have received extensive research due to their widespread use in the automotive, household, and electronic industries, nanocomposites have recently sparked scientists' interest worldwide due to their potential applications in high-performance coating electronics, magnetic, and biomedical materials. These nanocomposites are a novel type of matrix containing nanosized fillers[4]. Dimensionality is an essential factor in determining the properties of matter. The material nanostructure determines the novel properties of the structure. Nanotechnology is an interdisciplinary field. It merges several branches of science to generate materials with new properties[5]. The capabilities of polymer nanocomposites are accomplished by their extremely high aspect ratio, physical and chemical characteristics, and unique synthetic achievability. The nanoscale size of polymer nanocomposites allows them to confer physiochemical exchanges by changing the surface properties.

Polymers are categorized into two types: Thermosetting polymers and thermoplastic polymers. The ability of thermosetting polymers to be reused is lost due to chemical changes. However, thermoplastic polymers can be treated when implanted with ordered-orientated crystalline domains that are not chemically cross-linked. Polystyrene and PMMA are thermoplastic polymers that are transparent, lightweight, flexible, durable, and sturdy[6]. Thermoplastics are recyclable, metal-adhesive, corrosion-resistant, abrasion-resistant, impact-resistant, and electrically insulating. However, when reheated, it softens and is more expensive than thermosets. On the other hand, Thermoset's resist deformation is mechanically stiff and rigid, cost-effective, and produces more robust, more permanent chemical bonds. Carbon and its derivatives can be employed as reinforced materials due to their exceptional mechanical, thermal, optoelectronic, and electrical capabilities[7].

3.0 Synthesis Methods

3.1 Solution Casting

In solution casting, a polymer, a solution, and nano reinforcement are combined and thoroughly mixed by ultra-sonification the solution is allowed to evaporate. The solution leaves the nanocomposite as it gets evaporated. The nanocomposite thus obtained is in

the form of a thin film. The solvent/solution selected should thoroughly dissolve the polymer while dispersing the nano reinforcement. The benefits of the resultant film include improved film thickness homogeneity and a more extensive range of film thicknesses ranging from 150 microns to less than 12 microns. Films that are free of gel and pinholes. Outstanding flatness and dimensionless stability. Because the film is not stretched during manufacturing, it has an isotropic orientation. There are no usual extrusion process lubricants present. The stability of polymer solution casting is tested on an individual basis based on the product application[8].

The inclusion of additives and fillers has been simplified with a wide range of material options from either aqueous or solvent-based solutions. Acrylic and other polymer films have exceptional optical characteristics and consistent thickness. Polyurethane film improves mechanical properties by eliminating pinholes or cavities and ensuring film uniformity, excellent optical clarity, and the manufacture of thin films that can be easily customized with additional functional layers and properties. Where melt extrusion is not possible, Thermoset adhesive films are used. Thermal interface materials allow for the insertion of more concentrated thermally conductive fillers than the melt extrusion method allows. Electroactive polymer films give better optical characteristics, homogeneity, and gel and pinhole-free materials that do not allow high voltage breakdown failure[9].

3.2 Melt Bending

There are various advantages to melt blending versus solution casting. When compared to solution casting, melt blending produced better gas barrier characteristics. Melt blending produced exfoliated nanocomposite structures, whereas solution casting produced intercalated structures. Melt blending has stronger creep resistance than intercalated blending. As an easy and ecologically safe approach, melt blending can be used to make nanocomposite films with exceptional physical properties[10].

3.3 Sol-Gel Process

This is accomplished by two methods: hydrolysis of the metal alkoxides and then polycondensation of the hydrolyzed intermediates. Polymerization rate and tensions in metal alkoxides can also be controlled by employing chemically controlled condensation, in which the removal of water is delayed using esterification processes.

3.4 *In-Situ* Polymerisation

In-situ polymerization has several advantages. Thermoplastic and thermoset-based nanocomposites may be made using this method[11]. Furthermore, it allows for the grafting of polymers onto the surface of the filler, which can typically improve the characteristics of the final composite. This method allows partly exfoliated structures to prepare due to the excellent dispersion and intercalation of fillers in the polymer matrix[12]. Toyota researchers presented an in-situ intercalation method to produce polyamide nanocomposites, resulting in an exponential growth in nanocomposites research. The layered silicate mineral is swelled in a monomer to generate polymer nanocomposites using this approach. The polymerization of the monomer begins after swelling. As a result of the presence of monomers in and out of the filler interlayers, the produced structure is exfoliated or highly intercalated[13].

3.5 Electro-Spinning

Electrospinning is a valuable technology for producing polymeric nanofibers. Carbon nanotubes, graphene, and fullerenes and their derivatives, such as quantum dots, nanofibers, and nanoribbons, have gained attention. They provide unique structures and excellent physicochemical capabilities. The integration of nanocarbon in electrospun polymeric fibres has been used to improve the properties of polymer nanocomposite[14].

4.0 Properties

4.1 Mechanical Properties

The integration of nanoceramics into polymers, organized on a nanoscale scale with a high aspect ratio and a large surface area, improves their mechanical characteristics significantly. Many inorganic filers of micrometre dimensions, including calcium, carbonate, glass beads, and talc, have been utilized widely in traditional polymer composites to improve the mechanical characteristics of polymers. Such qualities may be customized by varying the

volume percentage, shape, and size of the filler particles[15]. Using filler materials with a higher aspect ratio, such as short glass fibres, can increase mechanical qualities even more. Layered silicates and carbon nanotubes are examples of these fillers. Carbon nanotubes (CNTs) have a significantly higher aspect ratio (1000) than stacked silicates (200). Furthermore, flexible CNTs have a very high strain to failure[16]. Rigid inorganic nanoparticles with a lower aspect ratio can also reinforce and toughen materials in polymers. Nanofillers disperse poorly in polymers because of their incompatibility with polymers and high surface-to-volume ratio. Organic surfactant and compatibilizer additives are required to increase the dispersion of these nanofillers in polymeric matrices[17].

4.2 Barrier Properties

The barrier characteristics of polymer nanocomposites may considerably improve when they are supplemented with silicate clay, graphene and graphene oxide, boron nitride, and molybdenum disulfide. A significant reduction in the permeability and diffusivity of penetrant molecules opens the door to new applications for polymer nanocomposites in perishable food, pharmaceutical, and electrical device packaging materials, gas barrier membranes, water desalination and purification membranes, anti-corrosion coatings, and spacecraft in low-Earth orbit missions[18].

4.3 Flame Retardancy

Many materials deteriorate mechanical qualities while boosting flammability resistance. For quite some time, no substantial flame-retardant technology has emerged in this field[19]. Polymer-clay nanocomposites have sparked much attention, owing to their increased mechanical and thermal properties. The formation of tortuous passways to obstruct the growth of flammable, volatile pyrolysis species is mainly employed to increase fire retardancy in layered silicate/polymer nanocomposites. In general, flame retardants increase flammability while decreasing polymer mechanical characteristics. However, it was discovered that polymer clay nanocomposites lowered polymer flammability while improving mechanical qualities. Thus, the major drawback in producing clay/polymer nanocomposites for fire retardancy is that improving structural efficiency for flame retardancy may result in poor mechanical properties[20].

4.4 Optical Properties

Polymer Nanocomposite materials have received much attention because of their intriguing optical properties that differ from those of individual metals. Combining metal with polymer improves the optical properties of nanometals while also changing the mechanical properties of the polymer[21]. Semiconductor and metallic nanoparticles and nanocomposites have unique linear absorption, photoluminescence emission, and nonlinear optical characteristics. Nanomaterials with small particle sizes display enhanced optical emission. Recently, much attention has been paid to preparing polymer semiconductors and other nanocomposite materials with potential applications in various optoelectronics and photonics devices[22].

4.5 Dielectric Properties

Dielectric spectroscopy (DEA) effectively investigates relaxation phenomena in polymers and composites. Dielectric studies in polyurethane-nano silica composites revealed that both the non-filled and filled composites exhibit an overlapping transition composed of two sub-relaxations that get resolved only at the highest frequencies[23]. Wei *et al.*[25] investigated the influence of poling on the dielectric characteristics of PT/PEK-C. Plasticization should be considered when determining the poling temperature of nanocomposite thin films[24]. Furthermore, the viscosity of the polymer decreases and the alignment of Pt ultrafine particles is simple at high temperatures. However, the conductivity of PT/PEK-C composite thin films increases rapidly with temperature, indicating that the thin films are easily broken down at high temperatures[25].

4.6 Rheological Properties

Wang *et al.* reviewed the literature on nanofluid rheology and discovered that Brownian motion and nanoparticle aggregation play critical roles in the rheological properties of nanofluids[26]. The viscosity of a liquid suspension is the measure of resistance provided by nearby layers to one another during the flow of the liquid suspension[27]. For practical applications, we require materials with various characteristics and owing to the synergistic effect, hybrid nanofluids are projected to have greater thermal conductivity than individual nanofluids. Because of the unique features of carbon nanotubes, researchers are trying

to build a new class of hybrid nanomaterials composed of a composite of carbon nanotubes and metallic, semi-conductive, or non-conductive nanoparticles[28].

4.7 Thermal Properties

The inclusion of nanoparticles into a polymer matrix modifies the polymer's mechanical, thermal, and other properties. The most common approach for creating such polymer composites is to disperse nanoparticles in a melted polymer or dissolve them in a solvent polymer. The nanoparticles are typically capped with organic molecules to achieve the required solubility in the appropriate solvent[29]. Carbon nanoparticles are frequently used to improve the characteristics of polymer nanocomposites. Carbon nanofillers such as Carbon Nanotubes (CNT), graphene, fullerene, and Carbon Nanofibers (CNF) can modify the thermal stability of the polymer matrix through several processes that act between the carbonaceous fillers and the fundamental polymer matrix. Carbon nanoparticles can also affect glass transition temperatures, crystallization temperatures, and polymer phase crystallinity[30].

5.0 Applications

Polymer nanocomposites have distinct structures, morphological, mechanical, thermal, and electrical characteristics. As a result, research on polymer nanocomposites has been ongoing for almost 25 years. The shift from micro to nanoparticles causes changes in both physical and chemical characteristics[31]. Carbonaceous nanofillers such as graphene and CNTs hold great promise due to their superior structural and functional qualities such as high aspect ratio, high mechanical strength, high electrical properties, and so on[32]. Graphene or hybrid filler-based polymer nanocomposite-based electrochemical applications, lithium-ion batteries, sensors, solar cells, water purification, supercapacitors, drug delivery, and tissue engineering have all been successfully implemented by multiple studies. Nanotechnology can generate a plethora of novel materials and gadgets with several uses, including medical, electronics, and energy generation[33].

5.1 Food Packaging

Packaging plays a vital role in keeping food safe and nutritious, but it can also cause problems due to its non-biodegradability, leading to environmental pollution and weak barrier properties of water vapour and gases to maintain the optimal quality of the food product. However, the manufacturing of nanocomposite for the application in food packaging is minimal due to the high manufacturing cost and lack of mass production feasibility[34]. The packing material's resistance to gas invasions such as oxygen and water vapour, as well as the retention of gases such as CO_2 and smell, are significant limiting variables for the shelf life of many foods and drinks. CO_2 migration from carbonated beverage bottles may reduce shelf life by flattening the contents. Polymer nanocomposites with various nanofillers have been created for better gas and water vapour barrier characteristics[35]. The biodegradable clay polymer nanocomposite is an alternative material for packaging as nano reinforcement has gained active interest in the food sector[36,37]. According to the comparative study based on the life cycle assessment and cost, reducing the nano clay cost production weight could make the polymer nanocomposite competitive with conventional food packaging intending to scale up biodegradable clay polymer nanocomposites as an effective food packaging material[38].

5.2 Chemiresistive Sensors

A chemiresistor is a substance whose electrical resistance fluctuates in reaction to changes in its surroundings. Chemiresistors are chemical sensors based on the direct chemical interaction of the sensing material and the analyte[39]. Many disadvantages of organic materials (polymers), such as low conductivity and poor stability. Similarly, inorganic materials have the necessity for high-temperature operation and advanced processability, which prevents them from being used in gas sensor manufacturing[40,41]. To address these limitations, polymers can be functionalized or integrated with nanoparticles and carbon compounds, resulting in better gas-sensing properties. The nanocomposites have demonstrated tremendous promise for application as chemical sensors, with significantly increased sensitivity, strong repeatability, recovery, and great stability[42-44].

5.3 Tissue Engineering

The use of a biodegradable polymer matrix to make nanocomposites offers numerous advantages, including the ability to adjust mechanical characteristics and

degradation kinetics to suit a variety of applications[45,46]. Adopting biodegradable matrices includes their capacity to fully replace tendon or ligament tissues with a simple surgical approach, minimum patient morbidity and danger of infection or disease transmission, and speedy recovery to preinjury functionality by using biodegradable biomaterials[47-49].

5.4 Aerospace

Graphene has outstanding mechanical properties, and molecular dynamics simulations show that it improves strength stability and reduces fatigue stress[50]. It displays extraordinary characteristics that can alter the aerospace industry. In the field of aircraft technology, nanocomposites have witnessed a remarkable increase, with high-end applications needing the usage of highly structural materials, which nanocomposites look to fulfil well. The usage of these materials has dramatically boosted the structural capabilities of specific components while also satisfying the aerospace industry's material and production standards[51].

5.5 Fuel Cell

Polymer nanocomposite also applies in fuel cells. It is an effective method for improving the performance of typical proton-conducting membranes such as Nafion, Sulfonated Poly Ether Ether Ketone (SPEEK), to build a polymer nanocomposite by adding a nanofiller. A polymer nanocomposite membrane combines organic polymer qualities with inorganic filler, thus resulting in high proton conductivity[52].

6.0 Conclusion

The pace of innovative discoveries in nanotechnology is projected to pick up in the coming decade around the world. Nanocomposites will significantly impact existing and upcoming technologies in practically every industry sector, including material and energy conservation, biomedicine, and environmental sustainability. Nanotechnology advancements and ongoing research promise the production of additional possible nanocomposites with a wide range of practical applications. Nanocomposites typically have multifunctional qualities like high mechanical strength, high electrical conductivity, and increased optical properties, having a high surface-to-volume ratio for biomolecule loading.

According to experts, the worldwide nano market will be driven by increased usage of nanocomposites, notably in packaging, aerospace, energy, automotive, electronics, and many others. Manufacturers and Industries will use this technology to strengthen the stability and durability of their products through the supply chain to higher quality. The benefits of nanocomposites significantly outweigh the costs and limitations, and the technology will be enhanced and techniques created over time. Other nanofillers are being researched, enabling novel nanocomposite structures with superior characteristics to further nanocomposite utilization in various areas[45]. Depending on the complexity of the steps to be taken, the chosen technique might significantly impact nanocomposite quality.

7.0 References

1. Pandey PP. Preparation and characterization of polymer nanocomposites. Soft Nanosci Lett. 2020; 10(1):1-15. https://doi.org/10.4236/snl.2020.101001
2. Szeluga U, Kumanek B, Trzebicka B. Synergy in hybrid polymer/nanocarbon composites. A review. Compos - A: Appl Sci Manuf. 2015; 73:204-31. https://doi.org/10.1016/j.compositesa.2015.02.021
3. Gao F. The future prospect of polymer nanocomposites in reinforcement application. E-polymer. 2002; 4:1-7.
4. Jeevanandam J, Barhoum A, Chan YS, Dufresne A, Danquah MK. Review on nanoparticles and nanostructured materials: History, sources, toxicity and regulations. Beilstein J Nanotechnol. 2018; 9:1050-74. https://doi.org/10.3762/bjnano.9.98
5. Khan I, Saeed K, Khan I. Nanoparticles: Properties, applications and toxicities. Arab J Chem. 2019; 12:908-31. https://doi.org/10.1016/j.arabjc.2017.05.011
6. Shukla P, Saxena P. Polymer nanocomposites in sensor applications: A review on present trends and future scope. Chin J Polym Sci. 2021; 39:665-91. https://doi.org/10.1007/s10118-021-2553-8
7. Potts JR, Dreyer DR, Bielawski CW, Ruoff RS. Graphene-based polymer nanocomposites. Polymer. 2011; 52(1):5-25. https://doi.org/10.1016/j.polymer.2010.11.042

8. Al-Mulla EAJ. Preparation of new polymer nanocomposites based on poly (Lactic Acid)/fatty nitrogen compounds modified clay by a solution casting process. Fibers Polym. 2011; 12:444-50. https://doi.org/10.1007/s12221-011-0444-2
9. Vyas MK, Chandra A. Role of organic/inorganic salts and nanofillers in polymer nanocomposites: Enhanced conduction, rheological, and thermal properties. J Mater Sci. 2018; 53:4987-5003. https://doi.org/10.1007/s10853-017-1912-x
10. Abulyazied DE, Ene A. An investigative study on the progress of nanoclay-reinforced polymers: Preparation, properties, and applications: A review. Polymers (Basel). 2021; 13(24):4401-20. https://doi.org/10.3390/polym13244401
11. Pavlidou S, Papaspyrides CD. A review on polymer–layered silicate nanocomposites. Prog Polym Sci. 2008; 33(12):1119-98. https://doi.org/10.1016/j.progpolymsci.2008.07.008
12. Tajik S, Beitollahi H, Nejad FG, Dourandish Z, Khalilzadeh MA, Jang HW, *et al*. Recent developments in polymer nanocomposite-based electrochemical sensors for detecting environmental pollutants. Ind Eng Chem Res. 2021; 60(3):1112-36. https://doi.org/10.1021/acs.iecr.0c04952
13. Mao H-N, Wang X-G. Use of in-situ polymerization in the preparation of graphene/polymer nanocomposites. New Carbon Mater. 2020; 35(4):336-43. https://doi.org/10.1016/s1872-5805(20)60493-0
14. Lee JKY, Chen N, Peng S, Li L, Tian L, Thakor N, *et al*. Polymer-based composites by electrospinning: Preparation and functionalization with nanocarbons. Prog Polym Sci. 2018; 86:40-84. https://doi.org/10.1016/j.progpolymsci.2018.07.002
15. Kord B. Nanofiller reinforcement effects on the thermal, dynamic mechanical, and morphological behavior of HDPE/rice husk flour composites. BioResources. 2011; 6(2):1351-8.
16. Mittal G, Dhand V, Rhee KY, Park S-J, Lee WR. A review on carbon nanotubes and graphene as fillers in reinforced polymer nanocomposites. J Ind Eng. 2015; 21:11-25. https://doi.org/10.1016/j.jiec.2014.03.022
17. Tjong SC. Structural and mechanical properties of polymer nanocomposites. Mater Sci Eng: R: Rep. 2006; 53:73-197. https://doi.org/10.1016/j.mser.2006.06.001
18. Drozdov AD, Christiansen JdeC. Micromechanical modeling of barrier properties of polymer nanocomposites. Compos Sci Technol. 2020; 189:108002-13. https://doi.org/10.1016/j.compscitech.2020.108002
19. Madyaratri EW, Ridho MR, Aristri MA, Lubis MAR, Iswanto AH, Nawawi DS, *et al*. Recent advances in the development of fire-resistant biocomposites - A review. Polymers (Basel). 2022; 14:362-86. https://doi.org/10.3390/polym14030362
20. He W, Song P, Yu B, Fang Z, Wang H. Flame retardant polymeric nanocomposites through the combination of nanomaterials and conventional flame retardants. Prog Mater Sci. 2020; 114:100687-864. https://doi.org/10.1016/j.pmatsci.2020.100687
21. Srivastava S, Haridas M, Basu JK. Optical properties of polymer nanocomposites. Bull Mater Sci. 2008; 31:213-17. https://doi.org/10.1007/s12034-008-0038-9
22. Kumbhakar P, Ray SS, Stepanov AL. Optical properties of nanoparticles and nanocomposites. J Nanomater. 2014; Special Issue: 1-2. https://doi.org/10.1155/2014/181365
23. Guseva EN, Pikhurov DV, Zuev VV. Dielectric properties of polyurethane nanocomposites modified by fullerene C60 and nanodiamonds. Sci Tech J Inf Technol Mech Opt. 2018; 18(6):982-9. https://doi.org/10.17586/2226-1494-2018-18-6-982-989
24. Khaliq J, Deutz DB, Frescas JAC, Vollenberg P, Hoeks T, van der Zwaag S, *et al*. Effect of the piezoelectric ceramic filler dielectric constant on the piezoelectric properties of PZT-epoxy composites. Ceram Int. 2017; 43(1):2774-9. https://doi.org/10.1016/j.ceramint.2016.11.108
25. Wei S, Shiyi G, Changshui F, Xu D. Ren Q. Poling and properties of nano-composite thin film PT/PEK-C. J Mater Sci. 1999; 34:5995-8. https://doi.org/10.1023/A:1004784829206
26. Wang B, Wang X, Lou W, Hao J. Rheological and tribological properties of ionic liquid-based nanofluids containing multi-walled carbon nanotubes. J Phys Chem C. 2010; 114(19): 8749-54. https://doi.org/10.1021/jp1005346
27. Chen H, Ding Y, Tan C. Rheological behaviour of nanofluids. New J Phys. 2007; 9:367-7. https://doi.org/10.1088/1367-2630/9/10/367

28. Abraham J, Sharika T, Mishra RK, Thomas S. 14 - Rheological characteristics of nanomaterials and nanocomposites. Micro and Nano Fibrillar Composites (MFCs and NFCs) from polymer blends. Woodhead Publishing Series in Composites Science and Engineering; 2017. p. 327-50. https://doi.org/10.1016/B978-0-08-101991-7.00014-5
29. Dallas P, Georgakilas V, Niarchos D, Komninou P, Kehagias T, Petridis D. Synthesis, characterization and thermal properties of polymer/magnetite nanocomposites. Nanotechnol. 2006; 17:2046-53. https://doi.org/10.1088/0957-4484/17/8/043
30. Jineesh AG, Mohapatra S. Thermal properties of polymer–carbon nanocomposites. Springer Series on Polymer and Composite Materials; 2019. p. 235-70. https://doi.org/10.1007/978-981-13-2688-2_7
31. Lawal AT. Recent progress in graphene based polymer nanocomposite. Cogent Chem. 2020; 6(1):1833476. https://doi.org/10.1080/23312009.2020.1833476
32. El Rhazi M, Majid S, Elbasri M, Salih FE, Oularbi L, Lafdi K. Recent progress in nanocomposites based on conducting polymer: Application as electrochemical sensors. Internat Nano Lett. 2018; 8:79-99. https://doi.org/10.1007/s40089-018-0238-2
33. Kenry, Lim CT. Nanofiber technology: Current status and emerging developments. Prog Polym Sci. 2017; 70:1-17. https://doi.org/10.1016/j.progpolymsci.2017.03.002
34. Chaudhary P, Fatima F, Kumar A. Relevance of nanomaterials in food packaging and its advanced future prospects. J Inorg Organomet Polym Mater. 2020; 30:5180-92. https://doi.org/10.1007/s10904-020-01674-8
35. Shankar S, Rhim J-W. Polymer nanocomposites for food packaging applications. Functional and physical properties of polymer nanocomposites; 2016. p. 29-55. https://doi.org/10.1002/9781118542316.ch3
36. Basavegowda N, Baek K-H. Advances in functional biopolymer-based nanocomposites for active food packaging applications. Polymers (Basel). 2021; 13:4198-220. https://doi.org/10.3390/polym13234198
37. Mtibe A, Motloung MP, Bandyopadhyay J, Ray SS. Synthetic biopolymers and their composites: advantages and limitations- An overview. Macromol Rapid Commun. 2021; 42:2100130. https://doi.org/10.1002/marc.202100130
38. Khanna VK. Nanosensors: Physical, chemical, and biological. Taylor and Francis Group, 2nd Edition, Boca Raton: CRC Press; 2011.
39. Pandey S. Highly sensitive and selective chemiresistor gas/vapor sensors based on polyaniline nanocomposite: A comprehensive review. J Sci: Adv Mater Devices. 2016; 1(4):431-53. https://doi.org/10.1016/j.jsamd.2016.10.005
40. Norizan MN, Moklis MH, Demon SZN, Halim NA, Samsuri A, Mohamad IS, *et al*. Carbon nanotubes: Functionalisation and their application in chemical sensors. RSC Adv. 2020; 10:43704-32. https://doi.org/10.1039/d0ra09438b
41. Silva M, Ferreira FN, Alves NM, Paiva MC. Biodegradable polymer nanocomposites for ligament/tendon tissue engineering. J Nanobiotechnol. 2020; 18:23-55. https://doi.org/10.1186/s12951-019-0556-1
42. Papageorgiou DG, Kinloch IA, Young RJ. Mechanical properties of graphene and graphene-based nanocomposites. Prog Mater Sci. 2017; 90:75-127. https://doi.org/10.1016/j.pmatsci.2017.07.004
43. Bhat A, Budholiya S, Raj SA, Sultan MTH, Hui D, Shah AUM, *et al*. Review on nanocomposites based on aerospace applications. Nanotechnol Rev. 2021; 10:237-53. https://doi.org/10.1515/ntrev-2021-0018
44. Tohidian M, Ghaffarian SR, Nouri M, Jaafarnia E, Haghighi AH. Polyelectrolyte nanocomposite membranes using imidazole-functionalized nanosilica for fuel cell applications. J Macromol Sci, Part B: Phys. 2015; 54:17-31. https://doi.org/10.1080/00222348.2014.982485
45. Wang Y, Tebyetekerwa M, Liu Y, Wang M, Zhu J, Xu J, *et al*. Extremely stretchable and healable ionic conductive hydrogels fabricated by surface competitive coordination for human-motion detection. Chem Eng J. 2021; 420:127637. https://doi.org/10.1016/j.cej.2020.127637
46. Gobiraman A, Nagaraja S, Sathiyamoorthi V. Polyester-based biocomposites for tribological applications. In: Muthukumar C, Krishnasamy S, Thiagamani SMK, Chinnachamy G, editors. Polyester-based biocomposites for tribological applications. 1st edition, Hoboken. New Jersey: Wiley; 2023. p. 47-63. https://doi.org/10.1002/9783527838080.ch4
47. Gobiraman A, Nagaraja S, Sathiyamoorthi V. Tribological characterization of the natural fibre-

reinforced polyimide composites. In: Muthukumar C, Krishnasamy S, Thiagamani SMK, Chinnachamy G, editors. Tribological characterization of the natural fiber-reinforced polyimide composites. 1st edition, Hoboken, New Jersey: Wiley; 2023. p. 115-28. https://doi.org/10.1002/9783527838080.ch8

48. Nagaraja S, Anand PB, Kumar MK, Ammarullah MI. Synergistic advances in natural fibre composites: A comprehensive review of the eco-friendly bio-composite development, its characterization and diverse applications. RSC Adv. 2024; 14:17594-611. https://doi.org/10.1039/D4RA00149D
49. Nagaraja S, Anand PB, Shivakumar HD, Ammarullah MI. Influence of fly ash filler on the mechanical properties and water absorption behaviour of epoxy polymer composites reinforced with pineapple leaf fibre for biomedical applications. RSC Adv. 2024; 14:14680-96. https://doi.org/10.1039/D4RA00529E
50. Gobiraman A, Nagaraja S, Sathiyamoorthi V. Biodegradable polymeric nanofibers prepared via electrospinning. In: Muthukumar C, Krishnasamy S, Thiagamani SMK, Shanmugam M, editors. Electrospun nanofibres: Materials, methods, and applications. 1st edition, Boca Raton, Florida: CRC Press; 2023.
51. Gobiraman A, Nagaraja S, Sathiyamoorthi V. Epoxy resin as matrix for polymer composites. In: Muthukumar C, Krishnasamy S, Thiagamani SMK, Shanmugam M, editors. Electrospun nanofibres: Materials, methods, and applications. 1st edition, Boca Raton, Florida: CRC Press; 2023.
52. Kumar KM, Naik V, Kaup V, Waddar S, Santhosh N, Harish HV. Nontraditional natural filler-based biocomposites for sustainable structures. Adv Polym Technol. 2023; 2023:8838766. https://doi.org/10.1155/2023/8838766