Journal of Mines, Metals and Fuels, *72(9): 949-955; 2024. DOI: 10.18311/jmmf/2024/45554*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.com/index.php/jmmf*

An Extensive Study of Metal Matrix Composites and their Various Properties for Different Uses

Satypal Warghat[1], Chetankumar Sedani[2], Amol Rasane[3], Kamalkishor Maniyar[4]*, Vishakha Dhanwate[4], Sachin P. Jadhav[4], Swapnil Deshmukh[4], Jagannath Gawande[5] and Ramdas Biradar[6]

[1]*Takshashila College of Engineering and Technology, Darapur, Amravati - 444814, Maharashtra, India*
[2]*SPPU, Pune - 411007, Maharashtra, India*
[3]*PVG's College of Engineering and Shrikrushna S. Dhamankar Institute of Management, Nashik - 422004, Maharashtra, India*
[4]*Dr. D. Y. Patil Institute of Technology, Pimpri, Pune - 411044, Maharashtra, India; kkmaniyar2020@gmail.com*
[5]*Ajeenkya D Y Patil School of Engineering, Pune - 412105, Maharashtra, India*
[6]*Pimpri Chinchwad University, Pune - 412106, Maharashtra, India*

Abstract

This study examines the creation and development of composite materials, from conventional techniques to their innovative uses in numerous industries. Composite materials that are robust, versatile, and resilient have advanced significantly, especially with the application of nanotechnology and hybrid fiber reinforcements. Composite materials are difficult to machine due to their anisotropic and non-homogeneous structure, as well as the high abrasiveness of their reinforcing parts. This typically results in the workpiece becoming damaged and the cutting tool wearing down very rapidly. On composite materials, traditional machining methods such as turning, drilling, and milling can be applied with the appropriate tool design and operating parameters. An overview of the various issues related to the conventional machining of the main types of composite materials is given in this work. This article examines novel matrix materials, forms of reinforcement, and production procedures to show how advanced metallic matrix nano composites and fiber-reinforced polymers are replacing traditional composites. Special emphasis is given to the strict manufacturing conditions in addition to the homogenous dispersion of nanoparticles and damage-free machining of fiber composite materials. The essay also discusses how sustainable alternatives, including reinforcements made of natural fibers, affect the ecosystem. This study aims to offer a comprehensive analysis and case studies.

Keywords: *Analysis, Composites, Machining Parameters, Mathematical Model, Output Responses*

1.0 Introduction

A relatively new class of materials known as metal-matrix composites has several properties that make them valuable in applications requiring high strength, low weight, high stiffness, and the capacity to function at high temperatures. These materials, which are composed of a more ductile matrix material and a hard, abrasive ceramic reinforcing media, are challenging to machine. Composite materials have a wide range of applications in the cutthroat industrial sector because of their remarkable mechanical and wear properties, including strength, hardness, toughness, wear in microns, and coefficient of friction[1]. About more recent advancements in materials like

*Author for correspondence




Figure 1. The metal matrix and its details[2].

composite and hybrid composite materials, conventional monolithic general materials have certain limits. A fascinating challenge in material science and metallurgy is the development of hybrid metal matrix composites. Since aluminum alloy composites have outstanding mechanical properties such as increased stiffness, reduced density, superior corrosion resistance, and significant wear resistance they are mostly used in the automotive and aerospace industries[2]. This study reports on development and examination of metal-matrix composite for getting optimum results. Figure 1 depicts the metal matrix and its details.

2.0 Development of Composites

Different materials have been used since the beginning of time, from the Stone Age to the Plastic Age, however for the materials to fulfill criteria and perform optimally, improved and advanced materials are now required. The polymer is without a doubt the greatest material ever created because of its exceptional properties for use in a wide range of applications. It is unquestionably 21st-century content. When other materials reinforce the polymers to form composites, the material acquires the qualities necessary to function optimally in a variety of sectors. Therefore, creating Polymer Matrix-based Composites (PMCs) is one of the most effective ways to modify the properties of the polymer[3].

Friction stir technique was first developed in the past ten years to join and weld metals and alloys, regardless of how close or dissimilar they are[1,2]. For creating bulk Metal Matrix Composites (MMCs) and surface composites in response to the evolving demands of a multidisciplinary industry, this approach was further refined[3-6]. The fundamental type of friction stirs welding created in the 1990s was improved upon friction stir processing




Figure 2. Shows several approaches to the development of composites[5].




Figure 3. The evolution of metal matrix and its details[9].

method in 1991[7]. One advantage of this technique is that it causes significant plastic deformation to the substrate, which prevents melting and creates a metal composite with uniform particle distribution and the necessary mechanical, microstructural, and chemical properties for the intended use.

The tool's swirling causes the substrate to distort when the reinforcing particles are added, resulting in the creation of composites with a variety of uses. These can be manufactured using appropriate substrate materials, such as copper, magnesium, aluminum (Al), and other ductile materials with reinforcements based on the application's requirements[8]. The metal aluminum finds extensive use in the fields of automotive, aerospace, and defense technologies[9]. Additionally, the various Al alloys for example have varying applications. To produce the qualities necessary for increased performance in the unique applications, these alloys are further changed to create a variety of composites[10].

3.0 Examination of the Composites

Polymer matrix composites provide significantly better performance and flexibility as compared to conventional structural materials. These advantages do, however, come at the expense of greater material complexity, and it is simple to forget about the difficulties in generating high-quality test data to meet the demands of design, development, and quality assurance[11]. As more and more




Figure 4. Examination of metal matrix and its details[11].

sectors come to understand the advantages that composite materials provide, they are being used in an ever-widening range of products and applications. The need for lighter composite structures in the fields of aerospace, land transportation, and environmentally friendly energy systems is driving an expansion in the mechanical testing standards for composite materials, parts, and structures. To fully characterize the characteristics of anisotropic and inhomogeneous composite materials for use in demanding structural applications, numerous mechanical tests must be conducted. Shear, compression, and tension testing are necessary to determine bulk characteristics. Mechanical testing defines the fundamental evaluation and characterization of each given material[12]. However,

defining composites requires knowing several important factors, including fibers, matrix phases, volume fractions, orientations, and the direction of applied load. The orientation, concentration, and matrix of a composite material affect its mechanical qualities, such as strength and stiffness, among other attributes. Unlike metals, these materials show distinct mechanical behavior in various orientations. Examining the mechanical, surface, and microstructural characteristics as well as the ensuing interfacial impacts is essential for better performance under high-temperature operating circumstances[9,10]. Previous techniques have not been able to improve a material's performance with a single or multiple pass surface alteration alone, without the inclusion of reinforcement and bulk or surface additions[11,12]. The two-fold improvement in yield strength and the increase in hardness have been attributed mostly to Al Matrix Composites (AMCs) containing Silicon Carbide (SiC) particles[13,14]. Furthermore, research on hybridization of many reinforcement types has demonstrated improved mechanical and microstructural capabilities, particularly at the nanoscale[15].

4.0 Functional properties of the Composites

While samples of different functionality are shown in the lower half of the picture, the upper half of the figure lists attributes that can be utilized to construct various functions in the material. A more complete view of the field can be created by adding more attributes and functions to this diagram. The aerospace structures have a strong interest in self-healing and damage-sensing




Figure 5. Attributes and functionality of composites[13].

capabilities. Engine applications involve the use of self-cleaning and self-lubricating surfaces. It may be possible to lessen the weight and the need for extra systems on the application platform by developing functional capabilities in the base material. Recent years have witnessed a significant increase in the use of carbon-fibre-reinforced polymer-matrix composites in wind turbine blades and auto bodywork. Nevertheless, high temperatures restrict the usage of polymer-matrix composites in engine components. For these kinds of applications, metallic materials work well. Under this topic, you can find studies that are currently being conducted in the demanding field of developing lightweight metal-matrix composites with high performance and functional qualities[15].

The wear process of polymers is far more complex than that of metals because of the vast range of variations in their mechanical characteristics, as well as their considerable dependence on temperature, deformation rate, and the susceptibility of their failure process to environmental circumstances. The majority of academics currently divide this intricate process into four categories: fatigue wear, abrasive wear, corrosive wear, and adhesive wear. The different categories of wear can change over time[16].

The surface of friction couples in the relative motion of the friction vice; nevertheless, even if the surface seems flat, the micro-surface remains uneven, thereby revealing just the local contact. At this moment, the local stress on the real contact surface is high enough to induce plastic deformation even with a smaller load. This squeezes the oxide film on this portion of the surface, among other things, and causes the atoms of the two contact surfaces to connect as a result of bonding interaction. The adhesion points shear off and is transmitted to the counterpart surface in the ensuing sliding, where it falls off to create abrasive chips and loses material on the part's surface[17].

Hard particles inside the contact surface also led to abrasive wear. Under the influence of abrasive particles, the polymer goes through a cutting process similar to planning, which can immediately result in material removal and create a chip, or micro cutting. By way of contrast, ploughing involves the extrusion of the polymer through abrasion to the sides. While this process does not immediately result in material removal, it can lead

to shedding and secondary chip development after many deformations. The wear rate of the polymer increases with the rougher the counterpart surface[18].

Furthermore, the rough pair surface may have fatigue wear. This is because the soft surface's rough peaks break first under cyclic stress, leaving a smoother surface, while the rough peaks of the friction pair are easily distorted when they slide against one another. This means that the rough peak to rough peak contact state is replaced by the rough peak's hard surface sliding across a comparatively smooth soft surface. At a certain depth below the surface, dislocation buildup results from the hard surface rough peak sliding across the soft surface, subjecting the points on the soft surface to a cyclic load that causes shear plastic deformation in the surface layer and accumulation. The positive stress on the parallel surface stops the crack from extending in the direction of depth when it forms at a specific depth, causing the crack to extend in the direction of the parallel surface at that depth, according to the stress field analysis. The substance separating the fissure from the surface will flake off as abrasive chip flakes when the crack reaches a certain length[19].

While oxidation and chemical degradation are the primary causes of corrosive wear in polymers, some polymers may become severely degraded or softened as a result of the high temperature created at the sliding interface. Numerous variables, including the activation energy of polymer degradation, the catalytic action of certain oxygen species, and interfacial contact stress, affect the chemical breakdown of polymers in addition to temperature. An efficient and practical method of improving the tribological properties of polymers is the insertion of functional fillers to influence the friction process, which is based on the friction and wear behaviour of polymers. Based on their functions, the fillers in filler-modified polymer composites can be divided into two categories: lubricating fillers and reinforcing fillers. In addition to exhibiting exceptional wear resistance, the authors showed that the insertion of glass fibre can significantly increase the mechanical properties of the composites, including tensile strength, tensile modulus, flexural strength, and flexural modulus. This is because of the strong interfacial interaction that exists between polyether ether ketone and glass fibres. This bonding prevents the matrix resin from being abraded and causes abrasive particles to accumulate in the vicinity of the glass fibres, interrupting the process of removing fibers[20].

5.0 Different Uses of the Metal Matrix Composites

It is hard to find the qualities and features displayed by polymer-based composites somewhere else because they are materials that are created via the mixing of composites. Polymer-based composites are distinctive because of their own working mechanics, which makes them especially good at performing in highly authentic applications. They are used in practically every industry, including maritime, civil, aerospace, biomedical, and many more. Their uses are so diverse. Research conducted in this topic has advanced dramatically over time, reflecting a significant shift in the field's state of development as times have progressed. Since their inception, polymer materials have been seen as useful and helpful for a wide range of applications; but, because of a lack of knowledge about them, their promise has not been fully realized[21].

However, in many applications today, polymer materials are quickly replacing other materials on a steady basis. As a result of increased understanding and study, they are currently regarded as the materials of choice for several applications. Due to the development



Figure 6. Metal Matrix Composites in various fields[15].

of more sophisticated materials made of polymers that are utilized daily, regions that were previously deemed unsuitable for polymers are now demonstrating their usefulness. Polymer has recently supplanted metal and ceramic in applications such as building, automotive, aerospace, and medical. The space shuttle, commercial airplanes, electronic substrates, bicycles, cars, golf clubs, and many other applications are either using metal-matrix composites or are in the process of prototyping them[22].

While aluminum matrix composites make up the great majority, more and more applications call for the matrix qualities of super alloys. Like other composites, aluminum-matrix composites are a class of materials whose density, stiffness, strength, and electrical and thermal properties may all be customized. To obtain the necessary qualities, one can alter the matrix alloy, the reinforcing material, the volume and form, and the construction technique. Compared to traditional materials, composites offer more design flexibility, making it easier to shape them into complex shapes. Designers can therefore create almost whatever they dream of. For example, most recreational boats built nowadays are made of fiber glass composites. This is because these materials are easily formed into complex forms, which results in more affordable boats that are of higher quality. Furthermore, the surfaces of composites can be molded to resemble any surface, whether it is pebbly or smooth. Part consolidation refers to the ability of a composite part to replace an entire group of metal components. Less-parts machines and structures require less upkeep and operate more smoothly over time[23].

6.0 Conclusion

The invention and evolution of composite materials are studied in this paper, from traditional methods to their creative applications in many industries. Strong, adaptable, and resilient composite materials have undergone significant development, particularly with the use of nanotechnology and hybrid fiber reinforcements. Because of their high abrasiveness of their reinforcing elements and anisotropic and non-homogeneous structure, composite materials are challenging to machines. This usually leads to the workpiece acquiring damage and the cutting tool developing wear extremely quickly. If the right tool design and operating conditions are used, conventional machining techniques like turning, drilling, and milling can be used on composite materials. This paper provides an overview of the different problems associated with the traditional machining of the primary kinds of composite materials. This work illustrates how sophisticated metallic matrix nano composites and fiber-reinforced polymers are replacing conventional composites by examining unique matrix materials, types of reinforcement, and manufacturing processes. In addition to homogeneous dispersion of nanoparticles and damage-free machining of fiber composites, special attention is paid to the rigorous manufacturing conditions. Furthermore, included in the article is the environmental impact of sustainable solutions such as natural fiber reinforcements. The goal of this research is to provide a thorough critique and case studies.

7.0 References

1. Habib SS. Study of the parameters in electrical discharge machining through response surface methodology approach. Appl Mathematical Modelling. 2009; 33:4397-407. https://doi.org/10.1016/j.apm.2009.03.021
2. Kathiresan M, Sornakumar T. EDM studies on aluminum alloy-silicon carbide composites developed by vortex technique and pressure die casting. J Minerals and Materials Characterization and Engg. 2010; 9:79-88. https://doi.org/10.4236/jmmce.2010.91007
3. Sasimurugan T, Palanikumar K. Analysis of the machining characteristics on surface roughness of a hybrid aluminium metal matrix composite (Al6061-SiC-Al2O3). J Minerals and Materials Characterization and Engg. 2011; 10:1213-24. https://doi.org/10.4236/jmmce.2011.1013094
4. Banarase S, Banarase M, Saravade N, Thamke V, Maniyar K. Evaluation of concrete building strengthening through non-destructive testing methods - A case study. AIP Conf Proc. 2024; 3196:040001. https://doi.org/10.1063/5.0227927
5. Thamke V, Saravade N, Banarase S, Maniyar K. Seismic performance and cost analysis of AAC blocks vs. fly ash bricks: A comparative study utilizing STAAD pro. AIP Conf Proc. 2024; 3196:060006. https://doi.org/10.1063/5.0227895
6. Jadhav PA, Maniyar K. Evaluation and characterization of aluminum silicon carbide Metal Matrix Composites. AIP Conf Proc. 2024. https://doi.org/10.1063/5.0227945
7. Ghutepatil PR, Khapare S, Joshi RB, Maniyar KG. A critical review of nanotechnology in various fields of

engineering. AIP Conf Proc. 2024; 3149: 030002. https://doi.org/10.1063/5.0224984
8. Maniyar KG, Ingole DS. Multi response optimization of EDM process parameters for aluminum hybrid composites by GRA. Mater Today: Proc. 2018; 5(9):19836-43. https://doi.org/10.1016/j.matpr.2018.06.347
9. Maniyar KG, Ingole DS. Investigation of EDM process parameters for hybrid metal matrix composites. IOP conf ser: Mater Sci Eng. 2018; 377:012204. https://doi.org/10.1088/1757-899X/377/1/012204
10. Maniyar KG, Ingole DS. Mathematical modeling and optimization of EDM process parameters for aluminum hybrid composites. Mater Today: Proc. 2018; 5(14):27700-9. https://doi.org/10.1016/j.matpr.2018.10.004
11. Maniyar KG, Ingole DS. Influence of EDM control factors for aluminium hybrid composites. Lecture Notes on Multidisciplinary Industrial Engineering. 2018; 275-84. https://doi.org/10.1007/978-3-319-76276-0_27
12. Maniyar KG. An experimental analysis of aluminium hybrid metal matrix composites. Mate Today: Proc. 2024. https://doi.org/10.1016/j.matpr.2024.01.021
13. Maniyar KG, Marode RV, Chikalthankar SB. Optimization of EDM process parameters on MRR and TWR of tungsten carbide by Taguchi method. Int J Eng Adv Technol. 2016; 5(3):112-6.
14. Maniyar KG. Analysis of EDM process parameters on material removal rate of WC. 2nd National Conference Recent Innovations in Science and Engineering. 2017; 5(9):37-9.
15. Maniyar KG, Agrawal SK, Ingole DS. Optimization of multiple performance characteristics in EDM: A critical literature review. Int J Innov Techn Expl Eng. 2016; 5(10):27-33.
16. Maniyar KG, Deore HV. Design and testing of carbon fiber composite material with comparative analysis. Int J Res Eng Technol. 2020; 7(8):1120-2.
17. Maniyar KG, Ingole DS. Current research development in machining of hybrid metal matrix composites: A review. Int J Recent Innov. Trends. 2016; 4(7):150-4
18. Maniyar K, Jadhav P, Biradar R, Gawande J. An experimental study of process parameters for nano composites. NanoWorld J. 2024; 10(S1):S209-S11.
19. Maniyar K, Jadhav P, Biradar R, Gawande J. Effect of nano-lubricants on journal bearing for performance enhancement. NanoWorld J. 2024; 10(S1):S206-S8.
20. Maniyar K, Suhane S. Parametric analysis of electric discharge machining for nano composites. Nano World J. 2024; 10(S1):S63-S5.
21. Maniyar K *et al*. The comprehensive study for machining of metal matrix composites. AIP Conf Proc. 2024; 3196:040005. https://doi.org/10.1063/5.0227955
22. Maniyar K *et al*. An extensive study of mechanical properties and tribological characteristics for hybrid composites. AIP Conf Proc. 2024; 3149(1):030038. https://doi.org/10.1063/5.0224994
23. Maniyar K *et al*. The comprehensive study of synthesis and characterization of hybrid nano fluids. AIP Conf Proc. 2024; 3149(1):030048. https://doi.org/10.1063/5.0224988