Journal of Mines, Metals and Fuels, *73(1): 87-101; 2025. DOI: 10.18311/jmmf/2025/46621*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.co.in/index.php/jmmf*

A Review on Additively Manufactured AlSi10Mg Alloy: Mechanical, Tribological, and Microstructure Properties

Nagareddy Gadlegaonkar[1], Premendra J. Bansod[1], Avinash Lakshmikanthan[2]* and Krishnakant Bhole[3]

[1]Department of Mechanical Engineering, G.H. Raisoni College of Engineering and Management, Wagholi, Pune - 412207, Maharashtra, India

[2]Department of Mechanical Engineering, Nitte Meenakshi Institute of Technology, Bengaluru - 560064, Karnataka, India; avinash.l@nmit.ac.in

[3]Vijay Bhoomi School of Science and Technology, Vijay Bhoomi University, Karjat - 410201, Mumbai, India

Abstract

Additive Manufacturing (AM) has rapidly evolved as a transformative technology, enabling the production of complex, high-performance materials that exhibit superior mechanical and tribological properties. Among the materials benefiting from this advancement is AlSi10Mg, an aluminum-silicon-magnesium alloy. AlSi10Mg has gained notable attention in industries like aerospace and automotive due to its excellent strength-to-weight ratio, high thermal conductivity, and robust wear resistance. These properties make it particularly suitable for lightweight, high-stress applications. This review consolidates state-of-the-art research on AlSi10Mg, specifically focusing on components produced through Selective Laser Melting (SLM), a prominent AM technique. SLM enables precise control over the materials microstructure and properties by melting and fusing powdered material layer-by-layer using a high-energy laser. The review delves into the influence of various SLM processing parameters, play a crucial role in influencing the alloy's density, porosity, and internal stress, ultimately affecting its mechanical performance. Additionally, the review examines post-processing treatments enhancing AlSi10Mg's strength, ductility, and fatigue resistance. Furthermore, the impact of these treatments on the alloy's microstructure, particularly the distribution and morphology of silicon phases within the aluminum matrix, is critically discussed, as they influence wear resistance and hardness.

Major Findings: *The major findings in this work are the potential of AM-produced AlSi10Mg as a high-performance material for industrial applications, highlighting current challenges and future research directions aimed at optimizing processing.*

Keywords: *Additive Manufacturing, AlSi10Mg, Microstructure, SLM Processing Parameters*

1.0 Overview of Additive Manufacturing (AM)

Additive manufacturing is a rapidly evolving technology that has fundamentally changed the way we propose and assemble complex components. One area where AM has shown promise is in the production of high-performance metal alloys, specifically aluminum alloys, due to their balance of strength, weight, and durability[1,2]. AlSi10Mg, an aluminum alloy, has become one of the most studied

**Author for correspondence*

materials in AM, especially for applications in demanding industries like aerospace and automotive. AlSi10Mg belongs to the family of aluminum-silicon alloys and is strengthened by a small amount of magnesium[3,4]. In conventional manufacturing, this alloy is usually produced through casting, but the fast development of AM processes, particularly Selective Laser Melting (SLM), has expanded the range of applications for this material. SLM, an advanced AM technique, uses a high-powered laser to melt and fuse powdered material layer by layer, allowing for precise control over the final parts shape, microstructure, and performance[5]. This control over the microstructure is particularly important because it aids the fabrication of finely tuned properties. For example, the rapid cooling and solidification results in a very fine microstructure, which can enhance the materials properties. Benefits of AM over traditional manufacturing techniques is ability to directly control process parameters during production. In the case of AlSi10Mg, controlling these parameters allows manufacturers to achieve an optimal balance of strength, ductility, and wear resistance[6]. For instance, increasing the laser energy density can ensure complete melting and bonding between powder particles, reducing defects like porosity and improving the overall strength of the final part. Adjusting the scanning strategy, which defines the laser's movement across the powder bed, can also impact the microstructure, affecting how silicon particles distribute within the aluminum matrix. This distribution is critical for wear resistance and can also influence the alloy's hardness and frictional properties[7]. Another advantage of AM-produced AlSi10Mg is the flexibility to apply various techniques such as HIP, a technique that applies high pressure and temperature to the part, is particularly effective at eliminating internal voids and defects, leading to improved fatigue resistance and overall strength. Surface finishing techniques like polishing and shot peening can further refine the surface texture, which is especially important for applications where smoothness is critical, such as in components exposed to friction and wear. Despite the advantages, there are still challenges associated with producing AlSi10Mg through AM. One of the main issues is porosity within material, which can significantly weaken the part[8]. Porosity often arises from incomplete melting of powder particles or trapped gas during the AM process. While optimizing process parameters can reduce porosity, it is difficult to eliminate it entirely without some form of post-processing. Residual stress is another concern, as the rapid temperature changes during AM can lead to internal stresses that may impact the part's mechanical properties and dimensional stability. These challenges highlight the importance of ongoing research and process refinement to fully realize the potential of AM-process produced for industrial products. In the aerospace and automotive industries AlSi10Mg has demonstrated great potential. In aerospace, for example, reducing weight is a constant priority, as it can lead to significant fuel savings and increased payload capacity[9]. AlSi10Mg's combination of lightweight and durability makes it ideal for producing components like brackets, structural supports, and heat exchangers that need to withstand high stresses without adding excessive weight. Similarly, in the automotive sector, AlSi10Mg is valued for its thermal conductivity and wear resistance, which make it suitable for engine parts and other components that need to dissipate heat effectively and resist wear. The use of AM allows these industries to produce parts that are not only lighter and stronger but also customized to meet specific performance criteria. This analysis brings together recent findings on mechanical, tribological (related to friction and wear), and microstructural properties of additively manufactured AlSi10Mg. It examines prompt of numerous AM process factors on these properties, providing insights into how adjustments to the AM process can enhance the alloy's performance. For instance, research has shown that by carefully controlling laser power and scan speed, it is possible to create parts with a higher density and fewer defects, resulting in improved strength and wear resistance[10]. The review also explores the role of post-processing treatments in further refining the alloy's characteristics. Heat treatments can modify the distribution of silicon particles within the aluminum matrix, thereby enhancing hardness and wear resistance, while HIP can reduce internal voids, leading to better fatigue performance. In summary, AlSi10Mg produced through AM, and especially SLM, offers significant advantages over conventionally manufactured parts, providing a way to create high-performance components with tailored properties. However, to maximize these benefits, it is crucial to address the challenges of porosity and residual stress, which continue to limit the materials potential in some applications. Future research is likely

to focus on refining these processes further, exploring new AM techniques, and developing advanced post-processing methods to expand the range of applications for AlSi10Mg. Through a better understanding of how process parameters and post-processing techniques impact AlSi10Mg's properties, the manufacturing industry can continue to push the boundaries of what is possible with AM. By tailoring microstructure and properties to specific needs, additively manufactured AlSi10Mg has the potential to become a cornerstone material in high-performance applications where weight, durability, and precision are essential. This review provides a foundation for that understanding, contributing to the body of knowledge that will drive the future of AM in high-stakes fields[11,12].

2.0 Selective Laser Melting (SLM)

Among the AM techniques available, Selective Laser Melting (SLM) has become the primary method for producing AlSi10Mg components due to its high precision and flexibility in customizing material properties. Each layer is selectively melted based on a digital model, allowing intricate shapes and designs to be manufactured without the need for moulds or dies[13].

SLM offers a unique advantage over traditional casting by enabling precise adjustments in processing parameters. These parameters influence key aspects of the alloy's final properties, such as microstructure, mechanical strength, tensile strength, hardness, and wear resistance[14]. For instance, adjusting laser power and scanning speed can impact the cooling rate, thereby controlling the size of the cellular structure formed within the alloy. A rapid cooling rate tends to result in a fine microstructure, enhancing the materials strength and wear resistance compared to cast counterparts[15]. SLM-produced AlSi10Mg components generally exhibit bettered mechanical properties, such as higher tensile strength and hardness, due to their refined microstructures. The enhanced control over the microstructure also contributes to the alloy's superior tribological performance, making it well-suited for applications requiring high resistance to wear and friction. By tailoring processing parameters, manufacturers can achieve a balance of strength, flexibility, and wear resistance that meets specific performance requirements. This customization is a distinct advantage of SLM over traditional methods, where controlling such properties is often more challenging[16].

2.1 Process Parameters

2.1.1 Laser Power

Laser power is the total energy output delivered by the laser onto the powder bed. This energy input directly affects the melt pool's temperature and depth, influencing how effectively particles fuse together. Higher laser power




Figure 1. Schematic of SLM process.




Figure 2. List of process parameter.

promotes deeper penetration and better fusion between particles, enhancing part density and strength. However, excessive power can cause overheating, leading to defects like keyhole porosity and vaporization, both of which can degrade the parts quality. For AlSi10Mg, achieving an optimal laser power level is crucial to balancing penetration depth with stable fusion and avoiding defects[17].

2.1.2 Scanning Speed

This parameter affects the exposure time of the laser on each area, impacting the heat input and, consequently, the melt pool dynamics. A high scanning speed reduces energy absorption, which can prevent excessive heat build up but may lead to inadequate melting and weaker bonding. Conversely, a slower scanning speed allows for deeper fusion, reducing porosity but increasing the risk of overheating. The optimal scanning speed for AlSi10Mg balances full melting with stability, ensuring sufficient bonding between layers without introducing excessive heat[17].

2.1.3 Hatch Spacing

Hatch spacing refers to the distance between successive laser passes across the powder bed. This spacing is critical for ensuring overlapping of melted tracks, creating a continuous structure without gaps. If hatch spacing is too large, un-melted areas may remain, leading to porosity and weak bonding. On the other hand, a narrow hatch spacing increases the heat input per area, potentially causing residual stress or warping. For AlSi10Mg, optimizing hatch spacing supports a consistent, dense microstructure, contributing to uniform mechanical properties across the part[17].

2.1.4 Laser Energy Density

Laser energy density combines laser power, scanning speed, and hatch spacing to describe the energy delivered per unit area. This parameter is essential to achieving complete melting and bonding between particles. Low energy density can lead to insufficient melting and high porosity, compromising mechanical strength. However, high energy density may cause keyhole porosity or other thermal defects. For AlSi10Mg, optimal energy density helps achieve a high-density, strong structure with minimal porosity, maximizing mechanical performance in applications demanding durability[17].

2.1.5 Scanning Strategy

Scanning strategy refers to the laser path across the powder bed. Different strategies, such as unidirectional, bidirectional (zigzag), and checkerboard or island

scanning, influence heat distribution and residual stresses. Unidirectional Scanning moves the laser in a single direction and can lead to residual stress due to thermal gradients. Bidirectional (Zigzag) Scanning involves alternating scan directions, distributing heat more evenly and reducing residual stresses. Checker board or Island Scanning breaks the layer into sections, distributing heat in a controlled sequence, which minimizes residual stress build up, especially useful for larger parts. These strategies affect grain structure and isotropy. Unidirectional scanning often creates columnar grains, whereas island scanning promotes equiaxed grains, resulting in more isotropic properties[17].

2.1.6 Powder Layer Thickness

Powder layer thickness impacts resolution, surface finish, and build time. Thicker layers reduce build time but may require higher power or slower speed to achieve full melting, risking defects like porosity. Thinner layers offer better surface finish and higher resolution, as the laser can more effectively melt each layer, creating a dense microstructure. However, thin layers increase build time. For AlSi10Mg, choosing the right layer thickness is essential to balance between production efficiency and mechanical quality[18].

2.1.7 Preheat Temperature

Preheat temperature refers to the temperature applied to the powder bed before the laser melts each layer. Preheating reduces thermal gradients between layers, decreasing residual stress and potential warping. It also lowers the energy needed to melt the powder, which can improve part quality by reducing the chances of thermal cracking and distortion. For materials prone to residual stress, like AlSi10Mg, preheating is particularly beneficial in maintaining dimensional accuracy and reducing post-processing needs.

2.1.8 Beam Spot Size

Beam spot size is the diameter of the laser beam on the powder bed. It affects the concentration of energy applied and the width of the melt track. A smaller spot size provides higher precision and can improve detail in intricate parts but may increase build time as more passes are required. Larger spot sizes, while faster, can decrease resolution and lead to a coarser surface finish. For AlSi10Mg, choosing an appropriate beam spot size based on part complexity is essential for achieving a balance between precision and efficiency.

2.2 Post-Processing Techniques

Post-processing techniques are essential for optimizing the properties of Additively Manufactured (AM) AlSi10Mg parts, as they address residual stresses, improve mechanical performance, and enhance surface finish[19,20].

Heat treatment is widely used to relieve residual stresses that develop during the AM process due to rapid heating and cooling cycles. For AlSi10Mg, solution heat treatment followed by aging is common. This approach involves heating the part to a temperature that allows for phase transformation, followed by




Figure 3. Schematic of post-processing method involved AM.

controlled cooling to improve ductility and reduce brittleness. Aging further promotes the precipitation of strengthening phases, which can increase hardness and yield strength. Overall, heat treatment enhances the alloy's ductility and toughness[21]. Hot Isostatic Pressing (HIP) is a post-processing method involving AM part to high temperatures and isostatic pressure within a pressurized chamber. HIP effectively closes internal voids and porosities that may form during the powder bed fusion process, enhancing the part's density and strength. Also, by applying surface finishing techniques, manufacturers can achieve smoother surfaces, enhancing the component's performance in applications where surface interaction is critical, such as in sliding or rotating components[21].

3.0 Mechanical Properties

3.1 Tensile Strength

The tensile strength of Additively Manufactured (AM) AlSi10Mg alloy, particularly when produced through Selective Laser Melting (SLM), is notably higher than that of conventionally cast versions. This enhanced tensile strength is largely attributed to the rapid cooling and solidification inherent in the SLM process[22]. During SLM, a high-energy laser selectively melts regions of AlSi10Mg powder in a layer-by-layer manner, and the rapid cooling that follows creates a unique fine cellular microstructure within the alloy. This microstructure, characterized by small and densely packed grains, leads to increased grain boundary density, which serves as a barrier to dislocation motion. Since dislocation movement within a material generally weakens its structure, the refined grain boundaries in SLM-processed AlSi10Mg significantly increase its tensile strength, making it an attractive option for applications in industries such as aerospace and automotive, where materials are regularly subjected to high stress[23]. However, SLM-processed AlSi10Mg often has limitations in ductility due to residual stresses that accumulate during rapid cooling. These internal stresses can make the material more brittle, increasing fracture risk under certain loads, despite high tensile strength. Additionally, porosity can impact ductility and tensile strength, as incomplete powder melting, or gas entrapment creates voids within the structure that concentrate stress. To balance these effects and improve ductility, post-processing techniques like stress-relief heat treatment and Hot Isostatic Pressing (HIP) are often applied, which effectively reduce internal stresses and porosity, improving both tensile strength and ductility.

3.2 Fatigue Resistance

Fatigue resistance is a vital property for AlSi10Mg components, particularly those used in industries such as aerospace and automotive, where materials are subjected to repeated cyclic loading. Fatigue failure occurs when a material gradually weakens under fluctuating stress, ultimately leading to fracture. The fatigue performance of Additively Manufactured (AM) AlSi10Mg has been studied extensively, with results showing that it is comparable to, and in some cases superior to, conventionally cast AlSi10Mg[24]. This favourable performance in AM AlSi10Mg is attributed to the refined microstructure achieved during the Selective Laser Melting (SLM) process, which typically includes smaller grains and increased grain boundary density, factors that help to resist crack initiation and propagation under cyclic loading[24]. Surface treatments like shot peening and polishing are often applied to improve fatigue resistance, reducing stress concentrators and extending the materials service life under cyclic loads[25]. Despite this, there are factors unique to AM that can negatively affect the fatigue life of AlSi10Mg, most notably surface roughness and internal defects like porosity. During the SLM process, the laser selectively melts layers of AlSi10Mg powder to create a part, but this process often leaves a relatively rough surface. This roughness, composed of partially melted particles, re-solidified splashes, and microscopic peaks and valleys, can act as stress concentrators under cyclic loads. These surface irregularities can initiate microcracks when subjected to fatigue loading, making the material more susceptible to fatigue failure. Comparatively, cast AlSi10Mg generally has a smoother surface finish when freshly manufactured, making it initially less vulnerable to fatigue-induced cracking. Porosity is another critical factor influencing fatigue resistance in AM AlSi10Mg.

Porosity can form when the laser does not fully melt all powder particles, leaving small voids or defects within the material. These pores become weak points, acting as crack initiation sites when the material is under fatigue loading. Pores within the bulk of the material, particularly larger or clustered pores, concentrate stress locally and thus reduce the overall fatigue resistance. In summary, the fatigue endurance of AM AlSi10Mg is comparable to that of conventionally cast material, but it is highly dependent on minimizing surface roughness and internal porosity. Surface treatments like shot peening and polishing play substantial role in enhancing fatigue resistance by reducing surface defects and adding compressive stress.

3.3 Hardness

The hardness of Additively Manufactured (AM) AlSi10Mg alloy is a key property that directly impacts its suitability for applications where wear resistance is critical. During SLM, a high-energy laser selectively melts layers of AlSi10Mg powder, which are then rapidly cooled, leading to a fine cellular microstructure with distinct grain boundaries. The rapid cooling also contributes to the formation of fine silicon particles dispersed throughout the aluminum matrix. One reason for the increased hardness in SLM-processed AlSi10Mg is the high solidification rate. When the melted material cools quickly, smaller and more uniformly distributed silicon particles form within the aluminum matrix. Silicon particles in AlSi10Mg are naturally hard, and their fine distribution increases the material's resistance to deformation. This distribution of silicon particles limits the movement of dislocations, which are defects in the crystal structure that allow materials to deform. As the silicon particles obstruct dislocation movement, they enhance the materials hardness and, by extension, its wear resistance. This wear resistance is particularly advantageous in applications where AlSi10Mg components may be exposed to abrasive or repetitive contact, as seen in the automotive and aerospace industries. Studies have documented the hardness of SLM-processed AlSi10Mg, with reported values typically ranging from 110 to 130 HV (Vickers Hardness). These values are significantly higher than those of conventionally cast AlSi10Mg, which has a coarser micro structure due to slower cooling rates[26]. The difference in cooling rates between SLM and conventional casting results in larger silicon particles within the cast material, which are less effective at hindering dislocation movement. This coarse structure of cast AlSi10Mg generally leads to lower hardness values, making the cast alloy less suitable for high-wear applications compared to its SLM counterpart. The high hardness of AM AlSi10Mg offers multiple advantages, particularly in extending the life of components subject to friction and wear[26]. Components like engine parts, gears, and other automotive and aerospace applications benefit from materials with high hardness because it reduces wear and tear, thereby lowering maintenance needs and improving overall efficiency. In conclusion, the hardness of additively manufactured AlSi10Mg, enhanced by the fine silicon particles and dense microstructure formed during SLM, positions this material as a viable option for applications requiring wear resistance and high hardness. With hardness values ranging from 110 to 130 HV, SLM-processed AlSi10Mg demonstrates notable advantages over conventionally cast versions, primarily due to the unique micro structural characteristics imparted by the SLM process. This makes AM AlSi10Mg particularly suited for high-performance environments, especially in sectors that demand both lightweight and durable materials. Future developments may focus on optimizing post-processing methods to achieve a balance between hardness and ductility, broadening the applicability of SLM-processed AlSi10Mg across an even wider range of industries[27].

4.0 Tribological Properties

4.1 Wear Resistance

Wear resistance is a crucial property for materials used in tribological applications, where components experience frequent friction and potential material degradation over time. Additively Manufactured (AM) AlSi10Mg, especially when processed through Selective Laser Melting (SLM), exhibits significant improvements in wear resistance due to its refined microstructure and enhanced hardness. This wear resistance makes AM AlSi10Mg suitable for high-

performance applications in industries like automotive, aerospace, and manufacturing, where parts are regularly exposed to abrasive or sliding contact[28]. The primary reason for the improved wear resistance in SLM-processed AlSi10Mg lies in the unique microstructure produced by the rapid solidification. During SLM, the laser melts each layer of AlSi10Mg powder and allows it to cool and solidify almost instantaneously. This rapid cooling produces a fine cellular structure with evenly distributed silicon particles, which are naturally hard and resistant to abrasion. In AM AlSi10Mg, the silicon particles are finely dispersed within the aluminum matrix, creating a composite-like structure where the hard silicon particles bear a significant portion of the frictional load. This structure contrasts with the coarser, less uniform distribution of silicon particles seen in conventionally cast AlSi10Mg, where larger grains reduce wear resistance[29]. As a result, the microstructural refinement in SLM-processed AlSi10Mg contributes to higher wear resistance, making it ideal for tribological applications. Moreover, the hardness of SLM-processed AlSi10Mg is an important factor contributing to its wear resistance. Hardness plays a direct role in reducing wear. Higher hardness means that the material is less likely to deform under frictional forces, helping it maintain structural integrity even under abrasive conditions. These conditions make the surface more resistant to crack initiation and propagation, which helps prevent wear-related degradation. When combined with heat treatment, shot peening can significantly improve the materials surface properties, providing both enhanced hardness and resilience under frictional conditions[30]. Fine-tuning these parameters affects the density and homogeneity of the final microstructure. For instance, higher laser power and optimized scanning strategies promote better fusion of powder particles, resulting in a denser material with fewer pores. In summary, the wear resistance of additively manufactured AlSi10Mg is a result of its fine microstructure, enhanced hardness, and the ability to undergo post-processing treatments. With the combination of optimized processing parameters and targeted post-processing methods like heat treatment and shot peening, AM AlSi10Mg is well-suited for tribological applications that require durability, minimal material loss, and stability under high wear conditions. These properties make it a valuable material choice for advanced engineering applications where reliable wear performance is critical.

4.2 Friction Coefficient

The friction coefficient of Additively Manufactured (AM) AlSi10Mg is a critical factor influencing its performance in applications involving sliding wear and frequent material contact, such as in aerospace, automotive, and industrial components. The friction coefficient is a measure of the resistance encountered when two surfaces slide against each other, directly affecting the wear rate, energy efficiency, and operational longevity of parts. In AM AlSi10Mg, this property is largely determined by the surface roughness and the distribution of hard silicon particles within the aluminum matrix[31]. SLM technique for AlSi10Mg, produces a unique microstructure with a fine Si-particles finely dispersed within the aluminum matrix, contributing to a lower friction coefficient compared to conventionally cast AlSi10Mg. These silicon particles are naturally hard and act as microscopic load-bearing elements within the matrix. Their homogeneous distribution means that they reduce localized frictional forces by offering a smooth, consistent interaction between sliding surfaces, which in turn minimizes material deformation under load[32]. This reduction in friction allows AM AlSi10Mg to perform well in tribological applications, where maintaining low friction is essential for efficiency and part longevity. However, surface roughness also plays a keypart in determining the friction coefficient. In AM processes like SLM, the layered structure can leave the surface of AlSi10Mg with some roughness, especially if no post-processing is applied. Rough surfaces increase friction because microscopic peaks and valleys create additional resistance as they met a counterpart surface.

5.0 Microstructure

5.1 As-Built Microstructure

Fine microstructure, which results from the rapid cooling and solidification rates intrinsic to the SLM process, sets it apart from the coarser structure

observed in conventionally manufactured AlSi10Mg. In SLM, a high-energy laser selectively melts a powder layer of AlSi10Mg in a highly controlled manner. Each layer of melted powder solidifies almost instantaneously as the laser moves along the build surface. This rapid solidification creates a unique microstructure marked by a cellular network of aluminum and silicon phases. Specifically, where grains are significantly smaller are found in conventionally cast AlSi10Mg alloy where fine grain structure provides a more robust and homogenous distribution of properties, contributing to the alloy's strength and durability[33]. In SLM-processed AlSi10Mg, silicon remains in a supersaturated state. This super saturation occurs because the rapid cooling does not allow silicon to fully separate out or coalesce into larger particles, as it would in slower cooling processes. As a result, SLM AlSi10Mg exhibits a microstructure with finely dispersed silicon particles distributed evenly throughout the aluminum matrix. These particles strengthen the material by acting as barriers to dislocation movement, thus improving alloy's confrontation to distortion and wear. This homogenous distribution of silicon particles also aids in improving tribological properties, such as wear resistance, by providing a uniform, hard phase throughout the matrix[34]. The fine cellular network observed in SLM AlSi10Mg contributes not only to increased hardness but also to better fatigue resistance. The cellular structure, with its many grain boundaries, hinders the propagation of microcracks under cyclic loading, making it more difficult for cracks to grow and ultimately increasing fatigue life. In conventionally cast AlSi10Mg, enhanced fatigue resistance can be largely attributed to its refined cellular structure, which is a direct outcome of the rapid cooling rates in SLM[35]. Another advantage of the as-built microstructure of AM AlSi10Mg is its improved wear resistance. The dense and fine-grained microstructure, coupled with the presence of hard silicon particles, reduces material loss during sliding or abrasive contact. In conventional manufacturing, AlSi10Mg is prone to coarser silicon particle formations, which do not provide the same level of wear protection as the finely dispersed silicon particles in SLM-processed AlSi10Mg. This micro structural refinement allows AM AlSi10Mg to retain its shape and function even under conditions of high friction or sliding wear, a property highly valued in automotive and aerospace components that experience continuous wear over time. While the as-built microstructure offers considerable benefits, it also presents some challenges, primarily due to the high residual stresses introduced by rapid cooling. These stresses arise because diverse zones of the material cool at slightly altered rates, creating internal strains. In some cases, these residual stresses can affect the materials overall performance by making it more susceptible to cracking or warping. To address this, post-processing treatments are often employed to relieve these stresses, thereby stabilizing the microstructure without significantly altering its favourable properties[36]. This refined microstructure provides a set of enhanced mechanical and tribological properties, including improved hardness, wear resistance, and fatigue life, which distinguish it from conventionally cast AlSi10Mg. These attributes makeAlSi10Mg particularly suitable for high-stress applications in industries that demand materials with durability, and wear endurance. Also, manufacturers can optimize this microstructure to meet specific performance requirements, making it a valuable material choice in advanced engineering applications.

5.2 Effect of Heat Treatment

It is a critical post-treating phase for tailoring microstructure and enhancing the mechanical properties of AlSi10Mg, particularly *via* SLM owing to quick solidifying rates. AlSi10Mg generally has a fine cellular structure with a super saturated aluminum matrix containing dispersed silicon particles. While this as-built microstructure offers considerable advantages, it can also harbour residual stresses and minor defects. Heat treatment provides a means to stabilize and further refine this microstructure, enabling control over properties such as hardness, ductility, and wear resistance. A common heat treatment process for AlSi10Mg involves solutionizing and aging. Solutionizing typically occurs at high temperatures, allowing the silicon and magnesium within the alloy to dissolve into the aluminum matrix. During this stage,

the alloy is held at a solutionizing temperature that facilitates the redistribution of silicon and magnesium atoms within the matrix. This step helps to homogenize the microstructure, eliminate residual stresses, and create a more uniform distribution of alloying elements. Solutionizing also provides a clean slate for the aging process, allowing the desired precipitates to form more evenly[37]. During aging, silicon and magnesium precipitate out of the supersaturated matrix, forming fine, dispersed particles within the aluminum. The presence of finely distributed precipitates increases alloy by preventing the easy faction of dislocations, which in turn enhances resistance to deformation. The refined microstructure resulting from this process is particularly beneficial[38]. However, while aging generally improves hardness and strength, there is a delicate balance in the aging process known as over-aging. Over-aging occurs when the aging process is prolonged beyond the optimal duration, or if the temperature is higher than ideal. During over-aging, the precipitates, instead of remaining fine and evenly dispersed, begin to grow larger and coarser. Coarse precipitates provide fewer obstacles to dislocation movement and can thus diminish the materials hardness and wear resistance. In essence, over-aging reduces the materials mechanical performance by allowing a less favourable microstructure to develop. In AM AlSi10Mg, this reduction in hardness and wear resistance is undesirable for applications that require robust material integrity over time. The precise control of heat treatment parameters is essential to maximize the mechanical benefits of AlSi10Mg. For example, a shorter aging time or a lower aging temperature may be applied to achieve a fine, stable distribution of precipitates without risking over-aging. This control is particularly beneficial in SLM-processed AlSi10Mg, where the rapid cooling has already imparted a degree of refinement to the microstructure. Properly calibrated heat treatment can enhance this fine structure, creating a balance between high tensile strength and sufficient ductility. Heat treatment also contributes to improved wear resistance in AM AlSi10Mg. The presence of fine precipitates distributed throughout the aluminum matrix during optimal aging serves to harden the material, making it more resistant to surface degradation under wear conditions. Applications that expose components to continuous friction or abrasive wear particularly benefit from heat-treated AlSi10Mg. For instance, automotive and aerospace parts that must withstand repeated contact and surface wear can maintain their performance over time due to the hardened, wear-resistant surface created by effective heat treatment[39]. Overall, heat treatment is a valuable tool for optimizing the properties of additively manufactured AlSi10Mg. Through solutionizing and controlled aging, manufacturers can promote the formation of fine precipitates within the aluminum matrix, enhancing hardness, strength, and wear resistance. However, precise control overheat treatment parameters is essential, as over-aging can lead to coarser precipitates, diminishing the mechanical advantages. By tailoring the microstructure through heat treatment, AM AlSi10Mg can be optimized for high-performance applications requiring a sequence of strength, durability, and wear resistance.

5.3 Porosity and Defects

Porosity is a prevalent issue in Additively Manufactured (AM) materials, and AlSi10Mg is particularly susceptible to it by SLM process. Porosity refers to small voids or air pockets within the material that form during fabrication. In AlSi10Mg, these pores typically arise from two primary sources: incomplete melting of powder particles and gas entrapment during the SLM process. These voids act as weak points within the structure, making it more vulnerable to crack initiation and propagation under stress[40]. During SLM, the laser selectively melts metal powder particles to form each layer of the AlSi10Mg component. However, if the laser power, scanning speed, or other parameters are not optimized, incomplete melting can occur. In this case, powder particles may only partially fuse, leaving gaps or pores in the material. This is particularly common when laser energy is insufficient to fully melt the particles or when scanning speeds are too high. In some instances, excess heat can also cause vaporization, leading to the formation of small gas bubbles that are trapped as pores in the solidified metal. These issues result in a porous structure that degrades the materials overall strength and durability. Gas entrapment is another factor contributing to porosity in SLM-processed AlSi10Mg.

When the laser melts the powder, any gases within the powder particles or the surrounding environment can become trapped in the molten pool. As the pool solidifies quickly, there may not be enough time for the gas to escape, leading to the formation of gas porosity. Entrapped gases are particularly problematic because they create spherical voids that are more challenging to eliminate. These gas-induced pores, like those caused by incomplete melting, can compromise the material's mechanical performance by serving as focal points for stress concentration. The impact of porosity on mechanical properties is significant. Pores act as stress concentrators, where stress tends to accumulate under loading conditions. For example, under cyclic loading, a porous structure may fail at much lower stress levels compared to a denser, pore-free structure. This makes minimizing porosity essential for applications requiring high structural integrity, especially in fields like aerospace and automotive, where components are regularly exposed to high and variable loads. To address porosity and enhance the density and mechanical performance of AlSi10Mg, post-processing methods are often employed. HIP is a process that applies both high temperature and high pressure to the part in a pressurized chamber, typically filled with an inert gas. Under these conditions, the material is heated just below its melting point, and the applied pressure compresses any voids within the structure. The combined effects of heat and pressure cause the material to plastically deform around the pores, closing them and eliminating internal voids. This process significantly reduces porosity, leading to a denser and mechanically stronger material[41,42]. In conclusion, porosity is a common but manageable issue in additively manufactured AlSi10Mg. The presence of pores, due to incomplete melting or gas entrapment, can compromise the materials mechanical properties by serving as sites for stress concentration and crack initiation. However, post-processing techniques like hot isostatic pressing offer an effective solution for reducing porosity and improving overall material strength and density. By employing HIP or optimizing AM processing parameters, manufacturers can achieve a more reliable, durable AlSi10Mg component suitable for demanding applications.

6.0 Applications of Additively Manufactured AlSi10Mg

Additively Manufactured (AM) AlSi10Mg is rapidly gaining traction in various high-performance industries, including aerospace, automotive, and electronics makes AlSi10Mg an attractive material for components that must perform reliably under stress while minimizing overall weight. SLM process used in AM enables precise control over the alloy's microstructure and properties, a level of customization difficult to achieve through traditional manufacturing methods. This capability to tailor properties opens a wide range of applications and provides industries with innovative solutions to traditional challenges[43].

6.1 Aerospace Applications

In the aerospace sector, where weight reduction and high-performance materials are paramount, additively manufactured AlSi10Mg is an excellent fit. Components in aircraft structures, such as brackets, supports, and housings, benefit greatly from AlSi10Mg's lightweight and high-strength properties. By reducing component weight, manufacturers can increase fuel efficiency and reduce emissions, which are both critical for sustainable aviation. Moreover, the ability to additively manufacture complicated geometries precisely a digital model allows for the design of parts that optimize material usage without compromising strength. For example, complex lattice structures, which reduce weight while maintaining rigidity, can be produced using AM AlSi10Mg, a design approach nearly impossible with traditional casting methods[44,45]. Components such as landing gear parts and actuator housings experience substantial wear due to constant motion and contact with other surfaces. AM AlSi10Mg's refined microstructure, which provides both hardness and wear resistance, helps these components maintain performance over time with minimal degradation. In heat-intensive applications, such as parts in engines, AlSi10Mg also performs well due to its thermal stability and heat dissipation properties, further enhancing its utility in aerospace[46].

6.2 Automotive Applications

In the automotive area, additively manufactured AlSi10Mg has become a material of choice for several applications, including engine parts, transmission components, and structural elements. AlSi10Mg's strength-to-weight ratio is particularly beneficial for automotive applications where lightweight materials are essential for increasing fuel efficiency and improving vehicle performance. Reducing the weight of engine and transmission components translates to less energy required for acceleration, allowing for better fuel economy and reduced emissions. Additionally, AM AlSi10Mg enables the integration of complex shapes and thin-walled structures, which are useful for manufacturing lightweight, high-performance components with intricate geometries[47]. Engine parts, in particular, benefit from AM AlSi10Mg's thermal conductivity and wear resistance. For instance, cylinder heads, piston heads, and intake manifolds, which are continuously exposed to high temperatures and mechanical stress, require materials that can handle intense operating conditions without degrading[48].

6.3 Electronics Applications

The electronics industry also benefits from the unique properties of additively manufactured AlSi10Mg. Its excellent thermal conductivity and lightweight nature make it ideal for heat exchangers and heat sinks, components essential for managing heat dissipation in electronic devices. Efficient heat dissipation is critical for electronic devices and systems to function reliably, particularly in high-performance applications where processors and other components generate significant heat. AM AlSi10Mg heat sinks and exchangers can be designed with intricate internal channels or lattice structures that maximize surface area, improving cooling efficiency without adding bulk or weight. The design flexibility of AM allows to produce compact yet highly efficient thermal management solutions that traditional casting techniques cannot achieve. In addition to heat management, the dimensional stability and durability of AlSi10Mg make it suitable for electronic enclosures and protective casings. Electronic components often require protective housings to shield them from physical impacts, environmental factors, and thermal stress[49].

6.4 General Advantages of AM AlSi10Mg

One of the key advantages of using additively manufactured AlSi10Mg across these industries is the ability to fine-tune the microstructure to achieve desired properties. Traditional manufacturing techniques, such as casting, have limited control over the microstructure and are subject to constraints such as mold design and cooling rates. In contrast, the SLM process used in AM enables the rapid cooling and solidification necessary to produce a refined microstructure with enhanced mechanical properties[50]. Furthermore, AM allows for reduced lead times and cost savings in prototype development and production. In applications where design customization is essential, AM enables manufacturers to produce parts directly from digital models, which reduces the need for tooling and molds. This level of flexibility is particularly valuable for industries that prioritize rapid prototyping and iterative design processes, such as aerospace and automotive sectors. AlSi10Mg also exhibits excellent mechanical properties, with superior strength, good thermal conductivity, augmented wear resistance, good thermal stability and fatigue resistance, which are critical for components exposed to variable loads and high temperatures. As a lightweight alloy, AlSi10Mg offers high strength while owning component weight low-a critical reason for industries that prioritize fuel efficacy, such as aerospace and automotive. The rapid melting and solidification during the AM process enhance the alloy's microstructure, resulting in refined grains and an improved distribution of silicon, which can boost mechanical properties and resistance to crack propagation[50].

7.0 Conclusion

In conclusion, Additively Manufactured (AM) AlSi10Mg exhibits distinct advantages over conventionally manufactured counterparts, particularly in terms of mechanical, tribological, and microstructural properties. The Selective Laser Melting (SLM) process enables

precise control over the microstructure, resulting in a refined cellular structure with finely dispersed silicon particles that enhance strength, hardness, and wear resistance. This microstructural control, combined with post-processing procedures like HT and HIP allows manufacturers to tailor AlSi10Mg properties for specific high-performance applications in aerospace, automotive, and electronics. However, encounters such as porosity and residual strains remain barriers to the full industrial adoption of AM AlSi10Mg. Porosity, often arising from incomplete melting or gas entrapment, and residual stresses, due to rapid cooling, can compromise fatigue resistance and ductility. Addressing these issues requires further optimization of process parameters and advancements in post-processing. Future research should focus on refining SLM parameters, exploring new post-processing methods, and developing innovative AM techniques that enhance the alloy's properties. By overcoming these challenges, AM AlSi10Mg can be more widely implemented, unlocking its potential in high-demand, structurally critical applications.

8.0 References

1. Gibson I, Rosen D, Stucker B, *et al*. Additive manufacturing technologies. Springer; 2015.
2. Campbell T. The promise of 3D printing. Atlantic Council; 2012.
3. Bourell DL, Rosen DW, Leu MC. Roadmap for additive manufacturing. The National Academies Press; 2014.
4. DebRoy T, Wei HL, Zuback JS, Mukherjee T, Elmer JW, Milewski JO, Zhang W. Additive manufacturing of metallic components-Process, structure, and properties. Prog Mater Sci. 2018; 92:112-224. https://doi.org/10.1016/j.pmatsci.2017.10.001
5. Yadav SPS, Ranganath S, Sharieff S, Suresh R, Avinash L. Investigations on the change in state of stress with respect to the sliding direction in dry sliding wear of hard elastic material with different geometry and orientation on ductile flat surface. FME Trans. 2020; 48(3):716-723. https://doi.org/10.5937/fme2003716S
6. Murr LE, Gaytan SM, Medina F, Lopez H, Martinez E, Machado BI, Hernandez DH, Wicker RB, *et al*. Next-generation biomedical implants using additive manufacturing of complex, cellular, and functional mesh arrays. Philos Trans R Soc A Math Phys Eng Sci. 2010; 368(1917):1999-2032. https://doi.org/10.1098/rsta.2010.0010
7. Read N, Wang W, Essa K, Attallah MM. Selective laser melting of AlSi10Mg alloy: Process optimization and mechanical properties development. Mater Des. 2015; 65:417-424.
8. Aboulkhair NT, Simonelli M, Parry L, Ashcroft I, Tuck C, Hague R. 3D printing of aluminium alloys: Additive manufacturing of Al-Al_2O_3 nanocomposites using selective laser melting. Mater Des. 2016; 106:263-273.
9. Jadhav SD, Liu C, Thakur A, Yang J. Effect of scanning speed on the microstructure and mechanical behavior of selective laser melted AlSi10Mg. Mater Sci Eng A. 2019; 748:228-239.
10. Sahadevan P, Chithirai PS, Lakshmikanthan A, Bhaumik A, Cuautle AF. Effect of printing process parameters on tensile strength and wear rate of 17-4PH stainless steel deposited using SLM process. Frattura Integrita Strutt. 2024; 18(70):157-176. https://doi.org/10.3221/IGF-ESIS.70.09
11. Liu W, Ma J, Luo J, Zhang Z. Effects of process parameters on microstructure and mechanical properties of AlSi10Mg produced by selective laser melting. Mater Des. 2018; 140:153-162.
12. Yu T, Li S, Zhang C, Chen Z. Porosity evolution and its influence on the mechanical properties of AlSi10Mg fabricated by selective laser melting. Mater Sci Eng A. 2020; 799:139890.
13. Kumar VS, Girish PA, Prasad M. Evaluation of microstructure and mechanical properties of Al6005 MMCs reinforced with B4C via stir casting route and optimisation through ANOVA DOE technique. Adv Mater Technol. 2024; 10. https://doi.org/10.1080/2374068x.2024.2306036
14. Qiu C, Panwisawas C, Ward M, Basoalto HC, Brooks JW, Attallah MM. On the role of melt flow into the surface structure and porosity development during selective laser melting. Acta Mater. 2015; 96:72-79. https://doi.org/10.1016/j.actamat.2015.06.004
15. Li P, Warner D, Fatemi A, Phan N. Critical assessment of the fatigue performance of additively manufactured metallic materials. Int J Fatigue. Elsevier. 2016; 93:257-271.
16. Attar H, Calin M, Zhang LC, Scudino S, Eckert J. Manufacture by selective laser melting and mechanical behavior of commercially pure titanium. Mater Sci Eng A. 2014; 593:170-177. https://doi.org/10.1016/j.msea.2013.11.038

17. Sun SH, Kuo C, Hsu KY. Applications of AlSi10Mg alloy produced by selective laser melting. Addit Manuf. 2019; 28:434-446.
18. Kumar S, Rahman Z. Properties and applications of additively manufactured AlSi10Mg alloy in automotive industry. J Mater Process Technol. 2020; 293:117-124.
19. Supriya B, Thimmaiah MB, *et al*. Wear behavior of AA2219-B4C composite fabricated *via* stir casting followed by age hardening. J Inst Eng India Ser D. 2024. https://doi.org/10.1007/s40033-024-00736-2
20. Louvis E, Fox P, Sutcliffe CJ. Selective laser melting of aluminium components. J Mater Process Technol. 2011; 211(2):275-284. https://doi.org/10.1016/j.jmatprotec.2010.09.019
21. Li Y, Zhang X, Chen Z. Controlling microstructure in AM of AlSi10Mg through parameter optimization. Mater Des. 2021; 194:108-116.
22. Sercombe TB, Li X. Selective laser melting of aluminium and aluminium metal matrix composites- Review. Mater Technol. Taylor and Francis. 2016; 31(2):77-85. https://doi.org/10.1179/1753555715Y.0000000078
23. Thijs L, Verhaeghe F, Craeghs T, Humbeeck JV, Kruth JP. A study of the microstructural evolution during selective laser melting of Ti–6Al–4V. Acta Mater. 2010; 58(9):3303-3312. https://doi.org/10.1016/j.actamat.2010.02.004
24. Suard M, Ebel T, Friedrich B. Selective laser melting of AlSi10Mg alloy. Mater Des. 2014; 61:140-150.
25. Amato KN, Gaytan SM, Murr LE, Martinez E, Shindo PW, Hernandez J, *et al*. Microstructures and mechanical behavior of Inconel 718 fabricated by selective laser melting. Acta Mater. 2012; 60(5):2229-2239. https://doi.org/10.1016/j.actamat.2011.12.032
26. Murr LE, Gaytan SM, Medina F, *et al*. Next-generation biomedical implants using additive manufacturing of complex, cellular, and functional mesh arrays. Philos Trans R Soc A Math Phys Eng Sci. 2010; 368(1917):1999-2032. https://doi.org/10.1098/rsta.2010.0010
27. Li P, Warner DH, Fatemi A, Phan N. Critical assessment of the fatigue performance of additively manufactured metallic materials. Int J Fatigue. Elsevier. 2016; 93:257-271.
28. Attar H, Calin M, Zhang LC, Scudino S, Eckert J. Selective laser melting and mechanical behavior of Al-Si alloys. Mater Sci Eng A. 2014; 640:280-289.
29. Rangappa R, Patel GCM, Chate GR, *et al*. Coaxiality error analysis and optimization of cylindrical parts of CNC turning process. Int J Adv Manuf Technol. 2022; 120:6617-6634. https://doi.org/10.1007/s00170-022-09184-2
30. Liu C, Wang Y, Wu J. Effects of laser parameters on microstructure and properties of AlSi10Mg. Mater Sci Eng A. 2019; 737:270-278.
31. Zhang Y, Xu Z. Impact of scan speed on AlSi10Mg in selective laser melting. Mater Process J. 2020; 2:42-55.
32. Read N, Wang W, Essa K, Attallah MM. Selective laser melting of AlSi10Mg alloy: Process optimization and mechanical properties development. Mater Des. 2015; 65:417-424. https://doi.org/10.1016/j.matdes.2014.09.044
33. Shankar VK, Lakshmikanthan A, Selvan CP, *et al*. Prediction of transient temperature at bit-rock interface using numerical modelling approach and optimization. Int J Interact Des Manuf. 2024; 18:6109-6121. https://doi.org/10.1007/s12008-023-01543-x
34. Casati R, Vedani M. Metal matrix composites reinforced by nano-particles- A review. Metals. 2014; 4(1):65-83. https://doi.org/10.3390/met4010065
35. Qiu C, Panwisawas C, Ward M, Basoalto HC, Brooks JW, Attallah MM. On the role of melt flow into the surface structure and porosity development during selective laser melting. Acta Mater. 2015; 96:72-79. https://doi.org/10.1016/j.actamat.2015.06.004
36. Kumaraswamy S, Malik V, Devaraj S, Jain VK, Lakshmikanthan A. A study of shear friction factor in friction stir welding for developing a finite element model and its importance in the context of formation of defect-free and defective weld. Mater Today Proc. 2021; 45(Part):299-303. https://doi.org/10.1016/j.matpr.2020.10.651
37. Hooreweder BV, Moens D, Boonen R, *et al*. Analysis of fracture toughness and crack propagation of Ti6Al4V produced by selective laser melting. Adv Eng Mater. 2012; 14(1-2):92-97. https://doi.org/10.1002/adem.201100233
38. Qian M, Das S. Selective laser melting and its effects on microstructure and properties of alloys. J Mater Process Technol. 2015; 1(7):389-403.
39. Tang M, Pistorius PC. Oxides, porosity, and fatigue performance of AlSi10Mg parts produced by selective laser melting. Int J Fatigue. 2017; 94:192-201. https://doi.org/10.1016/j.ijfatigue.2016.06.002
40. Sheshadri R, Nagaraj M, Lakshmikanthan A, *et al*. Experimental investigation of selective laser melting parameters for higher surface quality and microhardness properties: Taguchi and super ranking concept approaches. J Mater Res Technol. 2021; 14:2586-2600. https://doi.org/10.1016/j.jmrt.2021.07.144

41. Liu W, Ma J, Luo J, Zhang Z. Effects of surface finishing on microstructure and mechanical properties of AlSi10Mg produced by SLM. Mater Des. 2018; 140:153-162.
42. Weng F, Zhang H, Brochu M. A review of additive manufacturing of aluminum alloys and aluminum matrix composites. J Mater Sci Technol. 2017; 33(4):407-422.
43. Sahadevan P, Selvan CP, Bhaumik A, Lakshmikanthan A. Selective laser melting parametric optimization for microhardness of 17-4 PH stainless steel. J Mines Metals Fuels. 2023; 71(12):2512-2519. https://doi.org/10.18311/jmmf/2023/35128
44. Sun SH, Kuo C, Hsu KY. Applications of AlSi10Mg alloy produced by selective laser melting. Addit Manuf. 2019; 28:434-446.
45. Murr LE, Amato KN, Gaytan SM, *et al*. Microstructures and mechanical behavior of Inconel 718 fabricated by selective laser melting. Acta Mater. 2010; 60(5):2229-2239. https://doi.org/10.1016/j.actamat.2011.12.032
46. Sahadevan P, Selvan CP, Bhaumik A, Lakshmikanthan A. Surface roughness optimization of selective laser melting printed 17-4 PH stainless steel parts. J Mines Metals Fuels. 2023; 71(12):2405-2413. https://doi.org/10.18311/jmmf/2023/35123
47. Ning Y, Cong W, Qi H. Review of additive manufacturing of high-performance materials: Alloys, ceramics, and composites. J Mater Process Technol. 2018; 257:48-72.
48. Hooreweder BV, David M, Rene B, Jean-Pierre K, Paul S. Analysis of fracture toughness and crack propagation of Ti6Al4V produced by selective laser melting. Adv Eng Mater. 2012; 14(1-2):92-97
49. Liu W, Ma J, Luo J, Zhang Z. Effects of surface finishing on microstructure and mechanical properties of AlSi10Mg produced by SLM. Mater Des. 2018; 140:153-162.
50. Qian M, Das S. Selective laser melting and its effects on microstructure and properties of alloys. J Mater Process Technol. 2015; 1(7):389-403.