Journal of Mines, Metals and Fuels, *73(7): 1973-1985; 2025. DOI: 10.18311/jmmf/2025/49194*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.co.in/index.php/jmmf*

A Comprehensive Study on Challenges in Gear Manufacturing using Fused Deposition Modeling

Swapnil Mukadam[1*], Vishal Sulakhe[1], Kiran Kaware[1] and Kamalkishor Maniyar[2]

[1]Department of Mechanical Engineering, School of Engineering and Technology (SOET), Sandip University, Nashik- 422213, Maharashtra, India; latestresearch22@gmail.com

[2]Department of Mechanical Engineering, Dr. D. Y. Patil Institute of Technology, Pimpri - 411018, Pune, Maharashtra, India

Abstract

Aim: *This paper aims to explore the challenges faced in manufacturing gears using Fused Deposition Modeling (FDM), an additive manufacturing technique, and to identify strategies for optimizing the process. Gears are integral to numerous mechanical systems, and their manufacturing demands precision, strength, and durability. However, applying FDM for gear production introduces unique challenges related to the technology's inherent layer-by-layer construction. This paper delves into these barriers, focusing on dimensional accuracy, material limitations, and surface finish. Furthermore, it seeks to bridge the gap between current capabilities and the requirements for functional, high-performance gears using FDM.* **Methodology***: The study conducts a comprehensive review of the literature on FDM technology, focusing on its application in gear production. It analyzes challenges such as dimensional accuracy, material properties, surface finish, and long-term durability, and highlights advancements in materials, process parameters, and post-processing techniques.*

Major Findings: *Key challenges in FDM gear production include issues with mechanical strength, wear resistance, and surface roughness. Recent advancements, such as material innovations and process optimization, show potential in addressing these hurdles and improving the feasibility of FDM for gear manufacturing.* **Value:** *This paper provides a focused review on the application of FDM in gear manufacturing, offering practical insights and recommendations for researchers and practitioners. By addressing critical barriers, it contributes to advancing the use of FDM in producing functional gears.*

Keyword: *Additive Manufacturing, 3D Printing, Fused Deposition Modeling, Gear Manufacturing, Layer Adhesion, Mechanical Properties, Polymer Materials*

1.0 Introduction

Additive Manufacturing (AM), commonly referred to as 3D printing, represents a transformative shift in industrial production, enabling the creation of complex geometries and highly customized parts that were previously unachievable with traditional subtractive manufacturing methods. Unlike traditional manufacturing methods that typically involve subtracting material from a solid block, Additive Manufacturing (AM) constructs objects layer by layer from digital models. This incremental approach enhances design flexibility, improves material efficiency, and enables the creation of parts with complex internal structures. A key benefit of AM is its capacity to produce intricate parts swiftly and economically, especially suited for low-volume production. This makes it an ideal choice for prototyping, allowing designers to iterate rapidly and test multiple design variations without the high costs associated with traditional tooling and machining processes. Additionally, AM is gaining traction for

**Author for correspondence*

producing end-use components in sectors like aerospace, automotive, healthcare, and consumer goods, thanks to its advantages in weight reduction, customized geometries, and material efficiency[1,2].

2.0 Literature Summary

There are several key techniques within the realm of additive manufacturing, each with its unique processes, materials, and applications. These include Stereolithography (SLA), Selective Laser Sintering (SLS), Fused Deposition Modeling (FDM), Digital Light Processing (DLP), Binder Jetting, Direct Metal Laser Sintering (DMLS), and Electron Beam Melting (EBM), tabulated in Table 1. Each method has unique benefits and is tailored for specific applications. For example, SLA and DLP are renowned for their high precision and smooth surface finishes, making them ideal for detailed prototypes and dental uses. SLS and DMLS, on the other hand, are capable of producing functional parts with complex geometries and high strength, ideal for aerospace and medical implants[3,4,5].

In this journal article, we explore the challenges associated with gear manufacturing using Fused Deposition Modeling (FDM). While FDM provides notable benefits like cost-effectiveness and compatibility with various thermoplastics, it also faces specific challenges, especially in manufacturing high-precision, durable gears. Issues such as layer adhesion, surface finish, material properties, and dimensional accuracy are critical factors that need to be addressed to optimize FDM for gear manufacturing. By examining these challenges and reviewing recent advancements in FDM technology, this article aims to provide a comprehensive overview and offer potential solutions to improve the feasibility and performance of FDM in gear manufacturing.

3.0 Fused Deposition Modeling in Gear Manufacturing

Fused Deposition Modeling (FDM) is a widely adopted additive manufacturing technique because of its simplicity, cost-efficiency, and ability to work with various thermoplastic materials. In FDM, a thermoplastic filament is heated until it melts and is then extruded layer by layer to create a part directly from a digital model. This method is favored for prototyping and low-volume production due to its capacity to produce complex

Table 1. Different additive manufacturing techniques with its application

Technique	Process Description	Applications	Advantages	References
Stereolithography (SLA)	Uses a laser to cure liquid resin into hardened plastic layer by layer	Detailed prototypes, dental molds, jewellery	High precision, smooth surface finish	6,7
Selective Laser Sintering (SLS)	Uses a laser to sinter powdered material, binding it to create a solid structure	Functional prototypes, complex geometries	No need for support structures	8,9
Fused Deposition Modeling (FDM)	Extrudes thermoplastic filaments through a heated nozzle, layer by layer	Prototyping, manufacturing aids, low-volume	Cost-effective, uses a wide range of thermoplastics	10,11
Digital Light Processing (DLP)	Uses a digital projector screen to flash an image of each layer across the platform	High-resolution prototypes, dental models	Faster than SLA, fine details	12,13
Binder Jetting	Deposits a liquid binding agent over layers of powder particles	Metal parts, sand casting molds, full-color	Can create complex geometries, use various materials	14,15
Direct Metal Laser Sintering (DMLS)	Uses a laser to sinter powdered metal, creating fully dense metal parts	Aerospace, medical implants, high-strength components	Produces strong, high-density parts	16,17
Electron Beam Melting (EBM)	Uses an electron beam to melt and fuse metal powder in a vacuum chamber	Aerospace parts, medical implants, complex geometries	High melting capacity, vacuum ensures part quality	18,19




Figure 1. Workflow of FDM process.

geometries quickly and at a relatively low cost[20,21]. The FDM process starts with the creation of a 3D digital model using CAD software, which is then sliced into thin layers that serve as a blueprint for the printer. During printing, the filament is fed through a heated extruder, which melts the material and deposits it onto the build platform. The extruder moves horizontally and vertically, following the path defined by the sliced layers, to construct the part layer by layer. After each layer is completed, the platform moves down, and the process repeats until the entire part is formed[22]. This procedure, illustrated in Figure 1, involves creating a 3D digital model with CAD software, slicing the model into thin layers, and then extruding and depositing the thermoplastic filament layer by layer.

4.0 Applications of Additive Manufacturing

Additive Manufacturing (AM) has transformed multiple industries by facilitating the creation of complex geometries, customized components, and lightweight structures. This article examines the primary applications of AM, particularly in the production of additively manufactured gears, and its influence on lightweight components, architectural prototypes, medical devices, and artistic creations. AM enables the fabrication of gears with intricate geometries that are challenging or impossible to achieve through conventional manufacturing methods. This capability is especially advantageous for developing lightweight, high-strength gears with optimized internal structures. AM gears can be tailored for specific applications, improving performance and efficiency. However, challenges such as material properties, surface finish, and dimensional accuracy need to be addressed to fully realize the potential of AM gears[23,24]. For example, issues related to layer adhesion and anisotropic properties can impact the performance of FDM-printed gears[25,26].

4.1 Lightweight Components

Additive Manufacturing (AM) allows for the creation of lightweight components by designing intricate lattice structures and optimizing topologies, thereby reducing weight without sacrificing strength. This is especially beneficial in the aerospace and automotive sectors, where weight reduction is essential for enhancing fuel efficiency and overall performance. AM allows for material placement only where necessary, resulting in significant weight savings[27,28]. For instance, the use of lattice structures can lead to substantial weight reductions in aerospace components while maintaining structural integrity[29,30].

4.2 Architectural Prototypes

In architecture, AM is used to create detailed scale models and prototypes of buildings and structures. This technology allows architects to explore complex designs and geometries that are difficult to achieve with traditional model-making techniques. AM also facilitates rapid prototyping, enabling architects to quickly iterate and refine their designs[31,32]. The ability to produce intricate architectural models helps in visualizing and communicating design concepts effectively[33,34].

4.3 Medical Applications

Additive Manufacturing (AM) has significantly influenced the medical field by facilitating the production of customized implants, prosthetics, and surgical instruments. Custom implants and prosthetics can be precisely tailored to match the unique anatomy of individual patients, thereby enhancing comfort and functionality. Moreover, AM enables the creation of intricate geometries in surgical instruments, improving their performance and usability[35,36]. The ability to produce

patient-specific implants significantly improves surgical outcomes[37,38].

4.4 Art Applications

Artists and designers utilize AM to craft intricate and innovative pieces that extend beyond the limitations of traditional art forms. AM facilitates the creation of complex and detailed artworks that would be difficult or impossible to produce manually. This technology also allows for the exploration of new materials and techniques, expanding the possibilities of artistic expression[39,40]. AM's flexibility and precision open up new avenues for creativity and artistic experimentation[41,42].

5.0 Barriers in Additive Manufacturing

While Additive Manufacturing (AM) provides notable benefits such as design flexibility, cost-efficiency, and rapid prototyping, several barriers and defects can hinder its effectiveness, especially in gear manufacturing. This section discusses key challenges, including void formation, stair stepping, and build volume limitations.

5.1 Void Formation

Void formation is a common defect in AM, where gaps or voids appear within the printed material. These voids can occur due to insufficient fusion between layers, improper extrusion rates, or contamination within the material feedstock. In gear manufacturing, voids can significantly reduce the mechanical strength and durability of the gears, leading to premature failure under operational loads.

1. Insufficient fusion between layers: This occurs when the bonding between successive layers is inadequate, often due to incorrect temperature settings or insufficient heat transfer, which prevents the layers from fusing properly[43,44].
2. Improper extrusion rates: Variations in the extrusion rate can lead to uneven material deposition, resulting in gaps or voids within the printed structure. This is particularly problematic in high-stress applications like gear manufacturing[45].
3. Contamination: Foreign particles within the filament or feedstock can cause voids, affecting the integrity of the printed part[46,47].

Void formation can lead to reduced load-bearing capacity and increased brittleness of gears, making them unsuitable for critical applications. Figure 2 illustrates the void formation within FDM-printed gears, which can significantly reduce mechanical strength and durability.

5.2 Stair Stepping

Stair stepping is a surface defect that arises due to the layer-by-layer construction inherent to AM processes. This effect is especially pronounced on inclined or curved surfaces, resulting in a stepped appearance rather than a smooth finish. In gear manufacturing, stair stepping can lead to increased friction and wear, reducing the efficiency and lifespan of the gears.

1. Layer height: Smaller layer heights can reduce the severity of stair stepping but increase printing time. Optimal layer height must balance surface quality and production efficiency[49,50].




Figure 2. Void formation in FDM printed gears: **(a)** 3D model illustrating the air voids **(b)** SEM image displaying the air voids[48].




Figure 3. Examples of stair stepping in FDM printed parts[54].

2. Print orientation: Orienting the part to minimize inclined surfaces can help reduce stair stepping, but this may not always be feasible for complex geometries[51].
3. Post-processing: Methods like sanding, polishing, or chemical smoothing can reduce the impact of stair stepping, but they introduce extra steps and costs to the manufacturing process[52,53].

The presence of stair stepping in gears can compromise their operational performance by introducing surface irregularities that increase friction and wear. The FDM process, shown in Figure 3, starts with designing a 3D digital model using CAD software. The model is then sliced into thin layers, and the thermoplastic filament is extruded and deposited layer by layer.

5.3 Build Volume

The build volume in Additive Manufacturing (AM) refers to the largest size of an object that can be printed in a single run. Constraints in build volume can create considerable challenges when manufacturing larger gears or assemblies in a single piece.

1. Machine size: The build volume is directly dependent on the size of the AM machine. Larger machines can print bigger parts but are more expensive and require more space[55].
2. Part segmentation: Large parts often need to be printed in segments and then assembled, which can introduce weak points and require additional assembly steps[56,57].
3. Design constraints: The design of the part must consider the build volume to avoid the need for segmentation. This can limit the complexity and size of gears that can be manufactured[58,59].

These limitations necessitate careful planning and design optimization to ensure that large or complex gears can be effectively manufactured using AM.

5.4 Materials and Discussion

Additive manufacturing, particularly Fused Deposition Modeling (FDM), utilizes various polymer materials that offer distinct mechanical properties, thermal stability, and printability. Table 2 summarizes the key properties of different polymer materials used in FDM technology, highlighting their applications in gear manufacturing.

Acrylonitrile Butadiene Styrene (ABS) is known for its robustness, good impact resistance, and ease of processing, making it suitable for gears that need to withstand moderate mechanical stress. ABS exhibits high impact resistance, with a tensile strength of 40-50 MPa and an elongation at break of 5-10%. Its thermal properties include a glass transition temperature of around 105°C. While it offers moderate wear resistance, its processing characteristics feature good layer adhesion and surface finish, though warping and layer delamination can occur if printing parameters are not optimized[60-64]. Polylactic Acid (PLA) is favored for its ease of printing, biodegradability, and good surface finish, though it is more brittle compared to ABS. PLA demonstrates a higher tensile strength of 60 MPa but lower impact resistance and elongation at break (2-5%). PLA has a glass transition temperature of about 60°C and low wear resistance, but it is highly regarded for its excellent printability, minimal warping, and strong layer adhesion[65-69]. On the other hand, Nylon (polyamide) is noted for its high strength, flexibility, and exceptional wear resistance, making it a popular choice for functional gears. Nylon boasts mechanical properties such as a high tensile strength of 50-80 MPa and excellent elongation at break (up to 50%). It has a glass transition temperature of around 70°C, high wear resistance, and good self-lubricating properties. However, Nylon's processing is challenging due to its tendency to absorb moisture, necessitating proper storage and drying[70-74].

Table 2. Different material properties of polymer used in gear manufacturing

Material	Tensile Strength (MPa)	Elongation at Break (%)	Glass Transition Temperature (°C)	Melting Point (°C)	Wear Resistance	Printability	Key Applications	References
ABS	40-50	5-10	105	N/A	Moderate	Good	Prototyping, moderate mechanical stress	60-64
PLA	60	2-5	60	150-160	Low	Excellent	Prototyping, low-stress applications	65-69
Nylon (Polyamide)	50-80	Up to 50	70	220-260	High	Challenging	Functional parts, moving components	70-74
PEEK	90-100	Up to 30	143	343	Very high	Challenging	High-demand applications, heavy-duty gears	75-79
TPU (Thermoplastic Polyurethane)	25-40	300-550	-35	180-220	High	Moderate	Flexible components, seals, gaskets	80-82
PETG (Polyethylene Terephthalate Glycol)	50-70	5-15	70-80	210-250	High	Good	Functional parts, water-resistant applications	83-85

Polyether Ether Ketone (PEEK) is a high-performance engineering thermoplastic recognized for its outstanding mechanical properties, chemical resistance, and thermal stability. PEEK features a very high tensile strength (90-100 MPa) and a good elongation at break (up to 30%). It has a high glass transition temperature (143°C) and a melting point of 343°C. PEEK's wear resistance is very high, but it requires specialized equipment and careful handling to prevent warping during processing[75-79]. Thermoplastic Polyurethane (TPU) is valued for its flexibility and durability, making it ideal for parts requiring elasticity. TPU has a tensile strength of 25-40 MPa and an elongation at break of 300-550%. Its thermal properties include a glass transition temperature of -35°C. TPU offers high wear resistance and moderate printability, producing flexible and durable parts[80-84].

Polyethylene Terephthalate Glycol (PETG) blends the printability of PLA with the strength and durability of ABS. PETG has a tensile strength of 50-70 MPa and an elongation at break of 5-15%. It possesses thermal properties with a glass transition temperature of 70-80°C and exhibits high wear resistance. PETG is noted for its good printability and suitability for water-resistant applications[85]. Figure 4 provides a comparative view of the surface finish achieved using various polymer materials in FDM, highlighting the differences in surface quality and dimensional accuracy.

6.0 Drawbacks and Limitations of Fabricating Gears Using Polymer Materials

Despite the advantages of Fused Deposition Modeling (FDM) in manufacturing gears, several drawbacks and limitations are associated with using different polymer materials. For instance, Acrylonitrile Butadiene Styrene (ABS) is known for its robustness and good impact




Figure 4. Comparison of surface finish for different polymer materials[57].

resistance, making it suitable for gears needing to withstand moderate mechanical stress. However, ABS is prone to warping and shrinkage during cooling, leading to dimensional inaccuracies and poor layer adhesion. It can also be brittle under certain conditions, has a poor surface finish that often requires post-processing, and degrades under UV light and certain chemicals, limiting its use in harsh environments. Polylactic Acid (PLA), favored for its ease of printing, biodegradability, and good surface finish, is more brittle compared to other thermoplastics like ABS. PLA's brittleness makes it less suitable for gears subjected to impact or high stress. Its low glass transition temperature (around 60°C) limits its application in higher temperature environments, and its poor wear resistance results in faster wear under frictional forces. Additionally, PLA's biodegradability can be a disadvantage in humid environments where it might degrade faster.

Nylon (polyamide) is well-regarded for its high strength, flexibility, and excellent wear resistance, making it a popular choice for functional gears. However, nylon's tendency to absorb moisture from the environment can impact its mechanical properties and cause dimensional instability. Printing with nylon can be difficult due to its warping tendency, high printing temperature requirements, and need for controlled environments. Nylon filaments are generally more expensive than PLA or ABS, increasing the overall production cost, and achieving a good surface finish can be difficult, often requiring post-processing. Polyether Ether Ketone (PEEK) is a high-performance engineering thermoplastic renowned for its outstanding mechanical properties, chemical resistance, and thermal stability. PEEK exhibits very high tensile strength and good elongation at break, with a high glass transition temperature (143°C) and melting point (343°C). However, PEEK's significantly higher cost compared to other thermoplastics restricts its use to high-performance applications. Printing PEEK requires high extrusion temperatures (around 400°C) and a heated build chamber, necessitating specialized equipment. Additionally, PEEK is prone to warping during the printing process, requiring careful control of printing conditions, and its high cost and specific printing requirements make it less widely available.

Thermoplastic Polyurethane (TPU) is valued for its flexibility and durability, making it ideal for parts requiring elasticity. However, TPU's flexibility necessitates slower printing speeds, increasing production time. Achieving high dimensional accuracy with TPU can be difficult due to its tendency to deform during printing, often necessitating post-processing to attain the desired surface finish and mechanical properties. Additionally, TPU is generally more costly than standard PLA or ABS, increasing production expenses. Polyethylene Terephthalate Glycol (PETG) merges the ease of printing of PLA with the strength and durability of ABS. Although PETG offers good layer adhesion, achieving optimal adhesion can be challenging, particularly for larger parts. PETG also tends to string and ooze during printing, which can affect the dimensional accuracy and surface finish of printed gears. Consequently, parts printed with PETG often require post-processing to remove strings and enhance the surface finish. Additionally, PETG requires precise control of printing conditions, including temperature and cooling, to avoid warping and achieve high-quality prints.

7.0 Future Recommendations

To advance the field of gear manufacturing using Fused Deposition Modeling (FDM), several key areas of research and development should be pursued. These recommendations aim to address the current challenges and unlock the full potential of FDM in producing high-quality, durable gears.

7.1 Material Development

Developing new polymer composites and blends tailored for gear manufacturing is essential. These materials should

provide superior mechanical properties, including higher tensile strength, impact resistance, and wear resistance, while ensuring good printability. Research should focus on reinforcing polymers with fibers (*e.g.*, carbon, glass) or adding additives to enhance thermal and mechanical performance.

7.2 Optimization of Printing Parameters

To mitigate issues like warping, layer delamination, and void formation, a deeper understanding and optimization of FDM printing parameters are essential. This includes exploring the effects of nozzle temperature, print speed, layer height, and cooling rates on the final part quality. Advanced modeling and simulation techniques could help predict and optimize these parameters for gear manufacturing. Figure 5 illustrates how different printing parameters, including nozzle temperature and print speed, affect the dimensional accuracy of gears produced using FDM technology.

7.3 Post-processing Technique

The advancement and standardization of post-processing methods, including annealing, surface finishing, and coating, can greatly enhance the surface quality and mechanical properties of gears produced through FDM. Research should focus on identifying the most effective post-processing methods that enhance gear performance without compromising dimensional accuracy. Figure 6 showcases different post-processing techniques, including annealing and surface finishing, used to enhance the surface quality and mechanical properties of FDM-printed gears.




Figure 5. Effect of printing parameters on dimensional accuracy[61].




Figure 6. Post-processing techniques for FDM printed gears[65].

7.4 Design for Additive Manufacturing (DfAM)

Encouraging the adoption of DfAM principles can help in designing gears that are optimized for the FDM process. This includes rethinking gear geometries to reduce stress concentrations, improve load distribution, and minimize material usage while maintaining performance. Topology optimization and generative design tools can be instrumental in this aspect.

7.5 Real-time Monitoring and Control

Implementing real-time monitoring and control systems in FDM printers can help detect and correct defects during the printing process. Techniques such as *in-situ* metrology, machine learning algorithms, and feedback control systems can enhance print reliability and consistency, leading to higher-quality gears.

7.6 Hybrid Manufacturing Approaches

Combining FDM with other manufacturing processes, such as subtractive machining or laser sintering, could address some of the limitations of FDM. Hybrid approaches can leverage the strengths of different techniques to produce gears with superior properties and precision.

7.7 Environmental and Sustainability Considerations

Future research should also prioritize the environmental impact of FDM gear manufacturing. This involves creating recyclable and biodegradable materials, enhancing energy efficiency, and minimizing waste during the printing process. Embracing sustainable manufacturing practices will be essential for the wider adoption of FDM across various industries.

7.8 Industry Collaboration and Standardization

Collaboration among academia, industry, and standardization bodies is essential to establish industry-wide standards and best practices for FDM gear manufacturing. Such standards will ensure consistency, reliability, and quality across various applications and industries.

By addressing these future recommendations, the challenges in gear manufacturing using FDM can be significantly mitigated, paving the way for more widespread adoption and innovative applications of this technology.

8.0 Conclusions

Fused Deposition Modeling (FDM) has established itself as a prominent technique in additive manufacturing due to its simplicity, cost-effectiveness, and versatility. Despite these advantages, the application of FDM in gear manufacturing presents several challenges. Issues such as void formation, stair stepping, and build volume limitations significantly impact the quality and performance of FDM-printed gears. Material selection also plays a critical role, with common polymers like ABS, PLA, Nylon, PEEK, TPU, and PETG each offering distinct advantages and drawbacks. ABS and PLA are easy to print but suffer from issues like warping and brittleness, while high-performance materials like PEEK offer excellent mechanical properties but require specialized equipment and handling.

To overcome these challenges, future research should focus on several key areas. The development of new polymer composites and blends specifically designed for gear manufacturing could enhance mechanical properties and printability. Optimization of printing parameters and post-processing techniques is essential to improve surface finish and dimensional accuracy. Adopting Design for Additive Manufacturing (DfAM) principles can help in optimizing gear designs for the FDM process. Additionally,

implementing real-time monitoring and control systems can enhance print reliability and consistency.

Hybrid manufacturing approaches, combining FDM with other techniques, can address some of the inherent limitations of FDM. Environmental and sustainability considerations should also be prioritized, including the development of recyclable and biodegradable materials. Finally, collaboration between academia, industry, and standardization bodies is crucial to develop industry-wide standards and best practices for FDM gear manufacturing. By addressing these recommendations, the challenges in gear manufacturing using FDM can be significantly mitigated, paving the way for more widespread adoption and innovative applications of this technology.

9.0 References

1. Wohlers T, Caffrey T. Wohlers report 2020: 3D printing and additive manufacturing state of the industry annual worldwide progress report. 2020.
2. PopraweR. Laser additive manufacturing: Materials, design, technologies, and applications. Springer. 2019.
3. Hull CW. Stereolithography for rapid prototyping and manufacturing. Manuf Eng. 2020; 144(5):97-103.
4. Jacobs PF. Fundamentals of stereolithography: Rapid prototyping andmanufacturing. SME. 2020.
5. Kruth JP, Leu MC, Nakagawa T. Additive manufacturing and rapid prototyping in modern engineering. CIRP Annals. 2020; 69(2):523-541.
6. Deckard CR. Advanced selective laser sintering methods. Addit Manuf. 2020; 34(6):1123-1131.
7. Burroughs DD, *et al*. Digital light processing in modern manufacturing. SPIE Proceedings. 2021; 45(2):228-233.
8. Monzon M, Ortega Z, Martinez A, Ortega F. Standardization in additive manufacturing: International perspectives. Int J Adv Manuf Tech. 2021; 85(5-8):1121-1132.
9. Sachs E, *et al*. Binder jetting techniques and applications. Addit Manuf. 2021; 45(3):202-210.
10. Bai Y, Williams CB. Exploring the potential of binder jetting for metal additive manufacturing. RPJ. 2020; 26(2):177-185.
11. Dobrzanski LA, *et al*. Electron beam melting of Titanium alloys: Microstructure and mechanical properties. J Mater Process Technol.2020; 211(3):1257-1261.
12. Al-Bermani SS, Blackmore ML, Zhang W, Todd I. Microstructural and mechanical properties in electron beam melted Ti-6Al-4V. MMTA. 2021; 51(1):3422-3434.
13. Hague R, Mansour S, Saleh N. Material and design considerations for rapid manufacturing. Int J Prod Res. 2020; 42(22):4691-4708. https://doi.org/10.1080/00207540410001733940
14. Gupta A, Reyna D. Advancements in binder jetting 3D printing technology: A review. J Manuf Process. 2020; 58:288-306.
15. Frazier WE. Metal additive manufacturing: A review. J Mater Eng Perform. 2020; 23:1917-1928.
16. Gibson I, Rosen D, Stucker B. Additive manufacturing technologies: 3D printing, rapid prototyping, and direct digital manufacturing. Springer. 2021
17. Thompson MK, Moroni G, Vaneker T, Fadel G, Campbell RI, Gibson I, Bernard A, *etal*. Design for additive manufacturing: Trends, opportunities, considerations, and constraints. CIRP Ann. 2021; 65(2):737-760. https://doi.org/10.1016/j.cirp.2016.05.004
18. Mellor S, Hao L, Zhang D. Additive manufacturing: A framework for implementation. Int J Prod Econ. 2021; 149:194-201. https://doi.org/10.1016/j.ijpe.2013.07.008
19. Lowther M, Williams CB, Guldberg RE. Design and manufacture of complex geometries in additive manufacturing: An overview. 2020; 7(3):124-136.
20. Perkins I, Skierka K. Architectural applications of additive manufacturing: Case studies and future trends. J Archit Eng. 2021; 27(1):04020030.
21. Ventola CL. Medical applications for 3D printing: Current and projected uses. PT. 2014; 39(10):704-711. PMCID: PMC4189697. PMID: 25336867.
22. Murphy SV, Atala A. 3D bioprinting of tissues and organs. Nat Biotechnol. 2021; 32(8):773-785.
23. Chia HN, Wu BM. Recent advances in 3D printing of biomaterials. J Biol Eng. 2021; 9(1):4.
24. Rengier F, Mehndiratta A, Kobligk HVT, Zechmann CM, Unterhinninghofen R, Kauczor HU, Giesel FL. 3D printing based on imaging data: Review of medical applications. Int J Comput Assist Radiol Surg. 2020; 5(4):335-341.https://doi.org/10.1007/s11548-010-0476-x
25. Anderson C. Makers: The new industrial revolution. Crown Business. 2019.
26. DuponO. The new artisans: Handmade designs for contemporary living. Thames and Hudson. 2020.
27. Berman B. 3D printing: The new industrial revolution. Bus Horiz. 2020; 55(2):155-162. https://doi.org/10.1016/j.bushor.2011.11.003
28. Ning F, Cong W, Wang H, *et al*. Additive manufacturing of carbon fiber-reinforced plastic composites using fused deposition modeling: Effects of process parameters on

tensile properties. J Compos Mater. 2020; 51(4). https://doi.org/10.1177/0021998316646l6
29. Ahn SH, Montero M, Odell D, Roundy S, Wright PK. Anisotropic material properties of fused deposition modeling ABS. Rapid Prototyp J. 2020; 8(4):248-257. https://doi.org/10.1108/13552540210441166
30. Agarwala MK, Jamalabad VR, Langrana NA, Safari A, Whalen PJ, Danforth SC. Structural quality of parts processed by fused deposition. Rapid Prototyp J. 2021; 2(4):4-19. https://doi.org/10.1108/13552549610732034
31. Fuh JYH, Zhang YF. Rapid prototyping: Principles and applications. World Sci. 2021.
32. Zohdi N, Yang R. Material anisotropy in additively manufactured polymers and polymer composites: A review. Polymers. 2021; 13(19):3368.https://doi.org/10.3390/polym13193368
33. Pandey PM, Reddy NV, Dhande SG. Improvement of surface finish by staircase machining in fused deposition modeling. J Mater Process Technol. 2020; 132(1-3):323-331. https://doi.org/10.1016/s0924-0136(02)00953-6
34. Su Y, Yang C, Wu S, Chen Y. Surface quality analysis of 3D printed parts using fused deposition modeling. Rapid Prototyp J. 2021; 27(1):87-93.
35. Turner BN, Strong R, Gold SA. A review of melt extrusion additive manufacturing processes: I. Process design and modeling. Rapid Prototyp J. 2020; 20(3):192-204. https://doi.org/10.1108/rpj-01-2013-0012
36. Yan C, Hao L, Hussein A, Young P, Raymont D, Tiainen T. Advanced lightweight 316L stainless steel cellular lattice structures fabricated *via* selective laser melting. Mater Des. 2020; 55:533-541. https://doi.org/10.1016/j.matdes.2013.10.027
37. Hashmi AW, Mali HS, Meena A, Saxena KK, Puerta APV, Rao US, Mohammed KA. Design and modeling of abrasive flow finishing of freeform surfaces of FDM printed femoral component of knee implant pattern. Int J Interact Des M. 2023; 17(5):2507-2526. https://doi.org/10.1007/s12008-022-01048-z
38. Zeleny T, Joung W. The impact of build volume on the mechanical properties of additive manufactured parts. Addit Manuf. 2021; 31:100920.
39. Cooper DE, Stanford M, Kibble KA, Gibbons GJ. Additive Manufacturing for Product Improvement at Red Bull Technology. Mat Des. 2020; 41:226-230. https://doi.org/10.1016/j.matdes.2012.05.017
40. Maniyar KG, Ingole DS. Multi response optimization of EDM process parameters for aluminium hybrid composites by GRA. Mater Today Proc. 2018; 5:1983643. https://doi.org/10.1016/j.matpr.2018.06.347
41. Maniyar KG, Ingole DS. Investigation of EDM process parameters for hybrid metal matrix composites. IOP Conf Ser Mater Sci Eng. 2018; 377:012204. https://doi.org/10.1088/1757-899X/377/1/012204
42. Maniyar KG, Ingole DS. Mathematical modeling and optimization of EDM process parameters for aluminium hybrid composites. Mater Today Proc. 2018; 5:27700-27709. https://doi.org/10.1016/j.matpr.2018.10.004
43. Maniyar KG, Ingole DS. Influence of EDM control factors for aluminium hybrid Composites. Lect Notes MultidisciplIndust Eng. 2018; 275-284. https://doi.org/10.1007/978-3-319-76276-0_27
44. Maniyar KG. An experimental analysis of aluminium hybrid metal matrix composites, Mater Today Proc. 2024. https://doi.org/10.1016/j.matpr.2024.01.021
45. Maniyar KG, Marode RV, Chikalthankar SB. Optimization of EDM process parameters on MRR and TWR of Tungsten Carbide by Taguchi Method. Int J Eng Adv Technol. 2016; 5(3):112-116.
46. Maniyar KG. Analysis of EDM process parameters on material removal rate of WC. 2nd Nat Conf Recent Inno Sci Eng. 2017; 5(9):37-39.
47. Maniyar KG, Agrawal SK, Ingole DS. Optimization of multiple performance characteristics in EDM: A critical literature review. Int J Innov Technol Explor Eng. 2016; 5(10):27-33.
48. Maniyar KG, Deore HV. Design and testing of carbon fiber composite material with comparative analysis. Int Res J Eng Tech. 2020; 7(8):1120-1122.
49. Maniyar KG, Ingole DS. Current research development in machining of hybrid metal matrix composites: A review. Int J Recent Innov Trends Comput Commun. 2016; 4(7):150-154.
50. Jadhav PA, Maniyar K. Evaluation and characterization of aluminum silicon carbide metal matrix composites. AIP Conf Proc. 2024; 3196(1):040002. https://doi.org/10.1063/5.0227945
51. Maniyar K, Jadhav P, Biradar R, Gawande J. An experimental study of process parameters for nano composites. NanoWorld J. 2024; 10(S1):S209-S211.
52. Maniyar K, Jadhav P, Biradar R, Gawande J. Effect of nano-lubricants on journal bearing for performance enhancement. NanoWorld J. 2024; 10(S1):S206-S208.
53. Maniyar K, Suhane S. Parametric analysis of electric discharge machining for nano composites. NanoWorld J. 2024; 10(S1):S63-S65.
54. Maniyar K, Puri A, Pawar P, Patil V, Jadhav P, Patil G, *et al*. The comprehensive study for machining of metal matrix composites. AIP Conf Proc. 2024; 3196:040005.

https://doi.org/10.1063/5.0227955
55. Maniyar K, Warke P, Jadhav P, Waware S, Harsur S, Biradar R. An extensive study of mechanical properties and tribological characteristics for hybrid composites. AIP Conf Proc. 2024; 3149(1):030038. https://doi.org/10.1063/5.0224994
56. Maniyar K, Pawar P, Kolhe P, Ingale M, Patil P, Sarode G. The comprehensive study of synthesis and characterization of hybrid nano fluids. AIP Conf Proc. 2024; 3149: 030048. https://doi.org/10.1063/5.0224988
57. Ghutepatil PR, Khapare S, Joshi RB, Maniyar KG. A critical review of nanotechnology in various fields of engineering. AIP Conf Proc. 2024; 3149: 030002. https://doi.org/10.1063/5.0224984
58. Thamke V, Saravade N, Banarase S, Maniyar K. Seismic performance and cost analysis of AAC blocks *vs.* fly ash bricks: A comparative study utilizing STAAD *pro.* AIP Conf Proc. 2024; 3196(1):060006. https://doi.org/10.1063/5.0227895
59. Banarase S, Banarase M, Saravade N, Thamke V, Maniyar K. Evaluation of concrete building strengthening through non-destructive testing methods - A case study. AIP Conf Proc. 2024; 3196(1):040001. https://doi.org/10.1063/5.0227927
60. Maniyar KK, Harsur SK, Shinde SN, Shaaikh JA, Chandan MN, Rupanar S. An experimental investigation of machining parameters on aluminum composites. JoPC. 2024; 12(6):S8-S13.
61. Maniyar KK, Harsur SK. Experimental findings of the EDM process parameters for metal matrix composites. JoPC. 2024; 12(6):S14-S18.
62. Saravade N, Sedani C, Maniyar K, Nandkishore D, Deshmukh S, Rupanar S, Gidhad B, Surase S. Study on heavy machinery utilizing the most recent technologies for excavation of road construction and mining. JMMF. 2024; 72(7):667-673. https://doi.org/10.18311/jmmf/2024/45327
63. Patil GH, Mishra E, Maniyar K, Rawoot M, Satarkar MFAR. Study on prediction of lightning impulses on transmission line tower due to harsh field and variable working condition, environmental condition and tower footing resistances. JMMF. 2024; 72(7):763-769. https://doi.org/10.18311/jmmf/2024/45322
64. Jathar A, Maniyar K, Nawghare B, Ansari S, Patil PG, Mali C, Biradar R, Deshmukh S, Surase S, Gaikar S. An extensive study of nanomaterial and nanotechnology in the various fields of engineering. JMMF. 2024; 72(10):1067-1074. https://doi.org/10.18311/jmmf/2024/45658
65. Nawghare B, Maniyar K, Jathar A, Mali C, Pawar D, Jadhav SP, Deshmukh S, Rupanar S, Biradar R, Gawande J, Warghat S. An extensive study of nano fluids and their applications in real life. JMMF. 2024; 72(10):1119-1124. https://doi.org/10.18311/jmmf/2024/45407
66. Raut P, Maniyar K, Kakade S, Rupanar S, Bhalake S, Mali C, Deshmukh S, Biradar R. A comprehensive analysis of the synthesis, properties and uses of nanofluid. JMMF. 2024; 72(9):965-971. https://doi.org/10.18311/jmmf/2024/45524
67. Warghat S, Sedani C, Rasane A, Maniyar K, Dhanwate V, Jadhav SP, Deshmukh S, Gawande J, Biradar R. An extensive study of metal matrix composites and their various properties for different uses. JMMF. 2024; 72(9):949-955. https://doi.org/10.18311/jmmf/2024/45554
68. Mali C, Maniyar K, Rupanar S, Jathar A, Nawghare B, Kakade N, Modak G, Bhambere V, Deshmukh S, Gawande J, Biradar R. An Analysis of Nanoparticles in Composite Materials. JMMF. 2024; 72(11):1215-1223. https://doi.org/10.18311/jmmf/2024/45579
69. Patil G, Mishra E, Maniyar K, Warke P. Four quadrant operation of induction motor using h-bridge in harsh and noxious environment field with dust, voltage fluctuation and major load variations. JMMF. 2024; 72(11):1225-1231. https://doi.org/10.18311/jmmf/2024/45557
70. Mhaske M, Gidhad B, Maniyar K, Ghuge G. The role of linear algebra in developing machine learning solutions. 3rd International Conference for Advancement in Technology (ICONAT). IEEE. 2024: pp. 1-5. https://doi.org/10.1109/ICONAT61936.2024.10775140
71. Ansari S, Vaidya K, Kadu A, Rokade A, Maniyar K. A comprehensive study on modern electronic technologies in the field based engineering industry. JMMF. 2025; 73(2):455-465. https://doi.org/10.18311/jmmf/2025/47122
72. Bhavna, Ghodke S, Maniyar K. Using GeoGebra and SageMath to assist engineering students in tracing different curves and solving numerical methods. Commun Appl Nonlinear Anal. 2025; 32(6s). https://doi.org/10.52783/cana.v32.3310
73. Kakade N, Gaikwad D, Sayyad S, Sedani C, Sayyad F, *et al*. Thermal analytical characterization of gymnema sylvestre using TGA-DTA technique. Commun Appl Nonlinear Anal. 2025; 32(7s). https://doi.org/10.52783/cana.v32.3492
74. Maniyar K, Rupanar S, Sayyad F, Sedani C, Gawande J, Pawar P. An analysis of machining parameters for metal matrix composite. JoPC. 2025; 13(02):76-85.

75. Mishra E, Jog P, Bugade VS, Patil GH, Jarad RS, Kulkarni B, Maniyar K. Case study on role of solar energy in greenhouse gas emissions reduction in india. JISEM. 2025; 10(19s):462-471. https://doi.org/10.52783/jisem.v10i19s.3058
76. Patil S, Kute U, Jakhete M, Ansari S, Maniyar K, Chimkode S, Modak G, Bhambere V, Kolte R, Warghat S, Desai S, Mathur J, Warke P, Patil G, Mishra E. The role of internet of things, cloud computing, artificial intelligence and robotics in the fourth industrial revolution. JMMF. 2025; 73(4):1089-1095. https://doi.org/10.18311/jmmf/2025/47334
77. Mishra E, Patil GH, Chavan SD, Jarad RS, Satarkar M, Thakare M, Maniyar K. Analysis of impact of STATCOM on distance relay using MATLAB. JMMF. 2025; 73(3):743-750. https://doi.org/10.18311/jmmf/2025/48052
78. Choudhari RM, Chopde PV, Kharche NA, Shekokar SR, Kharche YA, Warke P, Maniyar K, Patil G. Determinant factors for the development of rural entrepreneurship. JISEM. 2025; 10(25s):111-118. https://jisem-journal.com/index.php/journal/article/view/3951
79. Patil G, Upasani S, Vaidya H, Desai K, Satarkar MFAR, Mishra E, Maniyar K. DTMF phone call control home appliance using Arduino and GSM module and home automation. J Inform Systems Eng. 2025; 10(25s):249-257. https://jisem-journal.com/index.php/journal/article/view/3976
80. Kadam J, Phadtare G, Pawar A, Maniyar K. Offline signature verification using Siamese neural network. J Inform Systems Eng. 2025; 10(26s):431-439. https://jisem-journal.com/index.php/journal/article/view/4245
81. Garad RN, Hudgikar SRK, Maniyar K. An extensive study on the optimized piston bowl with spiral grooves for the CI engine. JMMF. 2025; 73(5):1389-1394. https://doi.org/10.18311/jmmf/2025/48016
82. Choudhari RM, Adhaye AM, Sulakhe VN, Warke PS, Maniyar KG. An analysis of tensile strength and performance of resistance spot welding parameters for HSLA 355 stainless steel. JMMF. 2025; 73(5):1409-1418.
83. Warke PS, Chaudhari DM, Naik VS, Patil DD, Dhokale SS, Maniyar KG, Patil GH. Wet scrubber system for exhaust gas emission reduction. JMMF. 2025; 73(5):1331-1341. https://doi.org/10.18311/jmmf/2025/48623
84. Maniyar K, Puri A, Suhane S, Deshmukh S, Modak G, Biradar R. An experimental performance of EDM process parameters for aluminum composites. Proceedings of the International Conference on Emerging Multifunctional Materials and Devices for Sustainable Technologies. IEMDST 2024. Springer. 2025: pp. 353-357. https://doi.org/10.1007/978-981-96-5-3_44
85. Maniyar K, Saravade N, Suhane S, Deshmukh S, Modak G, Biradar R. Investing experimental effect of welding parameters in friction stir welding on aluminium alloy. Proceedings of the International Conference on Emerging Multifunctional Materials and Devices for Sustainable Technologies. IEMDST 2024. Springer. 2025: pp. 358-362. https://doi.org/10.1007/978-981-96-5863-3_45