Journal of Mines, Metals and Fuels, *73(9): 2817-2829; 2025. DOI: 10.18311/jmmf/2025/49535*

Print ISSN : 0022-2755

Journal of Mines, Metals and Fuels

Contents available at: *www.informaticsjournals.co.in/index.php/jmmf*

Advances in Ceramic Filler Reinforcement of Polymer Composites for Engineering and Industrial Applications

Bajirao K. Kakad*, Jainesh Sarvaiya and Vishal Sulakhe

Department of Mechanical Engineering, School of Engineering and Technology, Sandip University, Nashik - 422213, Maharashtra, India; bajiraokkakad@gmail.com

Abstract

Ceramic filler-reinforced polymer composites have gained considerable attention for their outstanding mechanical, thermal, and chemical properties, making them highly suitable for various industrial applications. This review provides an in-depth overview of fabrication techniques, such as hand lay-up, compression moulding, resin transfer moulding, and additive manufacturing and analyses how processing parameters influence composite performance. The effects of fibre type, ceramic filler content, matrix choice, fibre orientation, and volume fraction on key mechanical properties like tensile, flexural, impact strength, and hardness are critically evaluated. Additionally, physical attributes, including moisture uptake, thermal stability, and resistance to chemical and UV exposure, are discussed. Emphasis is placed on the role of fibre reinforcement in improving the structural strength of epoxy-based composites. Although these materials offer significant benefits, their broader application is limited by issues like high manufacturing costs, the absence of standardised design protocols, and challenges in performance prediction under complex loading. Overcoming these barriers is essential to fully realise the potential of ceramic-filled polymer composites in advanced industrial applications.

Major Findings: *The study highlights that ceramic filler-reinforced polymer composites exhibit excellent mechanical, thermal, and chemical properties, making them highly suitable for industrial applications. The inclusion of fillers such as SiC, WC, WS_2, and Al_2O_3 significantly enhances strength, stiffness, thermal stability, and moisture resistance. Additionally, optimisation of filler content and manufacturing techniques is crucial for maximising performance while minimising defects such as voids and agglomeration.*

Keywords: *Additive Manufacturing, Chemical, Composite, Manufacturing Techniques, Mechanical, Mechanical Characterisation, Physical, Polymer, Thermal, Ultra Violate*

1.0 Introduction

Polymer composites are the most popular topic among researchers today, due to the excellent properties that make the composites suitable for many engineering applications. It is widely accepted that composites compare favourably in cost, production ease, strength, and durability[1]. Owing to their wide spectrum of properties, scientists turn their attention to the development of fibre (either natural or man-made)- and filler (organic and inorganic)-reinforced polymer composites[2,3]. Especially, it is preferred to use synthetic fibres due to their high strength, durability, heat retention, lightweight performance, economic, and the potential to manufacture any complex shape for construction, automotive, aerospace, and marine applications[4-6]. In

**Author for correspondence*

addition, natural fibre-reinforced polymer composites are also being increasingly developed and used for various types of low to medium-load-bearing structural and non-structural applications. Natural fibre composites are not only lightweight and cheap, but they are also 100% recyclable, renewable, and kind to the environment. They are also low-cost to extract and process. Several parameters such as fibre, fibre orientation, fibre diameter and fibre position influence the properties of natural fibre composites[7,8]. Nevertheless, the properties of the resulting composites were not as predicted in view of some limitations in the natural as well as synthetic fibres. This inspired researchers to find various methods to improve the properties of Fibre Reinforced Polymer (FRP). To power up the mechanical, physical, thermal, tribological, and optical performances of FRPs, two traditional methods have been utilised. One of the first procedures adopted in literature regards the addition of inorganic and organic fillers to toughen the matrix material of the FRPs. The second method is to hybridise FRPs with other fibres or fillers in the same or different planes to enhance several properties of the composites[9-12]. Proper use of fillers significantly enhances the properties of the FRPs to make them applicable in various industrial fields. The mixing with various types of natural or synthetic fibres or fillers with FRPs to produce composite materials combining the merits of both materials and with applications, was termed hybridisation. When the fibres are hybridised, it is opposed to stacking them layer-by-layer when the fibres are different; however, some other manners, such as the carried, inverse position, crossed curvier, or selective fibres in a layer, can be performed to stack the fibres if there are various[13-15]. Hybridisation can be on the nanoscale by the incorporation of nanofillers, generating hybrid nanocomposites. The preparation method, the dispersivity of the nanofiller, the interaction between the fillers, fibrils, and the matrix, the type of nanofiller, and many other factors affect the properties of hybrid nanocomposites[16,17]. Filler addition for FRPs or polymer matrices is frequently studied by many researchers. Fillers, which are commonly used with FRPs to enhance the materials' performance by enhancing the mechanical and physical properties of the composites, are typically assumed as inactive materials[18,19].

With the addition of fillers to the matrix, they form composites having a fine surface finish, delaying the formation of coarse structure, resulting in better mechanical properties, which cannot be achieved with the presence of coarse structure[20]. Filler materials are inorganic or organic. In the case of polymer composites, inorganic fillers are used to enhance the features of the interface, tribological properties, thermal stability, and mechanical properties. The size, geometry, aspect ratio, surface area and degree of dispersion of the fillers within the composite all influence how these fillers influence the properties of the composites. The size, shape, and characteristics of the fillers are crucial parameters for the properties of the composites in applications such as tissue engineering and biomedical implants[21-23]. Many investigations have reported that the addition of fillers in the polymer matrix enhances the performance, processability, and material cost of the latter. In general, filler microparticles or microparticles are combined with the polymer matrix. Nanoparticles or nanofillers offer a much larger surface area than the micro-fillers and exhibit better interaction at the filler-matrix interface. Nanofillers are considered excellent particles to enhance the mechanical, thermal and physical properties of the FRP composites as a result of their high aspect ratio and specific surface area. Nanocomposites are prepared by adding the nanoparticles, nanotubes, or nanoflakes into a polymer matrix on a weight basis[24-27]. Due to the homogeneous dispersion of nanofillers in the matrix caused by mechanical mixing, the incorporation of nanofillers into the polymer matrix increases the mechanical properties and reduces the water uptake of fibre-reinforced nanocomposites. Therefore, the stress is well transferred between the matrix and the nanofillers because of the strong interfacial adhesion during loading.

A specific theory in the literature states that filler enhances the fibre-matrix interaction, which will promote better stress transfer from the fibre to the matrix under load. This, in turn, results in enhancement of the mechanical and thermal properties of the composites[28,29]. Filler addition may also increase the rigidity of the composite by reducing the number of matrix vacancies. Filler content controls the quality of mechanical properties of filled fibre-reinforced composites due to more fillers that facilitate an enhanced particle–particle and fibre–particle–matrix interaction, which may not occur if fillers are inadequately or excessively present in the composites[30,31]. Polymer composites offer attractive strength-to-weight advantages, making them particularly well suited where weight reduction is critical[2-6]. Such

strong and rigid materials as Carbon Fibre Reinforced Polymer (CFRP) have also been widely used in the aerospace industry[32,33]. When plane wings were replaced with aero foils by CFRP composite instead of replacing those with the conventional metallic material, Khan *et al.*[34] presented a 15% weight loss and a 30% fuel saving. Apart from the aerospace industry, the automotive industry also widely employs polymer composites for weight reduction and enhancement. For instance, it has been found that the stiffness and weight of a CFRP composite frame of a bicycle are enhanced by 20% and reduced by 30%, respectively, if they are compared with a common aluminium frame[35]. Kim *et al.* studied the application of Glass Fibre Reinforced Polymer (GFRP) composites to car door inner panels[36]. They were able to show that these composites decreased weight by 36% when compared to traditional steel panels while retaining mechanical properties. Korzhikova-Vlakh and Stepanova[37] reported the reinforcement of Polylactic Acid (PLA) composites using cellulose nanofibers, and the resultant composites exhibited higher modulus and tensile strength. Researchers are working on new methods to enhance the properties of fibre composites. A wide number of manufacturing technologies, such as hand lay-up, filament winding, pultrusion, Resin Transfer Moulding (RTM), Additive Manufacturing (AM), etc., offer the possibilities to produce polymer composites with their advantages and limitations. The properties desired of the composite material dictate the nature of the treatment employed. The generation of polymer composites has received extensive attention to enhance the mechanical characteristics and reduce the manufacturing expenses. Although some studies have investigated the substitution of synthetic fibres by the flax and jute fibres that are inexpensive and environmentally friendly[38,39], others have investigated the development of the bond between the fibres and matrix to provide strength to the composite material[40]. Mechanical characterisation is indispensable for the evaluation of polymer composites' performance, as well as potential industrial applications. Strength, stiffness, toughness, and fatigue resistance are key properties measured and analysed in mechanical characterisation[41,42]. To use polymer composites to their full potential under different load conditions, it is essential to understand this behaviour. The mechanical properties of fibre-based composites are characterised through tensile, compressive, shear and flexural tests. To perform tests with different loading conditions, to determine the mechanical properties of composites in diverse directions. Similarly, non-destructive evaluation techniques have also been developed to inspect composite flaws and their internal configuration, such as thermography, X-ray tomography, and ultrasonic testing. Many researchers have attempted to solve the challenge of improving the performance of polymer composites and their applications. Reviews of Natural Fibre Reinforced Polymer (NFRP) composites, CFRP composites, and GFRP composites are well-established[10-12]. However, no comprehensive review of all types of fibrous composites and their complex manufacturing processes is known to have been presented. Consequently, the present study offers a full picture of the polymer composite processing and mechanical test conditions and how these are changing the mechanical response.

2.0 Fabrication Methods of Polymer Composites

The fabrication method chosen for composite materials largely depends on their size and intended use. Fibre-Reinforced Polymer Composites (FRPCs) are commonly manufactured using techniques such as resin transfer moulding, compression moulding, injection moulding, hand lay-up, and filament winding[43]. This section provides an overview of prevalent methods for creating fibrous composites from natural and synthetic fibres for industrial applications, with hand lay-up being a particularly common approach. In this method, fibre reinforcements are placed in a mould and wetted with a thermosetting resin, typically spread evenly using a brush or roller. Layers are built up to the required thickness. A silicone demolding agent is usually applied to the mould beforehand to facilitate removal after curing[44]. Figure 1 shows the Hand Lay-up (HL) process for composite production.

3.0 Material and Fabrication

3.1 Materials

3.1.1 Epoxy

A widely applied thermosetting polymer, epoxy resin (also called polyepoxide), contains epoxide functional groups and usually exists in polymeric, semi-polymeric, or oligomeric forms. LY556 epoxy resin is employed.




Figure 1. Schematic representation of the HL process used for composite fabrication.

Epoxy is primarily used for bonding diverse materials due to its high mechanical strength, chemical resistance, electrical insulation, and corrosion-inhibiting properties.

3.1.2 Glass Fibre

Consisting of multiple thin glass filaments, glass fibre is a remarkably adaptable material derived from calcite, clay, and sand. Different types of glass fibres are available. For composite reinforcement in this study, C-Glass fibres were chosen because they are lightweight, inexpensive, possess excellent mechanical characteristics, and are easily formed into fibres.

3.1.3 Hardener

Certain types of mixtures contain hardener, which is often an amine that is used with epoxy to promote chemical interactions between the two. This is sometimes referred to as curing agents and involves epoxides and other compounds. HY951 hardener (Araldite hardener), which cures at room temperature, has a lower stickiness and exhibits a notable resistance to chemical and atmospheric deprivation, is employed.

3.1.4 Tungsten Carbide (WC)

Often called "carborundum," Tungsten Carbide (WC) is a very hard, crystal-like material formed from tungsten and carbon. It is widely used in industrial settings as both an abrasive and a steel additive. WC has different varieties, including green and black. The current work incorporates grey WC as a filler, recognising its notable thermal, chemical, and mechanical characteristics[45].

3.2 Fabrication Process

3.2.1 Mould Preparation

The first step in manufacturing involves creating a 300 x 300mm plywood mould. Mansion white wax is used as a release agent, applied uniformly between the plywood and the composite. Following a one-hour air-drying period, this procedure is duplicated to produce a second mould sheet.

3.2.2 Hand Lay-Up Moulding

First, 200 x 200mm woven glass fibre pieces are cut. Then, epoxy and hardener are mixed at a standard 10:1 ratio. This layering process is repeated eight times: epoxy is applied to the plywood, a glass fibre layer is added and rolled, more epoxy is applied to the glass fibre, and another glass fibre layer is placed on the resin and rolled. The goal is to use all the resin mixture by the time the eighth glass fibre layer is in place.

3.2.3 Curing

Following the composite's installation, a second plywood sheet is positioned on top of the final glass fibre ply and given some weight. The produced composite is not disturbed during the first 24 hours of cure.

3.2.4 Demoulding

The weight is removed after the 24-hour curing period, and the wax covering makes it easy to separate the two-ply sheets. The manufactured composite is then allowed to dry for an additional 24-hour period in the presence of air and sunlight.

3.2.5 Laminates

The laminates are commonly used as the finishing layer, which enhances the specific properties of the composite[46].

4.0 Characterisation of Fibrous Polymer Composites

4.1 Mechanical Characterisation

The mechanical characterisation of fibrous polymer composites entails evaluating their response to mechanical loads, offering valuable information regarding their strength, stiffness, and long-term

performance. The composite's overall mechanical behaviour is predominantly influenced by the properties of the reinforcing fibres, the polymer matrix, and the interfacial bonding between them. Data obtained from such evaluations plays a crucial role in the design and optimisation of composites for targeted applications across sectors like aerospace, automotive, and construction[47]. The subsequent section elaborates on the mechanical characterisation of synthetic fibre-reinforced composites.

Researchers investigated the influence of SiC-Glass Fibre (GF) reinforcement on the mechanical performance of composites. The study revealed that hybrid composites with 30% and 40% SiC content exhibited superior hardness and impact resistance. However, the incorporation of SiC led to a reduction in tensile and flexural strength, although the degree of reduction varied with the filler content[48]. They emphasised the importance of optimising SiC filler content under both ambient and elevated temperatures to achieve the desired mechanical properties. The study offers valuable insights into enhancing the tensile strength and thermal stability of composites for diverse engineering applications[49]. Increasing the filler ratio enhances hardness and tensile properties compared to unfilled samples, with 2% filler showing the highest elastic extension and creep rate, while 0.7% exhibited minimal creep. Creep behaviour is governed more by nonlinear viscoelasticity than by filler concentration[50]. Appropriate filler loading improves hardness, tensile, compressive, and bending strengths; however, excessive filler causes agglomeration and defects, reducing performance[51]. Fibres play a crucial role in bearing mechanical loads and significantly enhance overall composite strength, as shown by tensile, compressive, flexural, impact, and hardness testing[52]. The use of tungsten particles (1–9 wt%) as fillers in epoxy composites improves flexural strength by up to 124% at 7 wt%, beyond which agglomeration reduces performance. Shore D hardness also peaks at 7 wt% with an 85% increase[53]. WS_2-filled glass/epoxy composites demonstrate superior mechanical performance over unfilled ones, with 2% filler content proving optimal. Excess filler results in weaker bonding and greater embrittlement. Hardness improves up to 3% WS_2, with maximum ILSS observed at 2%[54]. Increasing glass fibre content enhances tensile, flexural, and impact strengths, while high epoxy and low fibre content negatively impact mechanical performance[55]. Raising WC content from 3% to 9% significantly boosts flexural strength (from 97 MPa to 127.8 MPa) and impact resistance (up to 573.44 J/m), with wear resistance also improving due to uniform WC dispersion confirmed via SEM[56]. A 5 wt% blend of coal fly ash and coal powder (CFACP) enhances tensile, flexural, Vickers hardness, and impact properties, indicating the potential of industrial waste as effective fillers[57]. E-glass fibre epoxy composites with 2% and 4% SiC fillers show increased compressive strength and hardness, but higher SiC loading reduces tensile and fracture strength due to increased brittleness[58]. WC-filled composites exhibit improved mechanical properties and lower wear rates. Among various formulations, the G+R+E configuration performs best, while wear resistance increases with both WC content and abrading distance[59]. Increasing Al_2O_3 weight fraction enhances mechanical performance, although larger particle sizes are detrimental. Process optimisation using the desirability function method yields validated improvements[60]. Incorporating glass fibres into epoxy matrices markedly boosts mechanical strength, supporting their use in lightweight, high-performance structural applications[61].

X-Ray Diffraction (XRD) is employed to identify the crystalline phases present in ceramic-filled composites. It reveals key microstructural features such as phase composition, degree of crystallinity, crystallite size, and lattice strain. XRD patterns help confirm the uniform dispersion of ceramic fillers within the polymer matrix and detect any unwanted secondary phases. These insights are essential for understanding how filler incorporation affects mechanical and thermal performance.

4.2. Thermal Characterisation

The incorporation of SiC fillers into neat epoxy leads to a marked improvement in thermal stability, with the highest enhancement observed in composites containing 40% SiC and glass fibre. Furthermore, the addition of SiC increased the thermal conductivity of both neat and hybrid composites, with experimental values closely matching predictions based on Maxwell's model[62]. An increase in filler content can also reduce thermal conductivity; however, a composite containing 0.7% filler exhibited the most notable improvement in thermal performance among the tested samples[63]. Thermal analysis of epoxy composites reinforced with 1–9 wt% tungsten particles showed enhanced thermal stability, indicated by a shift in decomposition temperature from 405°C (pure epoxy) to 410°C at 9 wt%. Differential scanning calorimetry revealed increases in glass transition, crystallisation, and melting temperatures, confirming

improved thermal characteristics with tungsten addition[64]. The inclusion of WS_2 as a filler also enhanced the thermal behaviour of glass/epoxy composites, with the most significant improvement in thermal stability observed up to 1.5 wt% WS_2 loading[65].

Epoxy composites degrade under fire exposure through a series of thermal events, including depolymerisation, chain scission, and char formation. These reactions release volatile compounds and gases, reducing mechanical strength and structural integrity. The onset temperature of degradation typically ranges from 300°C to 400°C. Mitigation strategies include incorporating flame retardant additives such as Alumina Trihydrate (ATH), phosphorus-based compounds, or ceramic fillers. Additionally, using surface coatings and intumescent layers can delay ignition and reduce heat release rates.

4.3 Physical Characterisation

The relationship between filler concentration and void formation shows that higher filler content generally leads to an increase in void fraction within the composite structure[66]. In contrast, WS_2-filled glass/epoxy composites demonstrate improved physical characteristics compared to unfilled samples. While overall density remained nearly constant, increasing WS_2 content contributed to lower moisture absorption and reduced void content[67].

4.4 Chemical and Ultraviolet Characterisation

It has been highlighted that storage tanks used in open-air biogas reactors must resist both the corrosive impact of Hydrogen Sulfide (H_2S) and degradation from Ultraviolet (UV) exposure. To meet these demands, materials with strong acid and UV resistance are essential for tank construction[68]. Addressing these requirements, reactor designs incorporating 157BQTN-EX composite reinforced with C-glass woven roving and ceramic fibres have been proposed to reduce construction costs, improve portability, and enhance durability under harsh environmental conditions[69].

A summary of the various investigations performed on fibrous polymer composites fabricated using different manufacturing techniques is presented in Table 1.

5.0 Factors Determining the Mechanical Failure

The mechanical properties of composite systems are a key determinant in evaluating their suitability for industrial applications. These materials must be capable of withstanding multi-directional loads. The final mechanical performance of hybrid composites is typically influenced by three primary factors. The first is the choice of constituent materials, specifically the filler and matrix, selected based on the intended application. This encompasses the type, form, and dimensions of the fibres (e.g., length, shape, or powder form). The overall mechanical behaviour is also significantly affected by fibre content and the fibre's aspect ratio. To ensure effective reinforcement, particularly under tensile loads, the fibre length must exceed the critical length required for adequate stress transfer from the matrix to

Table 1. An overview of the research done and the production techniques used to create fibrous polymer composites

Manufacturing Technique	Type of Matrix	Type of Reinforcement	Investigations Performed
HL	Epoxy	GFs and CFs	Mechanical Properties
HL	Epoxy	GFs	Mechanical Properties
HL	Epoxy	GFs	Mechanical Properties
HL	Epoxy	GFs	Mechanical Properties
HL	Epoxy	GFs, Jute Fibre and Sisal	Mechanical Properties
HL	Epoxy	GFs	Mechanical Properties
HL	Epoxy	Basalt fiber	Mechanical Properties
HL	Epoxy	GFs	Mechanical Properties
HL	Epoxy	GFs	Mechanical & Thermal Properties
HL	Epoxy	GFs	Mechanical & Thermal Properties

the fibre[70,71]. Furthermore, the selection of the polymer matrix plays a critical role, as its crystallinity directly impacts the composite's strength and stiffness[72]. The degree of crystallinity in polymers plays a significant role in controlling moisture diffusion into composite structures. Highly crystalline regions are tightly packed and less permeable, creating barriers that slow down water penetration. In contrast, amorphous regions have more free volume, allowing easier diffusion of moisture. Therefore, composites with higher crystallinity exhibit improved resistance to moisture ingress, leading to better dimensional stability and mechanical integrity in humid environments. The second major factor is the composite manufacturing process, including design parameters and processing conditions. The application, whether for indoor protective use or outdoor structural purposes, guides decisions regarding composite weight, mechanical strength, density, moisture absorption, recyclability, disposal, raw material availability, production cost, and compatibility with existing recycling systems[73]. An essential aspect influencing mechanical performance is the stacking sequence, which offers design flexibility through choices such as fibre orientation, preform type, and layer arrangement. For instance, unidirectional composites exhibit superior stiffness in the fibre direction compared to multi-directional laminates. Additionally, placing 0° plies on the outer surfaces of 0°/90° laminates enhances longitudinal flexural stiffness without compromising tensile properties[74-76]. The third and perhaps most critical factor is the interfacial bonding between the matrix and the fibre. Effective reinforcement is achieved through treatments that enhance interfacial adhesion, such as the application of coupling agents or chemical modifications, thereby improving tensile and flexural strength[77]. The surface treatments improve fibre dispersion, promote uniform stress distribution, and reduce void formation. Pre-treatment also enhances fibre mechanical properties and reduces moisture absorption. These treatments can be physical (e.g., mechanical agitation or heating) or chemical (e.g., alkalisation, silane, acylation, or benzoylation), all of which contribute to improved compressive strength and reduced fracture susceptibility[78]. Silane coupling agents play a crucial role in enhancing fibre–matrix interfacial bonding. They chemically graft onto the hydroxyl groups present on fibre surfaces, forming siloxane linkages. The organofunctional end of the silane reacts with the epoxy resin, creating covalent bonds that improve wettability and chemical compatibility. This dual reactivity strengthens fibre–matrix adhesion, reduces moisture sensitivity, and enhances load transfer efficiency, thereby improving overall composite performance. The interfacial bonding mechanism in thermoplastic and thermosetting matrices is fundamentally different. Thermoplastics rely on physical entanglement and van der Waals forces, allowing reversible bonding upon heating, while thermosetting matrices form permanent covalent bonds during curing, resulting in stronger interfacial adhesion and more effective load transfer. The fibre–matrix interaction plays a key role in determining the failure mechanisms of composites. Defects such as microcracks, delaminations, and fibre breakages typically arising during fabrication can serve as initiation points for failure[79]. In addition, moisture uptake poses a significant threat to the longevity of natural fibre composites, particularly in outdoor environments[80]. Environmental factors like humidity, temperature, and UV exposure accelerate material degradation, making it essential to assess long-term durability. Both hygrothermal and hydrothermal conditions, associated with ambient moisture and water immersion, critically influence mechanical strength and dimensional stability[81]. The aspect ratio of nanofillers significantly affects the percolation threshold in polymer composites. A higher aspect ratio leads to a lower percolation threshold because the elongated fillers form conductive or reinforcing networks at lower filler loadings. This network formation enhances stress transfer and mechanical reinforcement while maintaining processability and reducing weight. Conversely, fillers with low aspect ratios require higher concentrations to achieve similar connectivity, which may negatively impact composite uniformity and viscosity.

Tigga *et al.*[82], to address solid propellant time performance and calibration since the thermo-kinetic response is similar to novel load-bearing high temperature polymer-ceramic matrix composites used in stabilised green and cured states in aerospace quality composites. Patil *et al.*[83] emphasised the contribution of Artificial Intelligence in sustainable mining, which stands as an example where AI could be employed to optimise the selection, distribution and life cycle analysis of ceramic filler materials within composite mining tools and structural supports. In the area of mechanical enhancement, Chougule, Murali, and Kurhade[84,85] conducted Finite Element Analysis (FEA) and failure analysis on the paddle mixer shaft, with a specific

applicability to composite shaft development. Such simulation methods are important to predict and optimise stress distribution and fatigue resistance upon the addition of ceramic fillers to polymer matrices. Ramani *et al.*[86,] in the context of structural damage detection, can be further developed to detect the filler degradation or the interfacial damage (the two are key issues in ceramic-filled polymers for civil and geotechnical purposes). Yadav *et al.*[87], where a metallic material is analysed, the mechanisms and behaviour under traction offer comparison to the effect of ceramic particles for reinforcing the polymer structures, particularly on the impact, which is observed for steel. More extensive experimental work by Yadav *et al.*[88] describing deformation and resiliency, parameters greatly affected by the ceramic filler content/size as well as distribution, in composites and in particular in curvy/contoured structural applications. Deshpande *et al.*[89] also invented a surface finish measurement apparatus for inspection of ceramic-polymer composites during production, quality control, because surface roughness influences wear and tribological performance. In a corresponding physical analogy, Yadav *et al.*[90] compared composite and metal leaf springs; this similarly corresponds to the performance validation of ceramic-filled polymer-based parts in suspension/load-bearing applications. Their research contributes to the growing trend in the replacement of conventional materials with high-strength lightweight alternatives.

The hydrophilic nature of natural fibres arises from their chemical composition. Cellulose and hemicellulose, rich in hydroxyl (-OH) groups, are responsible for moisture absorption. While lignin exhibits more hydrophobic characteristics due to a lower -OH to carbon ratio, hemicellulose's high -OH content makes it more susceptible to water absorption. Although cellulose contains both crystalline and amorphous regions, only the amorphous portions are readily accessible to water molecules, restricting overall moisture ingress compared to hemicellulose. Surface roughness enhances mechanical interlocking at the fibre–matrix interface by increasing the surface area for contact and promoting frictional resistance during load transfer. This physical interlocking mechanism improves the load-bearing capacity of the interface, delays crack propagation, and enhances the overall tensile and flexural strength of the composite. Proper surface roughness also facilitates better wetting and adhesion of the matrix resin to the fibre surface. Fibre waviness introduces local misalignments that disrupt uniform stress transfer in laminated composites. These undulations lead to stress concentrations, which can initiate premature matrix cracking, interfacial debonding, or fibre kinking under load. As a result, composites with higher fibre waviness typically exhibit reduced stiffness, lower tensile strength, and increased susceptibility to buckling and delamination. Minimising fibre waviness during fabrication is crucial for maintaining mechanical integrity.

This comprehensive understanding is critical in designing polymer composites reinforced with ceramic fillers for robust industrial applications.

6.0 Industrial Applications of Reinforced Polymer Composites

Polymer composites play a vital role across various industries such as aerospace, automotive, marine, defence, electronics, construction, and biomedical sectors. Their key advantages over traditional metals include excellent vibration dampening, superior dielectric properties, lightweight construction, and exceptional corrosion resistance.

Aerospace: Carbon fibre-reinforced plastics are commonly used in aircraft structures to reduce overall weight and enhance fuel efficiency. Additionally, ceramic matrix composites are employed in thermal protection systems like heat shields.

Electronics: Ceramic-filled polymer composites are widely utilised in devices such as actuators, transducers, and capacitors. Their outstanding electrical insulation and thermal conductivity make them ideal for electronic packaging applications.

Automotive: Carbon-reinforced composites are extensively used in high-performance applications, including competitive cycling and racing watercraft, due to their strength and reduced weight.

Construction: The mechanical robustness and structural integrity of ceramic composites make them suitable for use in various building and infrastructure projects.

Biomedical: Biodegradable polymer composites with high mechanical strength, corrosion resistance, and biocompatibility are employed in medical applications such as implants and devices.

Biodegradable polymers, such as Polylactic Acid (PLA) and Polycaprolactone (PCL), are commonly used

in biomedical composites due to their biocompatibility and controlled degradation. While they eliminate the need for surgical removal, their long-term performance is influenced by the rate of degradation, mechanical integrity during resorption, and interaction with body fluids. Careful design is needed to balance structural support with biodegradability, ensuring that the material maintains functionality throughout the healing process.

Marine Industry: Composites are utilised in the fabrication of warship components, onboard equipment, and offshore structures. They are also essential in renewable marine energy systems and the construction of boats and ships.

Defence: Due to their lightweight nature, extended operational range, and low electromagnetic and acoustic signatures, composites are favoured in military applications for enhancing performance and stealth capabilities.

Emerging technologies for real-time monitoring of mechanical failure in composite structures include fibre optic sensors, piezoelectric sensors, and embedded strain gauges. These systems detect strain, crack initiation, delamination, or impact damage through changes in signal response. Advanced methods such as acoustic emission monitoring and Digital Image Correlation (DIC) offer non-invasive, high-resolution diagnostics. Integration with wireless networks and AI-based analytics further enhances predictive maintenance and structural health monitoring in critical applications.

7.0 Conclusions

This review presented a detailed examination of fabrication methods and mechanical evaluation strategies for ceramic filler-reinforced polymer composites aimed at industrial applications. With advantages such as high strength-to-weight ratio, stiffness, and corrosion resistance, fibrous polymer composites stand out as viable alternatives to conventional materials. The findings underscore the pivotal role of constituent materials, filler attributes, and processing techniques in determining composite performance. Among the characterisation tools, Dynamic Mechanical Analysis (DMA) proves particularly effective in assessing viscoelastic behaviour by providing key insights into storage modulus, loss modulus, damping characteristics, and thermal transitions like the glass transition temperature, essential for evaluating performance under dynamic conditions. Additionally, the integration of Artificial Intelligence (AI) in manufacturing processes, especially in Resin Transfer Moulding (RTM), enables process optimisation through predictive modelling of resin flow, curing behaviour, and fibre impregnation. AI-driven quality control minimises errors and enhances repeatability, leading to greater production efficiency and reduced material waste. Ceramic filler-reinforced polymer composites offer a balanced combination of mechanical strength, chemical durability, and thermal stability, which makes them suitable for a broad spectrum of applications, including aerospace, automotive, and structural components. The incorporation of nano and micro fillers further improves thermal and moisture resistance, though optimisation is critical to mitigate agglomeration effects. Their adaptability to diverse matrix and reinforcement configurations supports the development of application-specific materials, while extensive property testing ensures their reliability. Nevertheless, challenges such as high production costs, lack of standardisation, and performance prediction complexity persist. Moving forward, emphasis should be placed on sustainable production methods, standardised design protocols, and multifunctional composite development to expand their industrial applicability and environmental compatibility.

8.0 Author Contributions

Bajirao K. Kakad: Conceptualisation, methodology development, manuscript supervision, and final review and editing. **Jainesh Sarvaiya**: Data curation, literature survey, writing—original draft preparation, and analysis of fabrication and characterisation techniques. **Vishal Sulakhe**: Visualisation, tabular content preparation, writing—mechanical, thermal, and physical property sections, and reference formatting.

9.0 References

1. Sathishkumar TP, Rajeshkumar L, Rajeshkumar G, Sanjay MR, Siengchin S, Thakrishnan N. Improving the mechanical properties of jute fibre woven mat reinforced epoxy composites with addition of zinc oxide filler. E3S Web of Confe. 2022; 355:02006. https://doi.org/10.1051/e3sconf/202235502006
2. Madhu P, Sanjay MR, Senthamaraikannan P, Pradeep S, Saravanakumar SS, Yogesha. B. A review on synthesis

and characterisation of commercially available natural fibres: Part I. J Nat Fibres. 2018; 16:1132-1144. https://doi.org/10.1080/15440478.2018.1453433
3. Rohan T, Tushar B, Mahesha GT. Review of natural fibre composites. IOP Conf Series Mater Sci Eng. 2018; 314(1):012020. https://doi.org/10.1088/1757-899X/314/1/012020
4. Gowda TY, Sanjay MR, Bhat KS, Madhu P, Senthamaraikannan P, Yogesha B. Polymer matrix-natural fibre composites: An overview. Cogent Eng. 2018; 5(1):1446667. https://doi.org/10.1080/23311916.2018.1446667
5. Narendiranath Babu T, Aravind SS, Kumar KSN, Rao MSS. Study on mechanical and tribological behaviour of Angora, Kenaf and Ramie hybrid reinforced epoxy composites. Int J Mech Eng Technol. 2018; 9(4):11-20.
6. Sanjay MR, Arpitha GR, Naik LL, Gopalakrishna K, Yogesha. Applications of natural fibres and its composites: An overview. Nat Resour. 2016; 7(3):108-114. https://doi.org/10.4236/nr.2016.73011
7. Rana RS, Purohit R. A review on mechanical property of sisal glass fibre reinforced polymer composites. Mater Today Proc. 2017; 4(2):3466-3476. https://doi.org/10.1016/j.matpr.2017.02.236
8. Swolfs Y, Gorbatikh L, Verpoest I. Fibre hybridisation in polymer composites: A review. Compos Part A: Appl Sci Manuf. 2014; 67:181-200. https://doi.org/10.1016/j.compositesa.2014.08.027
9. Hayajneh MT, Al-Shrida MM, Al-Oqla FM. Mechanical, thermal, and tribological characterization of bio-polymeric composites: A comprehensive review. e-Polymers. 2022; 22:641-663. https://doi.org/10.1515/epoly-2022-0062
10. Dhawan V, Singh S, Singh I. Effect of natural fillers on mechanical properties of GFRP composites. J Compos. 2013; 2013:792620-792628. https://doi.org/10.1155/2013/792620
11. Habib E, Wang R, Wang Y, Zhu M, Zhu XX. Inorganic fillers for dental resin composites: Present and future. ACS Biomater Sci Eng. 2016; 2(1):1-11. https://doi.org/10.1021/acsbiomaterials.5b00401 PMid:33418639.
12. Hayajneh MT FM, AL-Oqla, Al-Shrida MM. Hybrid green organic/inorganic filler polypropylene composites: Morphological study and mechanical performance investigations. e-Polymers. 2021; 21:710-721. https://doi.org/10.1515/epoly-2021-0074
13. Ramesh M, Rajeshkumar L, Bhuvaneswari V. Leaf fibres as reinforcements in green composites: A review on processing, properties and applications. Emergent Mater. 2021; 5(3):833-857. https://doi.org/10.1007/s42247-021-00310-6
14. Balaji D, Ramesh M, Kannan T, Deepan S, Bhuvaneswari V, Rajeshkumar L. Experimental investigation on mechanical properties of banana/snake grass fibre reinforced hybrid composites. Mater Today Proc. 2021; 42:350-355. https://doi.org/10.1016/j.matpr.2020.09.548
15. Deepa C, Rajeshkumar L, Ramesh M. Thermal properties of Kenaf fibre-based hybrid composites. In: Senthilkumar K, Senthil Muthu Kumar T, Chandrasekar M, Rajini N, Suchart, Siengchin, editors. Natural fibre-reinforced composites: Thermal properties and applications. USA: John Wiley and Sons; 2021. p. 167-181. https://doi.org/10.1002/9783527831562.ch10
16. de Araujo Alves Lima R, Kawasaki Cavalcanti D, de Souza e Silva Neto J, Meneses da Costa H, Banea MD. Effect of surface treatments on interfacial properties of natural intralaminar hybrid composites. Polym Compos. 2020; 41(1):314-325. https://doi.org/10.1002/pc.25371
17. Devireddy SBR, Biswas S. Physical and mechanical behaviourr of unidirectional banana/jute fibre reinforced epoxy-based hybrid composites. Polym Compos. 2017; 38(7):1396-1403. https://doi.org/10.1002/pc.23706
18. Arteaga-Ballesteros BE, Guevara-Morales A, San MartínMartínez E, Figueroa-López U, Vieyra H. Composite of polylactic acid and microcellulose from Kombucha membranes. e-Polymers. 2021; 21:15-26. https://doi.org/10.1515/epoly-2021-0001
19. Sahayaraj AF, Muthukrishnan M, Ramesh M, Rajeshkumar L. Effect of hybridisation on properties of tamarind (*Tamarindus indica* L.) seed nano-powder incorporated jute-hemp fibres reinforced epoxy composites. Polym Compos. 2021; 42(12):6611-6620. https://doi.org/10.1002/pc.26326
20. Jagadeesh P, Thyavihalli Girijappa YG, Puttegowda M, Rangappa SM, Siengchin S. Effect of natural filler materials on fibre reinforced hybrid polymer composites: an overview. J Nat Fibres. 2020; 19:1-6. https://doi.org/10.1080/15440478.2020.1854145
21. Tang S, Wang W. Preparation and characterization of a novel composite membrane of natural silk fiber/nano-hydroxyapatite/chitosan for guided bone tissue regeneration. e-Polymers. 2021; 21:671-680. https://doi.org/10.1515/epoly-2021-0068
22. Praveenkumara J, Madhu P, Yashas Gowda TG, Sanjay MR, Siengchin S. A comprehensive review on the effect of synthetic filler materials on fibre-reinforced hybrid polymer composites. J Text Inst. 2022; 113(7):1231-1239. https://doi.org/10.1080/00405000.2021.1920151
23. Ramesh M, Balaji D, Rajeshkumar L, Bhuvaneswari V, Saravanakumar R, Khan A, *et al*. Tribological behavor of glass/sisal fiber reinforced polyester composites. In:

Jawaid M, Khan A, editors. Vegetable fiber composites and their technological applications. Singapore: Springer; 2021; p. 445-59. https://doi.org/10.1007/978-981-16-1854-3_20

24. Raza MA, Westwood AVK, Stirling C, Ahmad R. Effect of boron nitride addition on properties of vapour-grown carbon nanofiber/rubbery epoxy composites for thermal interface applications. Compos Sci Technol. 2015; 120:9-16. https://doi.org/10.1016/j.compscitech.2015.10.013
25. Ramesh M, Rajeshkumar L. Case studies on green corrosion inhibitors. In: Inamuddin, Mohammad Luqman, Mohd Imran Ahamed, Tariq Altalhi, editors. Sustainable corrosion inhibitors, materials research foundations. 2021; 107:204-221. https://doi.org/10.21741/9781644901496-9
26. Ramesh M, Rajeshkumar L, Bhoopathi R. Carbon substrates: A review on fabrication, properties and applications. Carbon Lett. 2021; 31:557-580. https://doi.org/10.1007/s42823-021-00264-z
27. Saba N, Md Tahir P, Jawaid M. A review on potentiality of nano-filler/natural fiber filled polymer hybrid composites. Polymers. 2014; 6(8):2247-2273. https://doi.org/10.3390/polym6082247
28. Amjad A, Anjang Ab Rahman A, Awais H, Zainol Abidin MS, Khan J. A review investigating the influence of nanofiller addition on the mechanical, thermal and water absorption properties of cellulosic fibre reinforced polymer composite. J Ind Text. 2022; 51:65S-100S. https://doi.org/10.1177/15280837211057580
29. Arya A, Tomlal JE, Gejo G, Kuruvilla J. Commingled composites of polypropylene/coir-sisal yarn: Effect of chemical treatments on thermal and tensile properties. e-Polymers. 2015; 15(3):169-177. https://doi.org/10.1515/epoly-2014-0186
30. Ramesh M, Rajeshkumar L, Balaji D, Priyadharshini M. Properties and characterization techniques for waterborne polyurethanes. In: Inamuddin, Boddula R, Khan A, editors. Sustainable production and applications of waterborne polyurethanes. Adv Sci Technol Innov. (IEREK interdisciplinary series for sustainable development). Cham: Springer; 2021; p. 109-123. https://doi.org/10.1007/978-3-030-72869-4_6
31. Jagadeesh P, Puttegowda M, Mavinkere Rangappa S, Siengchin S. Influence of nano-fillers on biodegradable composites: A comprehensive review. Polym Compos. 2021; 42(11):5691-5711. https://doi.org/10.1002/pc.26291
32. Xu J, Yin Y, Davim JP, Li L, Ji M, Geier N, Chen M. A critical review addressing drilling-induced damage of CFRP composites. Compos Struct. 2022; 294:115594-115597. https://doi.org/10.1016/j.compstruct.2022.115594
33. Xu J, Li C, Dang J, El Mansori M, Ren F. A study on drilling high-strength CFRP laminates: Frictional heat and cutting temperature. Materials 2018; 11:2366. https://doi.org/10.3390/ma11122366 PMid:30477257 PMCid:PMC6316996.
34. Khan HA, Nigar M, Chaudhry I.A. Tensile behavior of unidirectional carbon reinforced composites for aerospace structures under varying strain rates. Appl Mech Mater. 2015; 798:357-361. https://doi.org/10.4028/www.scientific.net/AMM.798.357
35. Amiri A, Krosbakken T, Schoen W, Theisen D, Ulven CA. Design and manufacturing of a hybrid flax/carbon fiber composite bicycle frame. Proc Inst Mech Eng. Part P J. Sport Eng Technol. 2018; 232:28-38. https://doi.org/10.1177/1754337117716237
36. Kim DH, Kim HG, Kim HS. Design optimization and manufacture of hybrid glass/carbon fiber reinforced composite bumper beam for automobile vehicle. Compos Struct. 2015; 131:742-752. https://doi.org/10.1016/j.compstruct.2015.06.028
37. Stepanova M, Korzhikova-Vlakh E. Modification of cellulose micro-and nanomaterials to improve properties of aliphatic polyesters/cellulose composites: A review. Polymers 2022; 14:1477. https://doi.org/10.3390/polym14071477 PMid:35406349 PMCid:PMC9003142.
38. Thakur VK, Thakur MK. Processing and characterization of natural cellulose fibers/thermoset polymer composites. Carbohydr Polym. 2014; 109:102-117. https://doi.org/10.1016/j.carbpol.2014.03.039 PMid:24815407.
39. Nguong C, Lee S, Sujan D. A review on natural fibre reinforced polymer composites. Int. J Mater Metall Eng. 2013; 7:52-59.
40. Vishkaei MS, Salleh MAM, Yunus R, Biak DRA, Danafar F, Mirjalili F. Effect of short carbon fiber surface treatment on composite properties. J Compos Mater. 2011; 45:1885-1891. https://doi.org/10.1177/0021998310389090
41. Botelho E, Rezende M, Lauke B. Mechanical behavior of carbon fiber reinforced polyamide composites. Compos Sci Technol. 2003; 63:1843-1855. https://doi.org/10.1016/S0266-3538(03)00119-2
42. Yan L, Chouw N, Jayaraman K. Effect of UV and water spraying on the mechanical properties of flax fabric reinforced polymer composites used for civil engineering applications. Mater Des. 2015; 71:17-25. https://doi.org/10.1016/j.matdes.2015.01.003 https://doi.org/10.1016/j.matdes.2015.01.003
43. Lunetto V, Galati M, Settineri L, Iuliano L. Sustainability in the manufacturing of composite materials: A literature review and directions for future research. J Manuf

Process. 2023; 85:858-874. https://doi.org/10.1016/j.jmapro.2022.12.020
44. Yahaya R, Sapuan S, Jawaid M, Leman Z, Zainudin E. Investigating ballistic impact properties of woven Kenaf-Aramid hybrid composites. Fibers Polym. 2016; 17:275. https://doi.org/10.1007/s12221-016-5678-6
45. Manickam Ramesh, Rajeshkumar LN, Srinivasan N, Kumar DV, Balaji D. Influence of filler material on properties of fiber-reinforced polymer composites: A review. e-Polymers. 2022; 22:898-916. https://doi.org/10.1515/epoly-2022-0080
46. Mayana P, Kavyasree G, Narasimhulu P, Hussain SG, Reddy E, Syman N. Fabrication and mechanical characterization of glass fiber reinforced epoxy with CFA and SiC. IOP Conf Ser Mater Sci Eng. 2022; 1248:01208. https://doi.org/10.1088/1757-899X/1248/1/012081
47. Ashrith HS, Jeevan TP, Xu J. A review on the fabrication and mechanical characterization of fibrous composites for engineering applications. J Compos Sci. 2023; 7252. https://doi.org/10.3390/jcs7060252
48. Rout LN, Mishra D, Swain PTR. Physical, thermal and mechanical characterization of ceramic (SiC) filled woven glass fiber reinforced hybrid polymer composites. 2023. https://doi.org/10.21203/rs.3.rs-3305802/v1
49. Sandeep B, Divakar HN, Keerthiprasad KS, Chandana R, Rao CG. Preparation and characterization of fiber reinforced with ceramic-based filler polymer matrix composites for high-temperature applications. Int J Mater Sci. 2023; 4(1):48-55.
50. Hassan AD, Naeem UJ, Bachic IO. Processing and evaluation of ceramic filler reinforced polymer matrix composites. J Phys Conf Ser. 2022; 2361:012009. https://doi.org/10.1088/1742-6596/2361/1/012009
51. Hanna WA, Gharib FE, Marhoon II. Characterization of ceramic-filled polymer matrix composite used for biomedical applications. J Miner Mater Charact Eng. 2011; 10(12):1167-1178. https://doi.org/10.4236/jmmce.2011.1012089
52. Takim SA, Okeo TF. Characterization of glass fiber reinforced epoxy composites. Guu-J Interdiscip Res Innov. 2022; 1(1).
53. Joseph JE, Kiran AK, Panneerselvam K. Mechanical and thermal characterization of tungsten particulate reinforced epoxy polymer composites. J Eng Res. 2020. https://doi.org/10.36909/jer.ICMMM.12389
54. Belhekar TA, Sorte M, Devtale SS. Determination of physical, mechanical, and thermal properties of glass fiber reinforced epoxy composite with a filler of tungsten disulfide. IJESR. 2016; 6(1):6-12
55. Prasad T, Reddy ACK, Reddy SM, Arun N. Experimental investigation of the mechanical behavior of glass-epoxy composites. RAMPT'13.
56. Thirupathy M, Vadivel M, Subbiah T, Pathinettampadian G. Impact of WC reinforcement on mechanical properties of sisal-fiber-reinforced composites. Eng Proc. 2024; 61:40.
57. Mohammed R, Badruddin IA, Shaik AS, Kamangar S, Khan AA. Mechanical characterization of epoxy-e-glass fiber-particulate reinforced hybrid composites. ACS Omega. 2024; 9:24761−24773. https://doi.org/10.1021/acsomega.4c01365 PMid:38882091 PMCid:PMC11170690.
58. Sharma D, Yadav S, Chand S, Kumar U, Kandpal BC, Kumar A, Gupta DK. Fabrication and characterization of glass fiber/SiC reinforced polymer composite. Int J Appl Eng Res. 2018; 13(6):175-178.
59. Athith D, Sanjay MR, Gowda TGY, Madhu P, Arpitha GR, Yogesha B, Omri MA. Effect of WC on properties of jute/sisal/E-glass reinforced rubber/epoxy composites. J Ind Text. 2018; 48(4):713-737. https://doi.org/10.1177/1528083717740765 https://doi.org/10.1177/1528083717740765
60. Singh PK, Modanwal RP, Kumar D. Mechanical characterization of glass fiber/Al_2O_3 hybrid-epoxy composite. Sādhanā. 2021; 46:32. https://doi.org/10.1007/s12046-020-01539-3
61. Kumar S, Varma V, Kumar S, Kumar A. Fabrication and mechanical characterization of glass fiber reinforced epoxy composite. Int J Prog Res Eng Manag Sci. 2024; 4(6):2049-2053.
62. Chandra DS, Reddy KVK, et al. Mechanical characterization of glass and carbon fibre reinforced composites for marine applications. Int J Eng Technol. 2018; 7(4.5):228-232. https://doi.org/10.14419/ijet.v7i4.5.20052
63. Mayana P, Kavyasree G, Narasimhulu P, *et al.* Fabrication and mechanical characterization of glass fiber reinforced epoxy with CFA and SiC. IOP Conf Ser Mater Sci Eng. 2022; 1248:012081. https://doi.org/10.1088/1757-899X/1248/1/012081
64. Patil MU. Mechanical characterization of e-glass/epoxy composite with ceramic powder filler. Int J Adv Res Ideas Innov Technol. 2021.
65. Kumar N, Mahesh VM, Mallesh G. Mechanical characterization of fiber reinforced glass epoxy hybrid composite. Int J Eng Res Mech Civ Eng. 2018; 3(2).
66. Athith D, Kittali P, Yogesha B. Mechanical characterization of silicon carbide filled hybrid composites. Mater Today Proc. 2020. https://doi.org/10.1016/j.matpr.2021.05.399
67. Gao G, Li Y. Mechanical properties of woven glass fibre-reinforced polymer composites. Emerg Mater Res. 2016. https://doi.org/10.1680/jemmr.16.00018

68. Ullegaddi K, Shivarudraiah, Mahesha CR. Tungsten carbide filler reinforcement and tensile strength of basalt fiber epoxy composites. Int J Recent Technol Eng. 2019; 8(3). https://doi.org/10.35940/ijrte.C6617.098319
69. Sembiring T, Sentana S, Sintawardani N, Nilawati D, Triastuti TJ, *et al*. Strength analysis of 157 BQTN-EX materials for biogas reactor tanks. Int Conf Sustain Energy Eng Appl. 2015.
70. Hapuhinna K, Gunaratne RD, Pitawala J. Thermal mechanical property enhancement with SiC ceramic filled composites. ceramics. 2022; 5:721-730. https://doi.org/10.3390/ceramics5040052
71. Agarwal G, Patnaik A, Sharma RK. Thermo-mechanical properties of SiC-filled chopped glass fiber-reinforced epoxy composites. Int J Adv Struct Eng. 2013; 5:21. https://doi.org/10.1186/2008-6695-5-21
72. Trzepieciński T, Batu T, Kibrete F, Lemu HG. Application of composite materials for energy devices. J Compos Sci. 2023; 7(2):55. https://doi.org/10.3390/jcs7020055
73. Bujjibabu G, Das VC, Ramakrishna M, Nagarjuna K. Water absorption behavior of natural fibers reinforced PP hybrid composites. Mater Today Proc. 2018; 5:12249-12256. https://doi.org/10.1016/j.matpr.2018.02.202
74. Mochane MJ, Mokhena TC, Mokhothu TH, Mtibe A, Sadiku ER, *et al*. Natural fiber hybrid composites for advanced applications: A review. Express Polym Lett. 2019; 13:159-198. https://doi.org/10.3144/expresspolymlett.2019.15
75. Shireesha Y, Nandipati G, Chandaka K. Properties of hybrid composites and applications: A brief review. Int J Sci Technol Res. 2019; 8:335-341.
76. Shah DU, Schubel PJ, Licence P, Clifford MJ. Minimum and critical fiber content for twisted yarn plant fiber composites. Compos Sci Technol. 2012; 72. https://doi.org/10.1016/j.compscitech.2012.08.005
77. Ghalia MA, Abdelrasoul A. Compressive and fracture toughness of natural and synthetic fibre-reinforced polymer. Elsevier. 2018. https://doi.org/10.1016/B978-0-08-102292-4.00007-2
78. Faruk O, Bledzki AK, Fink HP, Sain M. Progress on natural fiber reinforced composites. Macromol Mater Eng. 2014; 299:9-26. https://doi.org/10.1002/mame.201300008
79. Swolfs Y, Verpoest I, Gorbatikh L. Recent advances in fibre-hybrid composites: Materials selection and applications. Int Mater Rev. 2019; 64:181-215. https://doi.org/10.1080/09506608.2018.1467365
80. Schneider K, Lauke B. Compressive properties of fibre-reinforced polymers: ISO 14126. Appl Compos Mater. 2007; 14. https://doi.org/10.1007/s10443-007-9039-x
81. Garat W, Le Moigne N, Corn S, Beaugrand J, Bergeret A. Hygro- and hydrothermal swelling of natural fibres. Compos Part A Appl Sci Manuf. 2020; 131:105803. https://doi.org/10.1016/j.compositesa.2020.105803
82. Tigga AS, Murali G, PSN MV. Investigation on solid propellant test and time calibration for complete combustion. InE3S Web of Conferences 2023; 391:01097. EDP Sciences. https://doi.org/10.1051/e3sconf/202339101097
83. Patil Y, Tatiya M, Dharmadhikari DD, Shahakar M, Patil SK, Mahajan RG, Kurhade AS. The role of AI in reducing environmental impact in the mining sector. J Mines Met Fuels. 2025; 73(5):1365-1378.
84. Chougule SM, Murali G, Kurhade AS. Finite element analysis and design optimization of a paddle mixer shaft. J Mines Met Fuels. 2025; 73(5):1343-1354. https://doi.org/10.18311/jmmf/2025/48664
85. Chougule SM, Murali G, Kurhade AS. Failure investigation of the driving shaft in an industrial paddle mixer. J Mines Met Fuels. 2025; 73(5):1247-1256. https://doi.org/10.18311/jmmf/2025/48627
86. Ramani P, Reji V, Sathish Kumar V, Murali G, Kurhade AS. Deep learning-based detection and classification of moss and crack damage in rock structures for geo-mechanical preservation. J Mines Met Fuels. 2025; 73(3). https://doi.org/10.18311/jmmf/2025/47760
87. Yadav R, Nimbalkar A, Kirpekar S, Patil PJ, Dalvi SA, Jadhav PA, Kurhade AS, Wakchaure GN. Effect of transformed-induced plasticity steel plate thickness on ultimate tensile strength of butt welded joint using Nd: YAG Laser. Int J Veh Struct Syst. 2024; 31:16(6). https://doi.org/10.4273/ijvss.16.6.08
88. Yadav RS, Gandhi P, Veeranjaneyulu K, Gaji R, Kirpekar S, Pawar D, Khairnar YS, Patil S, Kurhade AS, Patil SP. Influence of plate thickness on the mechanical behaviour of mild steel curved plates: An experimental study. J Mines Met Fuels. 2024; 1319-1327. https://doi.org/10.18311/jmmf/2024/46253
89. Deshpande SV, Pawar RS, Keche AJ, Kurhade A. Absolute time surface finish measurement of stepped holding shaft by automatic system. J Adv Manuf Syst. 2025; 17.
90. Yadav RS, Nimbalkar A, Gadekar T, Patil P, Patil VN, Gholap AB, Kurhade AS, Dhumal JR, Waware SY. Comparison of experimental and numerical investigation of mono-composite and metal leaf spring. J Mines Met Fuels. 2024; 815-827. https://doi.org/10.18311/jmmf/2024/45325